




ORE RESEARCH & EXPLORATION P/L · ABN 28 006 859 856
37A Hosie St · Bayswater North · VIC · 3153 · AUSTRALIA
☎ 61 3 9729 0333 ☎ 61 3 9729 8338
📧 info@ore.com.au 🌐 www.ore.com.au

CERTIFICATE OF ANALYSIS FOR

Copper Sulphide Ore (Tritton Cu Project, NSW)

CERTIFIED REFERENCE MATERIAL

OREAS 111



COA-724-OREAS111-R1

Printed: 03-Sep-2018

Table 1. Certified Values, SDs, 95% Confidence and Tolerance Limits for OREAS 111.

Constituent	Certified Value	95% Confidence Interval		Tolerance Interval 1- α =0.99, ρ =0.95	
		Low	High	Low	High
Peroxide Fusion					
Silver, Ag (ppm)	<20	IND	IND	IND	IND
Arsenic, As (ppm)	217	188	245	208	225
Cadmium, Cd (ppm)	14	12	17	IND	IND
Cobalt, Co (ppm)	457	436	478	440	475
Copper, Cu (wt.%)	2.30	2.21	2.39	2.21	2.39
Iron, Fe (wt.%)	34.1	31.2	36.9	33.3	34.8
Lead, Pb (ppm)	375	356	393	351	398
Antimony, Sb (ppm)	19	14	24	16	22
Zinc, Zn (ppm)	4099	3893	4304	4040	4158
Acid Digest					
Silver, Ag (ppm)	10.1	9.6	10.6	9.5	10.6
Arsenic, As (ppm)	215	201	229	202	228
Cadmium, Cd (ppm)	12.0	10.7	13.3	11.6	12.5
Cobalt, Co (ppm)	452	437	467	441	463
Copper, Cu (wt.%)	2.37	2.30	2.44	2.33	2.42
Iron, Fe (wt.%)	35.2	33.8	36.6	34.2	36.3
Lead, Pb (ppm)	377	359	395	364	390
Antimony, Sb (ppm)	18	15	21	17	19
Zinc, Zn (ppm)	4196	4049	4342	4065	4326

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

Note: intervals may appear asymmetric due to rounding

Table 2. Indicative Values for OREAS 111.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Oxidising Fusion XRF								
Al ₂ O ₃	wt.%	0.745	Fe ₂ O ₃	wt.%	51.45	SnO ₂	ppm	25.4
As	ppm	230	K ₂ O	wt.%	0.015	SO ₃	wt.%	99.29
BaO	ppm	22.3	MgO	wt.%	0.218	SrO	ppm	23.7
CaO	wt.%	0.158	MnO	wt.%	0.011	TiO ₂	wt.%	0.040
Cl	ppm	< 10	NiO	ppm	51	V ₂ O ₅	ppm	71
CoO	ppm	617	P ₂ O ₅	wt.%	0.050	ZnO	ppm	5533
Cr ₂ O ₃	ppm	51	PbO	ppm	393	ZrO ₂	ppm	13.5
CuO	ppm	30419	SiO ₂	wt.%	18.20			
Thermogravimetry								
LOI ¹⁰⁰⁰	wt.%	26.52						
Laser Ablation ICP-MS								
Ag	ppm	9.00	Hf	ppb	175	Sn	ppm	7.60
As	ppm	216	Ho	ppb	80.0	Sr	ppm	6.65
Ba	ppm	5.25	In	ppm	1.25	Ta	ppb	50.0
Be	ppm	0.20	La	ppm	1.69	Tb	ppb	55.0
Bi	ppm	5.70	Lu	ppb	25.0	Te	ppb	1900
Cd	ppm	15.0	Mo	ppm	28.7	Th	ppm	0.77

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

Table 2. Indicative Values for OREAS 111 continued.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Laser Ablation ICP-MS								
Ce	ppm	3.26	Nb	ppm	0.42	Tl	ppm	3.60
Co	ppm	475	Nd	ppm	1.51	Tm	ppb	20.0
Cr	ppm	30.0	Ni	ppm	34.0	U	ppm	3.95
Cs	ppm	0.26	Pb	wt.%	0.037	V	ppm	41.6
Cu	ppm	23800	Pr	ppm	0.32	W	ppm	3.28
Dy	ppm	0.39	Rb	ppm	0.55	Y	ppm	1.81
Er	ppm	0.16	Re	ppb	55.0	Yb	ppb	160
Eu	ppb	95.0	Sb	ppm	21.0	Zn	ppm	4320
Ga	ppm	2.05	Sc	ppm	0.30	Zr	ppm	5.25
Gd	ppm	0.42	Se	ppm	< 5			
Ge	ppb	200	Sm	ppm	0.31			
Infrared Combustion								
C	wt.%	0.120	S	wt.%	37.25			

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

INTRODUCTION

OREAS reference materials are intended to provide a low cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

OREAS reference materials enable users to successfully achieve process control of these tasks because the observed variance from repeated analysis has its origin almost exclusively in the analytical process rather than the reference material itself.

SOURCE MATERIAL

OREAS 111 is a medium grade Cu ore certified reference material (CRM) prepared from material sourced from the Tritton Copper Project near Nyngan, New South Wales. The deposit consists of sulphide ore bodies (massive pyrite and chalcopyrite breccias) underlying oxide ores. The mineralisation is interpreted as stratiform "Besshi style" volcanic-hosted massive sulphide, within Ordovician turbidite metasediments and mafic volcanics. OREAS 111 has a pigeon pair with OREAS 111b which is ~4% higher in Cu grade. OREAS 111 is one of a suite of five CRMs and was prepared from massive pyrite ore material. All five CRMs have been characterised for Ag, As, Cd, Co, Cu, Fe, Pb, Sb and Zn by 4-acid ICP and sodium peroxide fusion ICP methods.

COMMUNITION AND HOMOGENISATION PROCEDURES

The material was prepared in the following manner:

- Drying at 65°C to constant mass;
- Crushing and screening;
- Multi-stage milling to 100% minus 35 microns;
- Final homogenisation;
- Packaging into 10g units sealed under nitrogen in laminated foil pouches.

ANALYTICAL PROGRAM

Ten commercial laboratories participated in the analytical program to characterise Ag, As, Cd, Co, Cu, Fe, Pb, Sb and Zn. Their results together with uncorrected means, medians, one sigma standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in Tables A2 and A19 (Appendix). The parameter PDM³ is a measure of laboratory accuracy while the relative standard deviation is an effective measure of analytical precision where homogeneity of the test material has been confirmed.

The approximate major and trace element composition of OREAS 111 is provided in Table 2. The non-certified values contained in this table are the means of duplicate assays from one laboratory.

The analytical methods employed by each laboratory are explained, together with other abbreviations used, in Table A1 (Appendix).

Each participating laboratory received 5 samples of 30g each. Each set of subsamples submitted to each laboratory was taken at regular intervals during packaging of the standard in order to maximise their representation. All ten laboratories reported 4-acid data for the requested elements while eight included sodium peroxide fusion results. Laboratories were instructed to assay samples as received.

STATISTICAL EVALUATION

Certified Value and Confidence Intervals

The certified value is the mean of means of accepted replicate values of accepted participating laboratories computed according to the formulae

$$\bar{x}_i = \frac{1}{n_i} \sum_{j=1}^{n_i} x_{ij} \qquad \ddot{x} = \frac{1}{p} \sum_{i=1}^p \bar{x}_i$$

where,

x_{ij} is the j th result reported by laboratory i ;

p is the number of participating laboratories;

n_i is the number of results reported by laboratory i ;

\bar{x}_i is the mean for laboratory i ;

\ddot{x} is the mean of means.

The confidence intervals are obtained by calculation of the variance (\hat{V}) of the consensus value (\bar{x}) (mean of means) and reference to Student's-*t* distribution with degrees of freedom ($p-1$).

$$\hat{V}(\bar{x}) = \frac{1}{p(p-1)} \sum_{i=1}^p (\bar{x}_i - \bar{x})^2$$

$$\text{Confidence Interval} = \bar{x} \pm t_{1-x/2}(p-1)(\hat{V}(\bar{x}))^{1/2}$$

where,

$t_{1-x/2}(p-1)$ is the $1-x/2$ fractile of the *t*-distribution with $(p-1)$ degrees of freedom.

The distribution of the values is assumed to be symmetrical about the mean in the calculation of the confidence interval. The test for rejection of individual outliers from each laboratory data set is based on *z* scores (rejected if $|z_i| > 2.5$) computed from the robust estimators of location and scale, *T* and *S*, respectively, according to the formulae

$$S = 1.483 \frac{\text{median } |x_j - \text{median}(x_i)|}{j=1, \dots, n \quad i=1, \dots, n}$$

$$z_i = \frac{x_i - T}{S}$$

where,

T is the median value in a data set;

S is the median of all absolute deviations from the sample median multiplied by 1.483, a correction factor to make the estimator consistent with the usual parameter of a normal distribution.

The *z*-score test is used in combination with a second method of individual outlier detection that determines the percent deviation of the individual value from the median. Outliers in general are selected on the basis of *z*-scores > 2.5 and with percent deviations $> 1.5\%$. In certain instances statistician's prerogative has been employed in discriminating outliers.

Each laboratory data set is tested for outlying status based on *z*-score discrimination and rejected if $|z_i| > 2.5$. After individual and lab data set outliers have been eliminated a non-iterative 3 standard deviation filter is applied, with those values lying outside this window also relegated to outlying status.

Individual outliers and, more rarely, laboratory means deemed to be outlying are shown left justified and in bold in the tabulated results (see Appendix) and have been omitted in the determination of certified values.

The magnitude of the confidence interval is inversely proportional to the number of participating laboratories and interlaboratory agreement. It is a measure of the reliability of the certified value, i.e. the narrower the confidence interval the greater the certainty in the certified value. A 95% confidence interval indicates a 95% probability that the interval includes the true value of the analyte under consideration.

Indicative (uncertified) values

The indicative (uncertified) values (Table 2) are provided for the major and trace elements determined by oxidising fusion XRF (Al_2O_3 to ZrO_2), LOI at 1000°C and laser ablation with ICP-MS (Ag to Zr) and are the means of duplicate assays from Bureau Veritas, Perth.

Additional indicative values by other analytical methods are present where the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification or where inter-laboratory consensus is poor.

Statement of Homogeneity

The standard deviation of each laboratory data set includes error due to both the imprecision of the analytical method employed and to possible inhomogeneity of the material analysed. The standard deviation of the pooled individual analyses of all participating laboratories includes error due to the imprecision of each analytical method, to possible inhomogeneity of the material analysed and, in particular, to deficiencies in accuracy of each analytical method.

In determining tolerance intervals that component of error attributable to measurement inaccuracy was eliminated by transformation of the individual results of each data set to a common mean (the uncorrected grand mean) according to the formula

$$x'_{ij} = x_{ij} - \bar{x}_i + \frac{\sum_{i=1}^p \sum_{j=1}^{n_i} x_{ij}}{\sum_{i=1}^p n_i}$$

where,

x_{ij} is the j th raw result reported by laboratory i ;

x'_{ij} is the j th transformed result reported by laboratory i ;

n_i is the number of results reported by laboratory i ;

p is the number of participating laboratories;

\bar{x}_i is the raw mean for laboratory i .

The homogeneity of each constituent was determined from tables of factors for two-sided tolerance limits for normal distributions (ISO 3207) in which

$$\text{Lower limit is } \bar{x} - k'_2(n, p, 1 - \alpha) s_g''$$

$$\text{Upper limit is } \bar{x} + k'_2(n, p, 1 - \alpha) s_g''$$

where,

n is the number of results;

$1 - \alpha$ is the confidence level;

p is the proportion of results expected within the tolerance limits;

k'_2 is the factor for two-sided tolerance limits (m, α unknown);

s_g'' is the corrected grand standard deviation.

The meaning of these tolerance limits may be illustrated for Cu by 4-acid digest, where 99% of the time at least 95% of subsamples will have concentrations lying between 0.156 and 0.168 wt.%. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

The corrected grand standard deviation, s_g'' , used to compute the tolerance intervals is the weighted means of standard deviations of all data sets for a particular constituent according to the formula:

$$s_g'' = \frac{\sum_{i=1}^p (s_i (1 - \frac{s_i}{s_g'}))}{\sum_{i=1}^p (1 - \frac{s_i}{s_g'})}$$

where,

$1 - (\frac{s_i}{s_g'})$ is the weighting factor for laboratory i ;

s_g' is the grand standard deviation computed from the transformed (i.e. means -adjusted) results

according to the formula

$$s_g' = \left[\frac{\sum_{i=1}^p \sum_{j=i}^{n_i} (x'_{ij} - \bar{x}'_i)^2}{\sum_{i=1}^p n_i - 1} \right]^{1/2}$$

where \bar{x}'_i is the transformed mean for laboratory i

The weighting factors were applied to compensate for the considerable variation in analytical precision amongst participating laboratories. Hence, weighting factors for each data set have been constructed so as to be inversely proportional to the standard deviation of that data set. It should be noted that estimates of tolerance by this method are considered conservative as a significant proportion of the observed variance, even in those laboratories exhibiting the best analytical precision, can presumably be attributed to measurement error.

Performance Gates

Performance gates provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. Sources of measurement error include inter-lab bias, analytical precision (repeatability) and inter-batch bias (reproducibility).

Two methods have been employed to calculate performance gates. The first method uses the same filtered data set used to determine the certified value, i.e. after removal of all individual, lab dataset (batch) and 3SD outliers. These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. The standard deviation is then calculated for each analyte from the pooled individual analyses generated from the certification program. Table 3 shows performance gates calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application

should be at the discretion of the QC manager concerned. A second method utilises a 5% window calculated directly from the certified value. Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow.

Table 3. Performance Gates for OREAS 111.

Constituent	Certified Value	1SD	2SD window		3SD window		Relative Standard Deviations			5% window	
			Low	High	Low	High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion											
Silver, Ag (ppm)	<20	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Arsenic, As (ppm)	217	20	176	257	156	278	9.40%	18.8%	28.2%	206	228
Cadmium, Cd (ppm)	14	1	12	16	11	18	7.24%	14.5%	21.7%	14	15
Cobalt, Co (ppm)	457	9	438	476	429	485	2.05%	4.11%	6.16%	434	480
Copper, Cu (wt.%)	2.30	0.12	2.07	2.53	1.95	2.65	5.01%	10.0%	15.0%	2.18	2.41
Iron, Fe (wt.%)	34.1	3.4	27.3	40.8	23.9	44.2	9.92%	19.8%	29.8%	32.4	35.8
Lead, Pb (ppm)	375	12	350	399	338	412	3.26%	6.52%	9.79%	356	394
Antimony, Sb (ppm)	19	3	13	25	10	28	15.2%	30.5%	45.7%	18	20
Zinc, Zn (ppm)	4099	249	3600	4598	3350	4847	6.09%	12.2%	18.3%	3894	4304
Acid Digest											
Silver, Ag (ppm)	10.1	0.9	8.3	11.8	7.5	12.7	8.58%	17.2%	25.7%	9.6	10.6
Arsenic, As (ppm)	215	15	185	245	170	260	6.94%	13.9%	20.8%	204	226
Cadmium, Cd (ppm)	12.0	1.7	8.6	15.5	6.8	17.2	14.4%	28.9%	43.3%	11.4	12.6
Cobalt, Co (ppm)	452	20	412	492	391	512	4.44%	8.88%	13.3%	429	474
Copper, Cu (wt.%)	2.37	0.11	2.16	2.58	2.06	2.69	4.43%	8.86%	13.3%	2.25	2.49
Iron, Fe (wt.%)	35.2	2.0	31.2	39.2	29.3	41.2	5.66%	11.3%	17.0%	33.5	37.0
Lead, Pb (ppm)	377	26	324	430	298	456	7.01%	14.0%	21.0%	358	396
Antimony, Sb (ppm)	18	3	12	23	10	26	15.2%	30.5%	45.7%	17	19
Zinc, Zn (ppm)	4196	228	3741	4651	3513	4878	5.42%	10.8%	16.3%	3986	4405

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

Note: intervals may appear asymmetric due to rounding

PARTICIPATING LABORATORIES

1. Acme Analytical Laboratories Ltd, Vancouver, BC, Canada
2. Activation Laboratories, Ancaster, Ontario, Canada
3. ALS Chemex, Brisbane, QLD, Australia
4. ALS Chemex, Vancouver, BC, Canada
5. Amdel Laboratories, Perth, WA, Australia
6. Bureau Veritas (Ultra Trace) Geoanalytical, Perth, WA, Australia
7. Genalysis Laboratory Services Pty Ltd, Perth, WA, Australia
8. Intertek Testing Services, Jakarta, Indonesia
9. OMAC Laboratories Ltd, Loughrea, County Galway, Ireland
10. SGS Australia, Perth, WA, Australia

PREPARER AND SUPPLIER OF THE REFERENCE MATERIAL

Reference material OREAS 111 has been prepared and certified by:



ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.ore.com.au
Email: info@ore.com.au

OREAS 111 available in 10g units sealed under a nitrogen environment in laminated foil pouches.

INTENDED USE

OREAS 111 is a reference material intended for the following:

- i) For the monitoring of laboratory performance in the analysis of Ag, As, Cd, Co, Cu, Fe, Pb, Sb and Zn in geological samples;
- ii) For the calibration of instruments used in the determination of the concentration of Ag, As, Cd, Co, Cu, Fe, Pb, Sb and Zn;
- iii) For the verification of analytical methods for Ag, As, Cd, Co, Cu, Fe, Pb, Sb and Zn.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 111 is a reference material made from medium grade copper sulphide ore from the Tritton Copper Mine. In its unopened state in the nitrogen-purged laminated foil pouches and under normal conditions of storage it has a shelf life beyond five years.

INSTRUCTIONS FOR THE CORRECT USE

The certified values for OREAS 111 refer to the concentration level of Ag, As, Cd, Co, Cu, Fe, Pb, Sb and Zn in its packaged state. The CRM should not be dried prior to weighing and analysis.

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions such as the use of safety glasses and dust masks are advised.

METROLOGICAL TRACEABILITY

The analytical samples were selected in a manner to represent the entire batch of prepared CRM. This 'representivity' was maintained in each submitted laboratory sample batch and ensures the user that the data is traceable from sample selection through to the analytical results that underlie the consensus values. Each analytical data set has been validated by its assayer through the inclusion of internal reference materials and QC checks during analysis.

The laboratories were chosen on the basis of their competence (from past performance in inter-laboratory programs undertaken by ORE Pty Ltd) for a particular analytical method, analyte or analyte suite, and sample matrix. Most of these laboratories have and maintain ISO 17025 accreditation. The certified values presented in this report are calculated from the means of accepted data following robust statistical treatment as detailed in this report.

Guide ISO/TR 16476:2016, section 5.3.1 describes metrological traceability in reference materials as it pertains to the transformation of the measurand. In this section it states, *“Although the determination of the property value itself can be made traceable to appropriate units through, for example, calibration of the measurement equipment used, steps like the transformation of the sample from one physical (chemical) state to another cannot. Such transformations may only be compared with a reference (when available), or among themselves. For some transformations, reference methods have been defined and may be used in certification projects to evaluate the uncertainty associated with such a transformation. In other cases, **only a comparison among different laboratories using the same method is possible. In this case, certification takes place on the basis of agreement among independent measurement results** (see ISO Guide 35:2006, Clause 10).”*

COMMUTABILITY

The measurements of the results that underlie the certified values contained in this report were undertaken by methods involving pre-treatment (digestion/fusion) of the sample. This served to reduce the sample to a simple and well understood form permitting calibration using simple solutions of the CRM. Due to these methods being well understood and highly effective, commutability is not an issue for this CRM. All OREAS CRMs are sourced from natural ore minerals meaning they will display similar behaviour as routine ‘field’ samples in the relevant measurement process. Care should be taken to ensure ‘matrix matching’ as close as practically achievable. The matrix and mineralisation style of the CRM is described in the ‘Source Material’ section and users should select appropriate CRMs matching these attributes to their field samples.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

DOCUMENT HISTORY

Revision No	Date	Changes applied
1	3 rd Sep, 2018	Added major and trace element characterisation
0	7 th Aug, 2012	First publication

QMS ACCREDITED

ORE Pty Ltd is accredited to ISO 9001:2015 by Lloyd's Register Quality Assurance Ltd for its quality management system including development, manufacturing, certification and supply of CRMs.



CERTIFYING OFFICER

A handwritten signature in blue ink, appearing to read 'S. Hamlyn'.

3rd Sep, 2018

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

REFERENCES

ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.

ISO Guide 30 (2015), Terms and definitions used in connection with reference materials.

ISO Guide 31 (2015), Reference materials – Contents of certificates and labels.

ISO Guide 35 (2017), Certification of reference materials - General and statistical principals.

APPENDIX

Analytical Data for OREAS 111

Table A1. Explanation of abbreviations used in Tables A2 – A11.

Abbreviation	Explanation
Std.Dev.	one standard deviation
Rel.Std.Dev.	one relative standard deviation (%)
PDM ³	percent deviation of lab mean from corrected mean of means
NR	not reported
4A	four acid digest (HF-HNO ₃ -HClO ₄ -HCl)
MAR	modified aqua regia digest
PF	sodium peroxide fusion
AAS	atomic absorption spectrometry
OES	inductively coupled plasma optical emission spectrometry
MS	inductively coupled plasma mass spectrometry

Table A2. Fusion results for Ag in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*MS	Lab C PF*MS	Lab D PF*MS	Lab E -	Lab F -	Lab G -	Lab H -	Lab I PF*OES	Lab J -
1	<10	10.0	9.0	14.0	NR	NR	NR	NR	25.0	NR
2	<10	10.0	10.0	14.0	NR	NR	NR	NR	23.0	NR
3	<10	10.0	9.0	16.0	NR	NR	NR	NR	<20	NR
4	<10	5.0	10.0	14.0	NR	NR	NR	NR	22.0	NR
5	<10	5.0	9.0	15.0	NR	NR	NR	NR	21.0	NR
Mean		8.0	9.4	14.6					22.8	
Median		10.0	9.0	14.0					22.5	
Std.Dev.		2.7	0.5	0.9					1.7	
Rel.Std.Dev.		34.2%	5.83%	6.13%					7.51%	
PDM ³		-41.6%	-31.3%	6.67%					66.2%	

Table A3. Fusion results for As in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*MS	Lab C PF*MS	Lab D PF*MS	Lab E -	Lab F -	Lab G PF*OES	Lab H -	Lab I PF*OES	Lab J -
1	214	235	214	240	NR	NR	200	NR	123	NR
2	188	240	215	240	NR	NR	200	NR	113	NR
3	190	240	219	250	NR	NR	200	NR	<100	NR
4	277	250	213	280	NR	NR	200	NR	<100	NR
5	190	230	215	230	NR	NR	200	NR	105	NR
Mean	212	239	215	248			200		114	
Median	190	240	215	240			200		113	
Std.Dev.	38	7	2	19			0		9	
Rel.Std.Dev.	17.9%	3.10%	1.06%	7.76%			0.00%		7.93%	
PDM ³	-2.26%	10.3%	-0.70%	14.4%			-7.71%		-47.5%	

Table A4. Fusion results for Cd in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*MS	Lab C PF*MS	Lab D PF*MS	Lab E -	Lab F -	Lab G -	Lab H -	Lab I PF*OES	Lab J -
1	14.0	10.0	14.0	18.2	NR	NR	NR	NR	<50	NR
2	14.0	10.0	13.0	17.1	NR	NR	NR	NR	<50	NR
3	14.0	10.0	14.0	14.9	NR	NR	NR	NR	<50	NR
4	14.0	<10	14.0	15.1	NR	NR	NR	NR	<50	NR
5	13.0	<10	14.0	15.4	NR	NR	NR	NR	<50	NR
Mean	13.8	10.0	13.8	16.1						
Median	14.0	10.0	14.0	15.4						
Std.Dev.	0.4	0.0	0.4	1.4						
Rel.Std.Dev.	3.24%	0.00%	3.24%	8.94%						
PDM ³	-4.22%	-30.6%	-4.22%	12.0%						

Table A5. Fusion results for Co in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*OES	Lab C NR	Lab D PF*MS	Lab E -	Lab F -	Lab G PF*OES	Lab H -	Lab I PF*OES	Lab J -
1	443	480	NR	465	NR	NR	460	NR	NR	NR
2	448	520	NR	450	NR	NR	460	NR	NR	NR
3	450	500	NR	470	NR	NR	450	NR	NR	NR
4	447	520	NR	465	NR	NR	460	NR	NR	NR
5	453	500	NR	476	NR	NR	460	NR	NR	NR
Mean	448	504		465			458			
Median	448	500		465			460			
Std.Dev.	4	17		10			4			
Rel.Std.Dev.	0.83%	3.32%		2.07%			0.98%			
PDM ³	-1.95%	10.3%		1.76%			0.19%			

Table A6. Fusion results for Cu in OREAS 111 (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A PF*OES	Lab B PF*OES	Lab C PF*OES	Lab D PF*OES	Lab E PF*OES	Lab F PF*OES	Lab G PF*OES	Lab H -	Lab I PF*OES	Lab J -
1	2.09	2.46	2.42	2.25	2.39	2.24	2.26	NR	2.37	NR
2	2.18	2.46	2.41	2.28	2.20	2.22	2.32	NR	2.24	NR
3	2.19	2.41	2.47	2.31	2.30	2.18	2.28	NR	2.30	NR
4	2.14	2.43	2.46	2.44	2.24	2.10	2.32	NR	2.27	NR
5	2.06	2.47	2.41	2.53	2.34	2.19	2.30	NR	2.14	NR
Mean	2.13	2.45	2.43	2.36	2.29	2.19	2.30		2.26	
Median	2.14	2.46	2.42	2.31	2.30	2.19	2.30		2.27	
Std.Dev.	0.06	0.03	0.03	0.12	0.08	0.05	0.03		0.08	
Rel.Std.Dev.	2.64%	1.03%	1.23%	5.02%	3.31%	2.45%	1.14%		3.64%	
PDM ³	-7.30%	6.35%	5.81%	2.70%	-0.26%	-4.96%	-0.17%		-1.63%	

Table A7. Fusion results for Fe in OREAS 111 (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A PF*OES	Lab B PF*OES	Lab C PF*OES	Lab D PF*OES	Lab E PF*OES	Lab F PF*OES	Lab G PF*OES	Lab H -	Lab I PF*OES	Lab J -
1	34.1	36.0	38.1	38.5	32.1	32.7	33.4	NR	29.7	NR
2	34.0	37.0	37.9	36.3	31.1	31.6	33.6	NR	29.2	NR
3	33.5	37.1	37.6	36.9	31.4	31.2	32.8	NR	29.8	NR
4	33.8	37.5	37.6	39.9	31.3	31.4	33.2	NR	28.2	NR
5	33.6	37.0	37.2	41.4	32.2	31.4	33.3	NR	27.9	NR
Mean	33.8	36.9	37.7	38.6	31.6	31.7	33.3		28.9	
Median	33.8	37.0	37.6	38.5	31.4	31.4	33.3		29.2	
Std.Dev.	0.3	0.6	0.3	2.1	0.5	0.6	0.3		0.9	
Rel.Std.Dev.	0.75%	1.50%	0.86%	5.45%	1.57%	1.89%	0.89%		2.97%	
PDM ³	-0.76%	8.40%	10.7%	13.3%	-7.14%	-7.05%	-2.35%		-15.0%	

Table A8. Fusion results for Pb in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*MS	Lab C PF*MS	Lab D PF*MS	Lab E -	Lab F -	Lab G PF*OES	Lab H -	Lab I PF*OES	Lab J -
1	369	370	383	383	NR	NR	300	NR	NR	NR
2	366	370	375	391	NR	NR	300	NR	NR	NR
3	358	370	369	383	NR	NR	200	NR	NR	NR
4	362	360	419	389	NR	NR	300	NR	NR	NR
5	371	360	388	402	NR	NR	300	NR	NR	NR
Mean	365	366	387	390			280			
Median	366	370	383	389			300			
Std.Dev.	5	5	19	8			45			
Rel.Std.Dev.	1.44%	1.50%	5.02%	2.00%			16.0%			
PDM ³	-2.58%	-2.37%	3.18%	3.92%			-25.3%			

Table A9. Fusion results for Sb in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*MS	Lab C PF*MS	Lab D PF*MS	Lab E -	Lab F -	Lab G -	Lab H -	Lab I PF*OES	Lab J -
1	16	20	19	21	NR	NR	NR	NR	110	NR
2	15	20	18	23	NR	NR	NR	NR	107	NR
3	15	20	18	22	NR	NR	NR	NR	59	NR
4	14	20	19	24	NR	NR	NR	NR	91	NR
5	14	20	19	23	NR	NR	NR	NR	141	NR
Mean	15	20	19	22					102	
Median	15	20	19	23					107	
Std.Dev.	1	0	1	1					30	
Rel.Std.Dev.	5.65%	0.00%	2.68%	3.66%					29.4%	
PDM ³	-22.1%	5.26%	-1.26%	18.1%					435%	

Table A10. Fusion results for Zn in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A PF*OES	Lab B PF*OES	Lab C PF*OES	Lab D PF*OES	Lab E -	Lab F PF*OES	Lab G PF*OES	Lab H -	Lab I PF*OES	Lab J -
1	4100	4340	4424	4290	4000	4300	4000	NR	3756	NR
2	4100	4340	4416	3960	3800	4200	4000	NR	3737	NR
3	4100	4340	4445	3930	3900	4100	4000	NR	3589	NR
4	4100	4420	4417	4290	3900	4100	4000	NR	3563	NR
5	4100	4320	4395	4470	4000	4100	4000	NR	3605	NR
Mean	4100	4352	4419	4188	3920	4160	4000		3650	
Median	4100	4340	4417	4290	3900	4100	4000		3605	
Std.Dev.	0	39	18	234	84	89	0		90	
Rel.Std.Dev.	0.00%	0.90%	0.41%	5.59%	2.13%	2.15%	0.00%		2.46%	
PDM ³	0.03%	6.18%	7.83%	2.18%	-4.36%	1.50%	-2.41%		-10.9%	

Table A11. 4-acid results for Ag in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*MS	Lab B 4A*MS	Lab C 4A*MS	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	10.0	11.0	10.0	10.0	10.0	11.0	8.2	9.5	10.0	9.7
2	10.0	10.0	10.0	11.0	8.0	11.0	8.9	9.3	10.9	9.4
3	10.0	10.5	10.0	12.0	8.0	9.0	8.3	9.5	10.5	9.6
4	10.0	10.5	10.0	12.0	9.0	10.0	7.7	9.4	9.1	10.0
5	10.0	10.5	10.0	12.0	11.0	9.0	8.1	9.4	10.3	9.7
Mean	10.0	10.5	10.0	11.4	9.2	10.0	8.2	9.4	10.1	9.7
Median	10.0	10.5	10.0	12.0	9.0	10.0	8.2	9.4	10.3	9.7
Std.Dev.	0.0	0.4	0.0	0.9	1.3	1.0	0.4	0.1	0.7	0.2
Rel.Std.Dev.	0.00%	3.37%	0.00%	7.85%	14.2%	10.0%	5.26%	0.89%	6.74%	2.40%
PDM ³	-0.68%	4.28%	-0.68%	13.2%	-8.63%	-0.68%	-18.2%	-6.44%	0.67%	-3.70%

Table A12. 4-acid results for As in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*MS	Lab B 4A*MS	Lab C 4A*MS	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	160	240	238	NR	<200	190	196	204	214	214
2	170	230	232	NR	<200	220	228	201	207	208
3	150	230	236	NR	<200	200	196	200	221	210
4	170	240	222	NR	<200	220	192	204	205	218
5	160	230	238	NR	<200	220	201	208	212	211
Mean	162	234	233			210	203	203	212	212
Median	160	230	236			220	196	204	212	211
Std.Dev.	8	5	7			14	15	3	6	4
Rel.Std.Dev.	5.16%	2.34%	2.88%			6.73%	7.18%	1.54%	2.97%	1.94%
PDM ³	-24.6%	8.93%	8.56%			-2.24%	-5.68%	-5.31%	-1.40%	-1.21%

Table A13. 4-acid results for Cd in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*MS	Lab B 4A*MS	Lab C 4A*MS	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	10.0	13.5	15.0	12.3	10.0	10.0	11.2	13.0	13.7	11.0
2	10.0	13.0	14.0	13.9	10.0	10.0	11.5	13.0	13.7	11.0
3	10.0	13.5	15.0	13.5	10.0	10.0	11.4	13.0	14.0	11.1
4	10.0	13.0	15.0	12.9	10.0	20.0	11.0	13.0	13.6	10.9
5	10.0	13.0	15.0	13.8	10.0	10.0	10.9	13.0	13.9	11.6
Mean	10.0	13.2	14.8	13.3	10.0	12.0	11.2	13.0	13.8	11.1
Median	10.0	13.0	15.0	13.5	10.0	10.0	11.2	13.0	13.7	11.0
Std.Dev.	0.0	0.3	0.4	0.7	0.0	4.5	0.3	0.0	0.2	0.3
Rel.Std.Dev.	0.00%	2.07%	3.02%	5.06%	0.00%	37.3%	2.28%	0.00%	1.21%	2.46%
PDM ³	-16.8%	9.77%	23.1%	10.4%	-16.8%	-0.21%	-6.86%	8.10%	14.6%	-7.57%

Table A14. 4-acid results for Co in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*MS	Lab B 4A*OES	Lab C 4A*MS	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	490	505	499	407	450	440	438	451	463	458
2	480	495	504	449	450	460	439	440	463	441
3	500	500	505	453	460	440	422	444	474	445
4	480	510	500	424	440	480	406	439	472	459
5	480	500	511	446	450	440	412	445	465	453
Mean	486	502	504	436	450	452	423	444	467	451
Median	480	500	504	446	450	440	422	444	465	453
Std.Dev.	9	6	5	20	7	18	15	5	5	8
Rel.Std.Dev.	1.84%	1.14%	0.95%	4.51%	1.57%	3.96%	3.53%	1.07%	1.12%	1.77%
PDM ³	7.61%	11.2%	11.5%	-3.51%	-0.36%	0.08%	-6.25%	-1.74%	3.49%	-0.09%

Table A15. 4-acid results for Cu in OREAS 111 (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A 4A*OES	Lab B 4A*OES	Lab C 4A*OES	Lab D 4A*AAAS	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	2.30	2.43	2.52	2.25	2.38	2.42	2.27	2.25	2.40	2.31
2	2.26	2.40	2.53	2.26	2.37	2.51	2.40	2.22	2.43	2.21
3	2.36	2.44	2.51	2.24	2.42	2.45	2.37	2.22	2.48	2.24
4	2.44	2.45	2.54	2.22	2.33	2.61	2.38	2.19	2.44	2.31
5	2.30	2.44	2.57	2.22	2.37	2.40	2.36	2.23	2.42	2.31
Mean	2.33	2.43	2.53	2.24	2.37	2.48	2.36	2.22	2.43	2.27
Median	2.30	2.44	2.53	2.24	2.37	2.45	2.37	2.22	2.43	2.31
Std.Dev.	0.07	0.02	0.02	0.02	0.03	0.08	0.05	0.02	0.03	0.05
Rel.Std.Dev.	3.01%	0.79%	0.94%	0.80%	1.40%	3.42%	2.13%	0.98%	1.25%	2.16%
PDM ³	-1.72%	2.49%	6.74%	-5.68%	-0.02%	4.43%	-0.71%	-6.36%	2.55%	-4.13%

Table A16. 4-acid results for Fe in OREAS 111 (abbreviations as in Table A1; values in wt.%).

Replicate No.	Lab A 4A*MS	Lab B 4A*OES	Lab C 4A*OES	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*AAS	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	35.0	37.5	38.1	33.0	34.9	33.7	33.0	34.3	36.2	34.3
2	34.4	36.7	38.1	37.3	34.7	34.9	32.7	33.8	36.3	33.4
3	35.7	37.2	37.5	41.0	35.5	34.1	31.3	34.1	37.3	33.4
4	35.9	36.9	37.9	36.2	34.3	36.0	30.4	34.3	37.0	34.8
5	33.1	36.9	38.7	37.7	34.4	32.7	30.4	34.3	36.2	34.0
Mean	34.8	37.0	38.1	37.0	34.7	34.3	31.6	34.2	36.6	34.0
Median	35.0	36.9	38.1	37.3	34.7	34.1	31.3	34.3	36.3	34.0
Std.Dev.	1.1	0.3	0.5	2.9	0.5	1.2	1.2	0.2	0.5	0.6
Rel.Std.Dev.	3.25%	0.85%	1.20%	7.78%	1.36%	3.63%	3.92%	0.64%	1.38%	1.71%
PDM ³	-1.17%	5.13%	8.05%	5.13%	-1.38%	-2.71%	-10.4%	-3.05%	3.89%	-3.54%

Table A17. 4-acid results for Pb in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*MS	Lab B 4A*MS	Lab C 4A*MS	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	370	368	379	339	400	470	338	403	410	351
2	370	365	379	386	400	420	337	395	400	344
3	380	371	376	381	400	380	323	401	410	346
4	370	375	392	366	400	410	312	395	400	359
5	350	368	391	392	400	370	315	401	400	351
Mean	368	369	383	373	400	410	325	399	404	350
Median	370	368	379	381	400	410	323	401	400	351
Std.Dev.	11	4	8	21	0	39	12	4	5	6
Rel.Std.Dev.	2.98%	1.02%	1.96%	5.69%	0.00%	9.60%	3.72%	0.94%	1.36%	1.67%
PDM ³	-2.38%	-2.01%	1.70%	-1.11%	6.11%	8.76%	-13.8%	5.84%	7.17%	-7.12%

Table A18. 4-acid results for Sb in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*MS	Lab B 4A*MS	Lab C 4A*MS	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	30.0	20.6	17.6	NR	<100	<50	17.0	20.0	<50	17.6
2	30.0	19.0	17.5	NR	<100	<50	17.0	20.0	<50	16.5
3	30.0	20.0	17.8	NR	<100	<50	9.0	21.0	<50	16.2
4	30.0	20.0	18.0	NR	<100	<50	12.0	21.0	<50	15.0
5	30.0	20.2	18.8	NR	<100	<50	12.0	22.0	<50	15.7
Mean	30.0	20.0	17.9				13.4	20.8		16.2
Median	30.0	20.0	17.8				12.0	21.0		16.2
Std.Dev.	0.0	0.6	0.5				3.5	0.8		1.0
Rel.Std.Dev.	0.00%	2.96%	2.89%				26.2%	4.02%		6.12%
PDM ³	67.7%	11.6%	0.30%				-25.1%	16.3%		-9.40%

Table A19. 4-acid results for Zn in OREAS 111 (abbreviations as in Table A1; values in ppm).

Replicate No.	Lab A 4A*OES	Lab B 4A*OES	Lab C 4A*OES	Lab D 4A*OES	Lab E 4A*OES	Lab F 4A*OES	Lab G 4A*OES	Lab H 4A*OES	Lab I MAR*OES	Lab J 4A*OES
1	4490	4410	4508	3620	4100	4050	4030	4200	4190	3960
2	4360	4300	4487	4190	4100	4210	3980	4130	4150	3927
3	4530	4420	4392	4620	4200	4130	3860	4140	4250	3839
4	4530	4350	4463	4140	4100	4360	3740	4190	4190	3994
5	4310	4270	4540	4350	4100	4150	3770	4130	4130	3927
Mean	4444	4350	4478	4184	4120	4180	3876	4158	4182	3930
Median	4490	4350	4487	4190	4100	4150	3860	4140	4190	3927
Std.Dev.	102	66	56	367	45	116	127	34	46	58
Rel.Std.Dev.	2.30%	1.52%	1.25%	8.76%	1.09%	2.77%	3.28%	0.82%	1.10%	1.47%
PDM ³	5.92%	3.68%	6.73%	-0.28%	-1.80%	-0.37%	-7.62%	-0.90%	-0.33%	-6.34%