



ORE RESEARCH & EXPLORATION P/L ABN 28 006 859 856
37A Hosie Street · Bayswater North · VIC 3153 · AUSTRALIA
☎ 61 3 9729 0333 ☎ 61 3 9729 8338
📧 info@ore.com.au 🌐 www.ore.com.au


CERTIFICATE OF ANALYSIS FOR

Basalt Blank Chip

Olivine tholeiite (Newer Volcanics Province, Victoria, Australia)

CERTIFIED REFERENCE MATERIAL

OREAS C26d



Document: COA-1548-OREASC26d-R0

(Template:BUP-70-10-01 Rev:2.0)

5-Jun-2020

TABLE OF CONTENTS

INTRODUCTION	5
SOURCE MATERIAL.....	5
PERFORMANCE GATES.....	5
PHYSICAL PROPERTIES.....	6
COMMUNITION AND HOMOGENISATION PROCEDURES.....	7
ANALYTICAL PROGRAM	7
STATISTICAL ANALYSIS.....	7
Homogeneity Evaluation	10
PARTICIPATING LABORATORIES	11
PREPARER AND SUPPLIER.....	11
METROLOGICAL TRACEABILITY	12
COMMUTABILITY	12
INTENDED USE	12
STABILITY AND STORAGE INSTRUCTIONS	13
INSTRUCTIONS FOR CORRECT USE	13
HANDLING INSTRUCTIONS	13
LEGAL NOTICE.....	13
DOCUMENT HISTORY	13
QMS CERTIFICATION	14
CERTIFYING OFFICER	14
REFERENCES	14

LIST OF TABLES

Table 1. Certified Values and Performance Gates for OREAS C26d.	3
Table 2. Indicative Values for OREAS C26d.....	4
Table 3. Particle size distribution of OREAS C26d.	6
Table 4. Physical properties of OREAS C26d.....	6
Table 5. 95% Confidence & Tolerance Limits for OREAS C26d.....	9

Table 1. Certified Values and Performance Gates for OREAS C26d.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Pb Fire Assay											
Au, ppb	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
4-Acid Digestion											
Ag, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Al, wt. %	7.50	0.191	7.12	7.88	6.92	8.07	2.55%	5.10%	7.64%	7.12	7.87
As, ppm	0.68	0.20	0.29	1.07	0.09	1.27	28.77%	57.54%	86.31%	0.65	0.72
Ba, ppm	254	7	240	269	233	276	2.85%	5.70%	8.55%	242	267
Be, ppm	1.11	0.055	1.00	1.22	0.95	1.28	4.98%	9.96%	14.94%	1.06	1.17
Bi, ppm	< 0.1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ca, wt. %	5.92	0.125	5.67	6.17	5.54	6.29	2.12%	4.24%	6.35%	5.62	6.21
Cd, ppm	0.052	0.010	0.032	0.072	0.022	0.082	19.43%	38.85%	58.28%	0.049	0.055
Ce, ppm	36.7	1.88	33.0	40.5	31.1	42.4	5.11%	10.22%	15.33%	34.9	38.6
Co, ppm	44.5	1.42	41.7	47.3	40.3	48.8	3.18%	6.36%	9.54%	42.3	46.7
Cr, ppm	187	18	152	223	134	241	9.58%	19.15%	28.73%	178	197
Cs, ppm	0.73	0.045	0.63	0.82	0.59	0.86	6.25%	12.49%	18.74%	0.69	0.76
Cu, ppm	46.8	2.18	42.5	51.2	40.3	53.4	4.66%	9.33%	13.99%	44.5	49.2
Dy, ppm	4.48	0.104	4.27	4.69	4.16	4.79	2.33%	4.66%	6.99%	4.25	4.70
Er, ppm	2.15	0.099	1.96	2.35	1.86	2.45	4.58%	9.15%	13.73%	2.05	2.26
Eu, ppm	1.66	0.073	1.51	1.81	1.44	1.88	4.41%	8.82%	13.24%	1.58	1.74
Fe, wt. %	7.82	0.236	7.34	8.29	7.11	8.52	3.02%	6.04%	9.06%	7.42	8.21
Ga, ppm	20.1	1.44	17.2	23.0	15.8	24.4	7.14%	14.28%	21.41%	19.1	21.1
Gd, ppm	5.26	0.273	4.72	5.81	4.44	6.08	5.19%	10.39%	15.58%	5.00	5.53
Hf, ppm	3.61	0.106	3.40	3.83	3.30	3.93	2.93%	5.86%	8.79%	3.43	3.79
Ho, ppm	0.82	0.020	0.78	0.86	0.76	0.88	2.48%	4.95%	7.43%	0.78	0.86
In, ppm	0.062	0.004	0.054	0.070	0.050	0.074	6.44%	12.87%	19.31%	0.059	0.065
K, wt. %	0.740	0.026	0.689	0.791	0.663	0.817	3.45%	6.91%	10.36%	0.703	0.777
La, ppm	17.8	0.75	16.3	19.3	15.6	20.1	4.23%	8.46%	12.69%	16.9	18.7
Li, ppm	7.38	0.189	7.00	7.75	6.81	7.94	2.56%	5.12%	7.68%	7.01	7.74
Lu, ppm	0.23	0.012	0.21	0.26	0.20	0.27	5.04%	10.08%	15.12%	0.22	0.24
Mg, wt. %	4.27	0.138	4.00	4.55	3.86	4.68	3.22%	6.44%	9.67%	4.06	4.48
Mn, wt. %	0.110	0.005	0.101	0.120	0.096	0.125	4.37%	8.73%	13.10%	0.105	0.116
Mo, ppm	1.44	0.084	1.27	1.61	1.19	1.69	5.81%	11.63%	17.44%	1.37	1.51
Na, wt. %	2.36	0.077	2.20	2.51	2.12	2.59	3.28%	6.57%	9.85%	2.24	2.47
Nb, ppm	21.4	0.49	20.4	22.4	20.0	22.9	2.30%	4.60%	6.90%	20.4	22.5
Nd, ppm	20.0	0.52	18.9	21.0	18.4	21.5	2.62%	5.25%	7.87%	19.0	21.0
Ni, ppm	154	5	144	164	139	169	3.20%	6.40%	9.60%	146	162
P, wt. %	0.146	0.007	0.133	0.160	0.126	0.166	4.54%	9.08%	13.63%	0.139	0.154
Pb, ppm	2.69	0.222	2.25	3.13	2.03	3.36	8.24%	16.48%	24.73%	2.56	2.83
Pr, ppm	4.60	0.175	4.25	4.95	4.08	5.12	3.80%	7.59%	11.39%	4.37	4.83
Rb, ppm	20.7	0.61	19.5	21.9	18.8	22.5	2.95%	5.91%	8.86%	19.6	21.7
Re, ppm	< 0.002	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt. % \equiv 1000 ppb, parts per billion.

IND: indeterminate;

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
S, wt.%	0.009	0.002	0.005	0.014	0.003	0.016	23.55%	47.11%	70.66%	0.009	0.010
Sb, ppm	0.13	0.02	0.09	0.16	0.07	0.18	14.93%	29.86%	44.79%	0.12	0.13
Sc, ppm	20.5	0.86	18.7	22.2	17.9	23.0	4.22%	8.43%	12.65%	19.4	21.5
Se, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Sm, ppm	4.94	0.121	4.70	5.18	4.58	5.31	2.45%	4.90%	7.34%	4.70	5.19
Sn, ppm	1.45	0.083	1.29	1.62	1.20	1.70	5.74%	11.48%	17.21%	1.38	1.53
Sr, ppm	415	14	387	443	372	457	3.40%	6.81%	10.21%	394	436
Ta, ppm	1.29	0.065	1.16	1.42	1.10	1.49	5.07%	10.13%	15.20%	1.23	1.36
Tb, ppm	0.79	0.029	0.73	0.85	0.70	0.87	3.65%	7.29%	10.94%	0.75	0.83
Te, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	2.79	0.084	2.62	2.95	2.54	3.04	3.00%	6.00%	9.00%	2.65	2.93
Ti, wt.%	1.06	0.042	0.98	1.15	0.94	1.19	3.96%	7.92%	11.88%	1.01	1.12
Tl, ppm	0.070	0.004	0.061	0.079	0.056	0.083	6.40%	12.80%	19.20%	0.066	0.073
Tm, ppm	0.28	0.020	0.24	0.32	0.22	0.34	7.35%	14.71%	22.06%	0.26	0.29
U, ppm	0.70	0.015	0.68	0.73	0.66	0.75	2.06%	4.12%	6.19%	0.67	0.74
V, ppm	155	6	143	168	137	174	3.95%	7.90%	11.85%	148	163
W, ppm	0.43	0.04	0.34	0.51	0.29	0.56	10.33%	20.67%	31.00%	0.40	0.45
Y, ppm	21.1	0.55	20.0	22.2	19.5	22.8	2.62%	5.24%	7.86%	20.1	22.2
Yb, ppm	1.67	0.034	1.60	1.74	1.57	1.77	2.05%	4.10%	6.15%	1.59	1.75
Zn, ppm	107	6	95	118	90	124	5.34%	10.68%	16.03%	101	112
Zr, ppm	139	7	125	152	119	158	4.74%	9.48%	14.22%	132	146

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

IND: indeterminate;

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 2. Indicative Values for OREAS C26d.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Pb Fire Assay								
Pd	ppb	< 1	Pt	ppb	< 5			
4-Acid Digestion								
Ge	ppm	0.29	Hg	ppm	0.018			
Borate Fusion XRF								
Al ₂ O ₃	wt.%	14.33	K ₂ O	wt.%	0.883	P ₂ O ₅	wt.%	0.345
CaO	wt.%	8.60	MgO	wt.%	7.32	SiO ₂	wt.%	51.19
Cl	ppm	137	MnO	wt.%	0.150	SO ₃	wt.%	0.030
Fe ₂ O ₃	wt.%	11.49	Na ₂ O	wt.%	3.14	TiO ₂	wt.%	1.88
Laser Ablation ICP-MS								
Ag	ppm	< 0.1	Hf	ppm	3.63	Sm	ppm	5.13
As	ppm	0.83	Ho	ppm	0.84	Sn	ppm	1.47
Ba	ppm	262	In	ppm	0.046	Sr	ppm	405

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

Table 2. continued.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Laser Ablation ICP-MS continued								
Be	ppm	1.33	La	ppm	17.9	Ta	ppm	1.33
Bi	ppm	< 0.02	Lu	ppm	0.24	Tb	ppm	0.80
Cd	ppm	0.083	Mn	wt. %	0.114	Te	ppm	< 0.2
Ce	ppm	35.6	Mo	ppm	1.50	Th	ppm	2.80
Co	ppm	46.0	Nb	ppm	21.9	Ti	wt. %	1.12
Cr	ppm	244	Nd	ppm	20.4	Tl	ppm	< 0.2
Cs	ppm	0.68	Ni	ppm	160	Tm	ppm	0.29
Cu	ppm	47.7	Pb	ppm	2.00	U	ppm	0.71
Dy	ppm	4.43	Pr	ppm	4.69	V	ppm	164
Er	ppm	2.21	Rb	ppm	21.0	W	ppm	0.42
Eu	ppm	1.68	Re	ppm	< 0.01	Y	ppm	21.5
Ga	ppm	19.8	Sb	ppm	0.083	Yb	ppm	1.72
Gd	ppm	5.08	Sc	ppm	20.9	Zn	ppm	109
Ge	ppm	1.23	Se	ppm	< 5	Zr	ppm	137
Thermogravimetry								
LOI ¹⁰⁰⁰	wt. %	0.238						
Infrared Combustion								
C	wt. %	0.053	S	wt. %	< 0.01			

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt. % \equiv 1000 ppb, parts per billion.

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

INTRODUCTION

OREAS reference materials are intended to provide a low-cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

OREAS reference materials enable users to successfully achieve process control of these tasks because the observed variance from repeated analysis has its origin almost exclusively in the analytical process rather than the reference material itself.

SOURCE MATERIAL

OREAS C26c is a basalt blank chip Certified Reference Material (CRM) prepared from rocks sourced from a quarry containing fresh olivine tholeiite (Newer Volcanics Province), near Melbourne (Victoria), Australia.

PERFORMANCE GATES

Table 1 above shows intervals calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or

rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned (also see 'Intended Use' section below). Westgard Rules extend the basics of single-rule QC monitoring using multi-rules (for more information visit www.westgard.com/mltirule.htm). A second method utilises a 5% window calculated directly from the certified value.

Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow. One approach used at commercial laboratories is to set the acceptance criteria at twice the detection level (DL) \pm 10%.

i.e. Certified Value \pm 10% \pm 2DL (adapted from Govett, 1983).

PHYSICAL PROPERTIES

OREAS C26d was tested at ORE Research & Exploration Pty Ltd's onsite facility for various physical properties. A sieve analysis was performed on three separate 1kg samples to determine the particle size distribution of OREAS C26d. Table 3 presents the average of these findings that should be used for informational purposes only.

Table 3. Particle size distribution of OREAS C26d.

Distribution	Mass Percentage (%)
Above 12.7mm	0.1
Under 12.7mm, Above 6.35mm	13.7
Under 6.35mm, Above 3.18mm	38.5
Under 3.18mm, Above 2mm	11.9
Under 2mm, Above 1.27mm	9.4
Under 1.27mm, Above 0.5mm	8.2
Under 0.5mm	17.9

Table 4 presents the bulk density, moisture percentage and Munsell color code for OREAS C26d. These findings should be used for informational purposes only.

Table 4. Physical properties of OREAS C26d.

Bulk Density (g/L)	Moisture (%)	Munsell Notation [‡]	Munsell Color [‡]
1011.9	0.8	N7	Light Gray

[‡]The Munsell Rock Colour Chart helps geologists and archeologists communicate with colour more effectively by cross-referencing ISCC-NBS colour names with unique Munsell alpha-numeric colour notations for rock colour samples.

COMMINUTION AND HOMOGENISATION PROCEDURES

The material constituting OREAS C26d was prepared in the following manner:

- Drying to constant mass at 105° C;
- Crushing to achieve a nominal particle size of minus 6mm to simulate RC drill chip samples;
- Homogenisation using a rotary splitter;
- Packaging in 500g and 1kg units into sealed robust barrier bags, 20kg units into plastic buckets and 200kg units into 44-gallon (166L) drums.

ANALYTICAL PROGRAM

Ten commercial analytical laboratories participated in the program to characterise the elements reported in Table 1. The following methods were employed:

- Au via 25-40g fire assay with ICP-MS (4 laboratories) and ICP-OES (6 laboratories) finish;
- Full elemental suite by four acid digestion (HNO₃-HClO₄-HCl-HF) with ICP-OES and ICP-MS finish (10 laboratories);

Major and trace elements were also characterised by Bureau Veritas Geoanalytical (Perth, Australia) using borate fusion XRF (Al₂O₃ to TiO₂), laser ablation with ICP-MS (Ag to Zr), LOI at 1000°C and C+S by infrared combustion furnace (see Table 2 'Indicative Values').

For the round robin program ten 1kg samples were taken at 10 predetermined sampling intervals during rotary splitting and are considered representative of the entire prepared batch of OREAS C27e. These 10 x 1kg samples were pulverised (to 95% passing 75 microns), homogenised and each split into six 110g subsamples. Six 110g samples were submitted to each laboratory for analysis. The samples received by each laboratory were obtained by taking two samples from each of three separate 1kg test units. This format enabled a nested ANOVA treatment of the results to evaluate homogeneity, i.e. to ascertain whether between-unit variance is greater than within-unit variance (see 'Homogeneity Evaluation' section).

Tabulated results of all elements together with uncorrected means, medians, standard deviations, relative standard deviations and per cent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM ([OREAS C26d-DataPack.1.0.200605_123749.xlsx](#)).

STATISTICAL ANALYSIS

Standard Deviation intervals (see Table 1) provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability.

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program (see Intended Use section for more detail).

The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e. after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. ***The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.***

Certified Values, Standard Deviations, Confidence Limits and Tolerance Limits (Table 5) have been determined for each analyte following removal of individual, laboratory dataset (batch) and 3SD outliers (single iteration).

For individual outliers within a laboratory batch the z-score test is used in combination with a second method that determines the per cent deviation of the individual value from the batch median. Outliers in general are selected on the basis of z-scores > 2.5 and with per cent deviations (i) > 3 and (ii) more than three times the average absolute per cent deviation for the batch. In certain instances, statistician's prerogative has been employed in discriminating outliers.

Each laboratory data set mean is tested for outlying status based on z-score discrimination and rejected if > 2.5 . After individual and laboratory data set (batch) outliers have been eliminated a non-iterative 3 standard deviation filter is applied, with those values lying outside this window also relegated to outlying status.

95% Confidence Limits are inversely proportional to the number of participating laboratories and inter-laboratory agreement. It is a measure of the reliability of the certified value. A 95% confidence interval indicates a 95% probability that the true value of the analyte under consideration lies between the upper and lower limits. ***95% Confidence Limits should not be used as control limits for laboratory performance.***

Indicative (uncertified) values (Table 2) are present where the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification or where inter-laboratory consensus is poor.

Table 5. 95% Confidence & Tolerance Limits for OREAS C26d.

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
Pb Fire Assay					
Au, Gold (ppb)	< 2	IND	IND	IND	IND
4-Acid Digestion					
Ag, Silver (ppm)	< 0.05	IND	IND	IND	IND
Al, Aluminium (wt.%)	7.50	7.37	7.63	7.30	7.69
As, Arsenic (ppm)	0.68	0.61	0.76	IND	IND
Ba, Barium (ppm)	254	249	259	246	263
Be, Beryllium (ppm)	1.11	1.08	1.15	1.06	1.17
Bi, Bismuth (ppm)	< 0.1	IND	IND	IND	IND
Ca, Calcium (wt.%)	5.92	5.84	5.99	5.77	6.06
Cd, Cadmium (ppm)	0.052	0.044	0.060	IND	IND
Ce, Cerium (ppm)	36.7	35.5	37.9	35.7	37.8
Co, Cobalt (ppm)	44.5	43.6	45.4	42.9	46.2
Cr, Chromium (ppm)	187	174	201	179	196
Cs, Caesium (ppm)	0.73	0.69	0.76	0.69	0.76
Cu, Copper (ppm)	46.8	45.2	48.5	44.7	49.0
Dy, Dysprosium (ppm)	4.48	4.37	4.59	4.34	4.62
Er, Erbium (ppm)	2.15	2.04	2.27	2.02	2.29
Eu, Europium (ppm)	1.66	1.58	1.74	1.56	1.76
Fe, Iron (wt.%)	7.82	7.66	7.97	7.56	8.07
Ga, Gallium (ppm)	20.1	19.2	21.1	19.3	21.0
Gd, Gadolinium (ppm)	5.26	4.91	5.62	5.08	5.45
Hf, Hafnium (ppm)	3.61	3.55	3.68	3.40	3.83
Ho, Holmium (ppm)	0.82	0.79	0.84	0.78	0.85
In, Indium (ppm)	0.062	0.059	0.064	IND	IND
K, Potassium (wt.%)	0.740	0.721	0.759	0.714	0.766
La, Lanthanum (ppm)	17.8	17.3	18.3	17.3	18.3
Li, Lithium (ppm)	7.38	7.23	7.52	7.16	7.59
Lu, Lutetium (ppm)	0.23	0.22	0.24	IND	IND
Mg, Magnesium (wt.%)	4.27	4.18	4.36	4.16	4.38
Mn, Manganese (wt.%)	0.110	0.107	0.113	0.106	0.114
Mo, Molybdenum (ppm)	1.44	1.39	1.49	1.31	1.57
Na, Sodium (wt.%)	2.36	2.30	2.41	2.29	2.42
Nb, Niobium (ppm)	21.4	21.2	21.7	20.8	22.1
Nd, Neodymium (ppm)	20.0	19.4	20.5	19.4	20.6
Ni, Nickel (ppm)	154	151	157	149	159
P, Phosphorus (wt.%)	0.146	0.141	0.152	0.141	0.152
Pb, Lead (ppm)	2.69	2.52	2.86	2.52	2.86

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

IND: indeterminate;

Note: intervals may appear asymmetric due to rounding.

Table 5. continued.

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
4-Acid Digestion continued					
Pr, Praseodymium (ppm)	4.60	4.38	4.83	4.48	4.72
Rb, Rubidium (ppm)	20.7	20.3	21.0	20.1	21.3
Re, Rhenium (ppm)	< 0.002	IND	IND	IND	IND
S, Sulphur (wt.%)	0.009	0.008	0.010	IND	IND
Sb, Antimony (ppm)	0.13	0.11	0.14	IND	IND
Sc, Scandium (ppm)	20.5	19.9	21.0	19.7	21.2
Se, Selenium (ppm)	< 1	IND	IND	IND	IND
Sm, Samarium (ppm)	4.94	4.86	5.03	4.69	5.19
Sn, Tin (ppm)	1.45	1.38	1.52	IND	IND
Sr, Strontium (ppm)	415	406	424	404	426
Ta, Tantalum (ppm)	1.29	1.24	1.34	1.24	1.34
Tb, Terbium (ppm)	0.79	0.75	0.82	0.75	0.83
Te, Tellurium (ppm)	< 0.05	IND	IND	IND	IND
Th, Thorium (ppm)	2.79	2.74	2.84	2.68	2.89
Ti, Titanium (wt.%)	1.06	1.03	1.09	1.03	1.10
Tl, Thallium (ppm)	0.070	0.068	0.072	IND	IND
Tm, Thulium (ppm)	0.28	0.25	0.31	IND	IND
U, Uranium (ppm)	0.70	0.70	0.71	0.66	0.75
V, Vanadium (ppm)	155	150	160	149	162
W, Tungsten (ppm)	0.43	0.40	0.45	IND	IND
Y, Yttrium (ppm)	21.1	20.9	21.3	20.5	21.7
Yb, Ytterbium (ppm)	1.67	1.65	1.69	IND	IND
Zn, Zinc (ppm)	107	103	111	103	110
Zr, Zirconium (ppm)	139	134	143	132	145

SI unit equivalents: ppm, parts per million \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb, parts per billion.

IND: indeterminate;

Note: intervals may appear asymmetric due to rounding.

Homogeneity Evaluation

The tolerance limits (ISO 16269:2014) in Table 5 were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for copper (by 4-acid digestion), where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($\rho=0.95$) will have concentrations lying between 44.7 and 49.0ppm. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35). **Please note that tolerance limits pertain to the homogeneity of the CRM only and should not be used as control limits for laboratory performance.**

P-values are a measure of probability where values less than 0.05 indicate a greater than 95% probability that the observed differences in within-unit and between-unit variances are real. The datasets were filtered for both individual and laboratory data set (batch) outliers

prior to the calculation of p -values. None of the other certified values showed significant p -values except for Pr by 4-acid digestion (p -value = 0.038). This isolated case is most likely due to random* statistical probability as there is no other supporting evidence to suspect greater between-unit variance compared with within-unit variance. The null hypothesis is therefore retained.

** p -values are calculated at the 95% probability level. Therefore, by definition 5% of p -values calculated will naturally fall as 'significant' (<0.05). For every 100 p -values calculated, 5 will 'fail' naturally meaning a significant difference is detected (a false positive) where, in reality, none exists.*

Only results for constituents present in concentrations well above the detection levels (i.e. >20 x Lower Limit of Detection) for the various methods undertaken were considered for the objective of evaluating homogeneity. It is important to note that ANOVA is not an absolute measure of homogeneity. Rather, it establishes whether or not the analytes are distributed in a similar manner throughout the packaging run of OREAS C26d and whether the variance between two subsamples from the same unit is statistically distinguishable to the variance from two subsamples taken from any two separate units. A reference material therefore, can possess poor absolute homogeneity yet still pass a relative homogeneity test if the within-unit heterogeneity is large and similar across all units.

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS C26d is sufficiently homogenous and is fit-for-purpose as a certified reference material (see 'Intended Use' below).

PARTICIPATING LABORATORIES

1. Actlabs, Ancaster, Ontario, Canada
2. ALS, Brisbane, QLD, Australia
3. ALS, Perth, WA, Australia
4. ALS, Vancouver, BC, Canada
5. Bureau Veritas Geoanalytical, Adelaide, SA, Australia
6. Bureau Veritas Geoanalytical, Perth, WA, Australia
7. Intertek Genalysis, Adelaide, SA, Australia
8. Intertek Genalysis, Perth, WA, Australia
9. SGS Australia Mineral Services, Perth, WA, Australia
10. SGS Canada Inc., Vancouver, BC, Canada

PREPARER AND SUPPLIER

Certified reference material OREAS C26d was prepared, certified and supplied by:



ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.ore.com.au
Email: info@ore.com.au

METROLOGICAL TRACEABILITY

The analytical samples were selected in a manner to represent the entire batch of prepared CRM. This 'representivity' was maintained in each submitted laboratory sample batch and ensures the user that the data is traceable from sample selection through to the analytical results that underlie the consensus values. Each analytical data set has been validated by its assayer through the inclusion of internal reference materials and QC checks during analysis.

The laboratories were chosen on the basis of their competence (from past performance in inter-laboratory programs undertaken by ORE Pty Ltd) for a particular analytical method, analyte or analyte suite, and sample matrix. Most of these laboratories have and maintain ISO 17025 accreditation. The certified values presented in this report are calculated from the means of accepted data following robust statistical treatment as detailed in this report.

Guide ISO/TR 16476:2016, section 5.3.1 describes metrological traceability in reference materials as it pertains to the transformation of the measurand. In this section it states, *“Although the determination of the property value itself can be made traceable to appropriate units through, for example, calibration of the measurement equipment used, steps like the transformation of the sample from one physical (chemical) state to another cannot. Such transformations may only be compared with a reference (when available), or among themselves. For some transformations, reference methods have been defined and may be used in certification projects to evaluate the uncertainty associated with such a transformation. In other cases, **only a comparison among different laboratories using the same method is possible. In this case, certification takes place on the basis of agreement among independent measurement results** (see ISO Guide 35:2006, Clause 10).”*

COMMUTABILITY

The measurements of the results that underlie the certified values contained in this report were undertaken by methods involving pre-treatment (digestion/fusion) of the sample. This served to reduce the sample to a simple and well understood form permitting calibration using simple solutions of the CRM. Due to these methods being well understood and highly effective, commutability is not an issue for this CRM. All OREAS CRMs are sourced from naturally occurring rocks and sediments meaning they will display similar behaviour as routine 'field' samples in the relevant measurement process. Care should be taken to ensure 'matrix matching' as close as practically achievable. The matrix and mineralisation style of the CRM is described in the 'Source Material' section and users should select appropriate CRMs matching these attributes to their field samples.

INTENDED USE

OREAS C26d is intended to cover all activities needed to produce a measurement result. This includes extraction, possible separation steps and the actual measurement process (the signal producing step). OREAS C26d may be used to calibrate the entire procedure by producing a pure substance CRM transformed into a calibration solution.

OREAS C26d is intended for the following uses:

- For the monitoring of laboratory performance in the analysis of analytes reported in Table 1 in geological samples;

- For the verification of analytical methods for analytes reported in Table 1;
- For the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

QC monitoring using multiples of the Standard Deviation (SD)

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program.

The majority of data generated in the round robin program was produced by a selection of world class laboratories. The SD's thus generated are more constrained than those that would be produced across a randomly selected group of laboratories. To produce more generally achievable SD's the 'pooled' SD's provided in this report include inter-laboratory bias. This 'one size fits all' approach may require revision at the discretion of the QC manager concerned following careful scrutiny of QC control charts.

STABILITY AND STORAGE INSTRUCTIONS

OREAS C26d was prepared from fresh, barren rhyodacite material. In its unopened state under normal conditions of storage it has a shelf life beyond ten years.

INSTRUCTIONS FOR CORRECT USE

The certified values for OREAS C26d refer to the concentration levels in its packaged state.

HANDLING INSTRUCTIONS

OREAS C26d is a chip CRM but contains a portion of fine powder. Fine powders pose a risk to eyes and lungs and therefore standard precautions such as the use of safety glasses and dust masks are advised.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

DOCUMENT HISTORY

Revision No.	Date	Changes applied
0	5 th June, 2020	First publication.

QMS CERTIFICATION

ORE Pty Ltd is ISO 9001:2015 certified by Lloyd's Register Quality Assurance Ltd for its quality management system including development, manufacturing, certification and supply of CRMs.



CERTIFYING OFFICER

A handwritten signature in blue ink, appearing to read 'S.H.', is positioned above the name of the certifying officer.

5th June, 2020

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

REFERENCES

Govett, G.J.S. (1983), ed. Handbook of Exploration Geochemistry, Volume 2: Statistics and Data Analysis in Geochemical Prospecting (Variations of accuracy and precision), P.O. Box 330, 1000 AH Amsterdam, The Netherlands.

ISO Guide 30 (2015), Terms and definitions used in connection with reference materials.

ISO Guide 31 (2015), Reference materials – Contents of certificates and labels.

ISO Guide 35:2017. Certification of reference materials - General and statistical principals.

ISO 16269:2014. Statistical interpretation of data – Part 6: Determination of statistical tolerance intervals.

ISO/TR 16476:2016, Reference Materials – Establishing and expressing metrological traceability of quantity values assigned to reference materials.

Munsell Rock Color Book (2014). Rock-Color Chart Committee, Geological Society of America (GSA), Minnesota (USA).