

CERTIFICATE OF ANALYSIS FOR

CERTIFIED REFERENCE MATERIAL

OREAS 236

Gold Ore (Frogs Leg Gold Mine, Western Australia)

Table 1. Certified Values and Performance Gates for OREAS 236.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Pb Fire Assay											
Au, ppm	1.85	0.059	1.73	1.97	1.67	2.03	3.19%	6.39%	9.58%	1.76	1.94
Aqua Regia Digestion (sample weights 10-50g)											
Au, ppm	1.75	0.087	1.58	1.93	1.49	2.01	4.99%	9.98%	14.96%	1.66	1.84
Cyanide Leach											
Au, ppm	1.79	0.048	1.70	1.89	1.65	1.94	2.66%	5.33%	7.99%	1.70	1.88
X-ray Photon Assay											
Au, ppm	1.78	0.062	1.66	1.91	1.60	1.97	3.47%	6.94%	10.41%	1.69	1.87
4-Acid Digestion											
Ag, ppm	0.478	0.058	0.363	0.594	0.305	0.651	12.06%	24.13%	36.19%	0.454	0.502
Al, wt. %	6.59	0.152	6.29	6.90	6.14	7.05	2.30%	4.60%	6.90%	6.26	6.92
As, ppm	68	4.0	60	76	56	80	5.88%	11.77%	17.65%	64	71
Ba, ppm	246	9	228	264	219	273	3.65%	7.30%	10.96%	233	258
Be, ppm	0.46	0.029	0.40	0.52	0.37	0.55	6.39%	12.78%	19.16%	0.44	0.48
Bi, ppm	0.061	0.007	0.048	0.075	0.042	0.081	10.70%	21.39%	32.09%	0.058	0.064

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb (parts per billion).

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.



Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
Ca, wt.%	5.93	0.246	5.44	6.43	5.20	6.67	4.14%	8.29%	12.43%	5.64	6.23
Cd, ppm	0.62	0.044	0.53	0.71	0.49	0.76	7.12%	14.25%	21.37%	0.59	0.65
Ce, ppm	14.0	1.36	11.2	16.7	9.9	18.0	9.74%	19.48%	29.22%	13.3	14.7
Co, ppm	41.5	2.36	36.8	46.2	34.4	48.6	5.69%	11.39%	17.08%	39.4	43.6
Cr, ppm	86	4.3	78	95	74	99	4.92%	9.85%	14.77%	82	91
Cs, ppm	1.01	0.072	0.86	1.15	0.79	1.23	7.18%	14.37%	21.55%	0.96	1.06
Cu, ppm	170	6	158	182	152	188	3.51%	7.02%	10.53%	161	178
Dy, ppm	3.94	0.264	3.41	4.47	3.15	4.73	6.70%	13.39%	20.09%	3.74	4.13
Er, ppm	2.43	0.154	2.12	2.74	1.97	2.89	6.32%	12.64%	18.96%	2.31	2.55
Eu, ppm	0.96	0.030	0.90	1.02	0.87	1.05	3.07%	6.14%	9.21%	0.92	1.01
Fe, wt.%	8.00	0.273	7.46	8.55	7.18	8.82	3.41%	6.83%	10.24%	7.60	8.40
Ga, ppm	16.1	1.6	12.8	19.4	11.2	21.1	10.21%	20.42%	30.63%	15.3	16.9
Gd, ppm	3.47	0.230	3.01	3.93	2.78	4.16	6.62%	13.24%	19.86%	3.30	3.65
Hf, ppm	1.80	0.081	1.64	1.96	1.56	2.04	4.50%	9.01%	13.51%	1.71	1.89
Ho, ppm	0.86	0.032	0.80	0.92	0.76	0.96	3.73%	7.45%	11.18%	0.82	0.90
In, ppm	0.080	0.008	0.063	0.096	0.055	0.104	10.18%	20.37%	30.55%	0.076	0.084
K, wt.%	0.559	0.019	0.521	0.597	0.502	0.616	3.41%	6.83%	10.24%	0.531	0.587
La, ppm	5.99	0.462	5.06	6.91	4.60	7.38	7.72%	15.44%	23.16%	5.69	6.29
Li, ppm	10.5	0.61	9.3	11.7	8.7	12.4	5.84%	11.69%	17.53%	10.0	11.0
Lu, ppm	0.37	0.028	0.32	0.43	0.29	0.46	7.55%	15.09%	22.64%	0.35	0.39
Mg, wt.%	3.40	0.104	3.19	3.60	3.08	3.71	3.06%	6.11%	9.17%	3.23	3.57
Mn, wt.%	0.133	0.007	0.120	0.147	0.113	0.154	5.07%	10.15%	15.22%	0.127	0.140
Mo, ppm	1.56	0.19	1.18	1.94	0.99	2.13	12.20%	24.39%	36.59%	1.48	1.64
Na, wt.%	2.15	0.056	2.04	2.27	1.99	2.32	2.60%	5.20%	7.79%	2.05	2.26
Nb, ppm	3.63	0.282	3.06	4.19	2.78	4.47	7.76%	15.53%	23.29%	3.45	3.81
Nd, ppm	9.01	0.462	8.09	9.94	7.63	10.40	5.13%	10.25%	15.38%	8.56	9.46
Ni, ppm	68	4.3	60	77	56	81	6.26%	12.52%	18.78%	65	72
P, wt.%	0.045	0.003	0.040	0.050	0.038	0.053	5.69%	11.38%	17.07%	0.043	0.048
Pb, ppm	30.5	1.99	26.5	34.5	24.5	36.5	6.53%	13.06%	19.59%	29.0	32.0
Pr, ppm	1.94	0.101	1.74	2.14	1.64	2.24	5.22%	10.44%	15.65%	1.84	2.04
Rb, ppm	14.1	0.83	12.4	15.7	11.6	16.6	5.91%	11.82%	17.73%	13.4	14.8
Re, ppm	0.003	0.001	0.001	0.004	0.000	0.005	32.25%	64.50%	96.76%	0.003	0.003
S, wt.%	0.444	0.017	0.411	0.477	0.394	0.494	3.75%	7.49%	11.24%	0.422	0.466
Sb, ppm	1.76	0.147	1.47	2.06	1.32	2.20	8.36%	16.72%	25.08%	1.67	1.85
Sc, ppm	38.5	1.91	34.7	42.3	32.8	44.2	4.96%	9.92%	14.88%	36.6	40.4
Se, ppm	< 5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Sm, ppm	2.71	0.171	2.37	3.05	2.19	3.22	6.32%	12.64%	18.96%	2.57	2.84
Sn, ppm	1.08	0.13	0.82	1.35	0.68	1.48	12.33%	24.66%	36.99%	1.03	1.14
Sr, ppm	95	4.9	85	105	81	110	5.10%	10.20%	15.30%	90	100
Ta, ppm	0.25	0.03	0.19	0.31	0.16	0.33	11.52%	23.04%	34.55%	0.24	0.26

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb (parts per billion).

Note 1: intervals may appear asymmetric due to rounding; IND = indeterminate.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
Tb, ppm	0.62	0.036	0.54	0.69	0.51	0.72	5.78%	11.57%	17.35%	0.59	0.65
Te, ppm	0.11	0.02	0.08	0.15	0.06	0.17	15.54%	31.08%	46.63%	0.11	0.12
Th, ppm	1.10	0.11	0.87	1.33	0.76	1.44	10.34%	20.68%	31.02%	1.05	1.16
Ti, wt. %	0.639	0.026	0.586	0.692	0.559	0.718	4.15%	8.30%	12.44%	0.607	0.671
Tl, ppm	0.24	0.018	0.21	0.28	0.19	0.30	7.34%	14.69%	22.03%	0.23	0.25
Tm, ppm	0.36	0.022	0.31	0.40	0.29	0.42	6.03%	12.06%	18.09%	0.34	0.38
U, ppm	0.35	0.04	0.26	0.43	0.22	0.48	12.54%	25.09%	37.63%	0.33	0.36
V, ppm	279	15	248	310	233	325	5.50%	10.99%	16.49%	265	293
W, ppm	30.5	1.43	27.6	33.4	26.2	34.8	4.70%	9.41%	14.11%	29.0	32.0
Y, ppm	21.7	0.85	20.0	23.4	19.1	24.2	3.92%	7.84%	11.76%	20.6	22.7
Yb, ppm	2.32	0.152	2.02	2.63	1.87	2.78	6.54%	13.07%	19.61%	2.21	2.44
Zn, ppm	144	6	131	157	124	163	4.52%	9.04%	13.55%	136	151
Zr, ppm	55	3.9	47	63	43	67	7.16%	14.33%	21.49%	52	58
Aqua Regia Digestion											
Ag, ppm	0.488	0.029	0.430	0.546	0.400	0.575	5.96%	11.91%	17.87%	0.463	0.512
Al, wt. %	3.16	0.167	2.82	3.49	2.65	3.66	5.28%	10.57%	15.85%	3.00	3.31
As, ppm	67	3.4	60	73	56	77	5.10%	10.21%	15.31%	63	70
B, ppm	90	6.9	76	104	70	111	7.64%	15.28%	22.92%	86	95
Ba, ppm	35.7	2.94	29.8	41.6	26.9	44.5	8.24%	16.49%	24.73%	33.9	37.5
Be, ppm	0.26	0.020	0.22	0.30	0.20	0.32	7.73%	15.46%	23.20%	0.25	0.28
Bi, ppm	0.062	0.006	0.050	0.074	0.044	0.079	9.50%	19.00%	28.50%	0.059	0.065
Ca, wt. %	2.64	0.209	2.22	3.06	2.01	3.26	7.93%	15.86%	23.79%	2.51	2.77
Cd, ppm	0.61	0.031	0.55	0.68	0.52	0.71	5.03%	10.06%	15.10%	0.58	0.65
Ce, ppm	10.6	0.39	9.8	11.4	9.4	11.8	3.71%	7.42%	11.13%	10.1	11.2
Co, ppm	30.8	2.21	26.4	35.2	24.2	37.4	7.18%	14.37%	21.55%	29.3	32.3
Cr, ppm	32.8	1.81	29.2	36.4	27.4	38.3	5.52%	11.04%	16.57%	31.2	34.5
Cs, ppm	0.73	0.023	0.68	0.77	0.66	0.80	3.21%	6.43%	9.64%	0.69	0.76
Cu, ppm	169	6	157	182	151	188	3.66%	7.32%	10.98%	161	178
Dy, ppm	2.58	0.204	2.18	2.99	1.97	3.19	7.90%	15.79%	23.69%	2.45	2.71
Er, ppm	1.52	0.16	1.20	1.85	1.03	2.02	10.74%	21.48%	32.21%	1.45	1.60
Eu, ppm	0.58	0.08	0.42	0.74	0.34	0.82	13.79%	27.59%	41.38%	0.55	0.61
Fe, wt. %	5.95	0.217	5.52	6.38	5.30	6.60	3.64%	7.28%	10.92%	5.65	6.25
Ga, ppm	11.6	0.69	10.3	13.0	9.6	13.7	5.91%	11.82%	17.73%	11.0	12.2
Gd, ppm	2.24	0.142	1.96	2.53	1.81	2.67	6.35%	12.70%	19.06%	2.13	2.35
Ge, ppm	0.15	0.02	0.11	0.18	0.09	0.20	12.24%	24.47%	36.71%	0.14	0.15
Hf, ppm	0.54	0.045	0.45	0.63	0.41	0.68	8.38%	16.76%	25.13%	0.51	0.57
Hg, ppm	0.046	0.012	0.022	0.071	0.009	0.084	26.63%	53.25%	79.88%	0.044	0.049
Ho, ppm	0.53	0.06	0.40	0.65	0.34	0.71	11.58%	23.17%	34.75%	0.50	0.55
In, ppm	0.039	0.003	0.032	0.045	0.029	0.048	8.47%	16.95%	25.42%	0.037	0.040
K, wt. %	0.134	0.008	0.117	0.151	0.109	0.160	6.31%	12.63%	18.94%	0.128	0.141

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt. % \equiv 1000 ppb (parts per billion).

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
La, ppm	4.72	0.262	4.20	5.25	3.94	5.51	5.55%	11.10%	16.65%	4.49	4.96
Li, ppm	9.28	0.440	8.40	10.16	7.96	10.60	4.74%	9.48%	14.22%	8.82	9.74
Lu, ppm	0.18	0.017	0.15	0.22	0.13	0.23	9.30%	18.59%	27.89%	0.17	0.19
Mg, wt. %	1.72	0.049	1.63	1.82	1.58	1.87	2.83%	5.66%	8.49%	1.64	1.81
Mn, wt. %	0.071	0.004	0.063	0.079	0.059	0.083	5.62%	11.23%	16.85%	0.068	0.075
Mo, ppm	1.49	0.071	1.35	1.63	1.27	1.70	4.80%	9.59%	14.39%	1.41	1.56
Na, wt. %	0.265	0.017	0.231	0.299	0.214	0.316	6.37%	12.74%	19.11%	0.252	0.278
Nb, ppm	0.16	0.05	0.07	0.25	0.02	0.30	29.25%	58.50%	87.75%	0.15	0.17
Nd, ppm	6.89	0.326	6.23	7.54	5.91	7.87	4.74%	9.48%	14.22%	6.54	7.23
Ni, ppm	48.8	3.29	42.3	55.4	39.0	58.7	6.73%	13.45%	20.18%	46.4	51.3
P, wt. %	0.045	0.001	0.042	0.048	0.040	0.049	3.26%	6.53%	9.79%	0.043	0.047
Pb, ppm	30.5	2.06	26.3	34.6	24.3	36.6	6.77%	13.54%	20.31%	28.9	32.0
Pr, ppm	1.43	0.130	1.17	1.69	1.04	1.82	9.08%	18.16%	27.24%	1.36	1.50
Rb, ppm	5.87	0.428	5.02	6.73	4.59	7.16	7.28%	14.57%	21.85%	5.58	6.17
Re, ppm	0.002	0.000	0.001	0.003	0.001	0.003	18.47%	36.94%	55.42%	0.002	0.002
S, wt. %	0.445	0.025	0.395	0.496	0.369	0.521	5.67%	11.34%	17.01%	0.423	0.467
Sb, ppm	0.90	0.31	0.28	1.52	0.00	1.83	34.64%	69.28%	103.92%	0.85	0.94
Sc, ppm	6.47	0.66	5.15	7.80	4.48	8.46	10.24%	20.49%	30.73%	6.15	6.80
Se, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Sm, ppm	1.89	0.184	1.52	2.26	1.34	2.44	9.74%	19.49%	29.23%	1.79	1.98
Sn, ppm	0.68	0.049	0.59	0.78	0.54	0.83	7.21%	14.42%	21.64%	0.65	0.72
Sr, ppm	29.7	2.67	24.4	35.1	21.7	37.8	8.98%	17.96%	26.94%	28.3	31.2
Ta, ppm	< 0.01	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tb, ppm	0.39	0.021	0.35	0.43	0.32	0.45	5.38%	10.77%	16.15%	0.37	0.41
Te, ppm	0.11	0.01	0.08	0.13	0.07	0.15	12.64%	25.29%	37.93%	0.10	0.11
Th, ppm	0.88	0.057	0.76	0.99	0.71	1.05	6.50%	13.00%	19.51%	0.83	0.92
Ti, wt. %	0.387	0.061	0.265	0.509	0.204	0.570	15.76%	31.51%	47.27%	0.368	0.406
Tl, ppm	0.13	0.009	0.11	0.14	0.10	0.15	7.18%	14.37%	21.55%	0.12	0.13
Tm, ppm	0.20	0.02	0.15	0.24	0.13	0.26	10.75%	21.49%	32.24%	0.19	0.21
U, ppm	0.24	0.014	0.21	0.27	0.20	0.29	5.83%	11.66%	17.50%	0.23	0.25
V, ppm	158	10	137	179	127	190	6.63%	13.27%	19.90%	150	166
W, ppm	22.6	2.9	16.7	28.5	13.8	31.5	13.05%	26.10%	39.15%	21.5	23.7
Y, ppm	12.9	0.84	11.2	14.6	10.4	15.4	6.54%	13.08%	19.61%	12.3	13.6
Yb, ppm	1.29	0.13	1.03	1.55	0.90	1.68	10.17%	20.35%	30.52%	1.23	1.35
Zn, ppm	133	7	118	148	111	155	5.53%	11.05%	16.58%	126	139
Zr, ppm	17.8	2.1	13.7	22.0	11.6	24.1	11.73%	23.46%	35.19%	16.9	18.7

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt. % \equiv 1000 ppb (parts per billion).

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

TABLE OF CONTENTS

INTRODUCTION	6
SOURCE MATERIAL.....	7
PERFORMANCE GATES	7
COMMUNITION AND HOMOGENISATION PROCEDURES	8
PHYSICAL PROPERTIES	8
ANALYTICAL PROGRAM.....	8
STATISTICAL ANALYSIS.....	9
Homogeneity Evaluation	10
PREPARER AND SUPPLIER.....	16
PARTICIPATING LABORATORIES.....	17
METROLOGICAL TRACEABILITY	22
COMMUTABILITY	22
INTENDED USE	22
STABILITY AND STORAGE INSTRUCTIONS	23
INSTRUCTIONS FOR CORRECT USE.....	23
HANDLING INSTRUCTIONS.....	24
LEGAL NOTICE	25
DOCUMENT HISTORY	25
CERTIFYING OFFICER.....	25
QMS CERTIFICATION	25
REFERENCES	25

LIST OF TABLES

Table 1. Certified Values and Performance Gates for OREAS 236.....	1
Table 2. Indicative Values for OREAS 236.....	6
Table 3. Physical properties of OREAS 236.....	8
Table 4. 95% Confidence & Tolerance Limits for OREAS 236.....	11
Table 5. Neutron Activation Analysis of Au (in ppm) on 20 x 85mg subsamples1583.....	15

LIST OF FIGURES

Figure 1. Au by Fire Assay in OREAS 236	18
Figure 2. Au by aqua regia digestion in OREAS 236	19
Figure 3. Au by cyanide leach in OREAS 236	20
Figure 4. Au by photon assay in OREAS 236	21

Table 2. Indicative Values for OREAS 236.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
4-Acid Digestion								
Ge	ppm	0.12	Hg	ppm	< 2			
Aqua Regia Digestion								
Pd	ppb	< 10	Pt	ppb	9.80			
Borate Fusion XRF								
Al ₂ O ₃	wt.%	12.67	Fe ₂ O ₃	wt.%	11.81	S	wt.%	0.442
As	ppm	70	K ₂ O	wt.%	0.669	SiO ₂	wt.%	52.79
BaO	ppm	285	MgO	wt.%	5.85	Sn	ppm	7.50
CaO	wt.%	8.56	MnO	wt.%	0.177	Sr	ppm	127
Cl	ppm	2705	Na ₂ O	wt.%	2.90	TiO ₂	wt.%	1.10
Co	ppm	50	Ni	ppm	75	V ₂ O ₅	ppm	570
Cr ₂ O ₃	ppm	145	P ₂ O ₅	wt.%	0.110	Zn	ppm	155
Cu	ppm	185	Pb	ppm	35.0	Zr	ppm	78
Thermogravimetry								
LOI ¹⁰⁰⁰	wt.%	3.27						
Infrared Combustion								
C	wt.%	0.195	S	wt.%	0.380			
Laser Ablation ICP-MS								
Ag	ppm	0.500	Hf	ppm	2.11	Sm	ppm	2.79
As	ppm	67	Ho	ppm	0.92	Sn	ppm	1.10
Ba	ppm	258	In	ppm	0.075	Sr	ppm	95
Be	ppm	0.35	La	ppm	6.12	Ta	ppm	0.27
Bi	ppm	0.060	Lu	ppm	0.37	Tb	ppm	0.63
Cd	ppm	0.70	Mn	wt.%	0.140	Te	ppm	< 0.2
Ce	ppm	13.7	Mo	ppm	1.60	Th	ppm	1.12
Co	ppm	44.4	Nb	ppm	3.80	Ti	wt.%	0.659
Cr	ppm	103	Nd	ppm	9.54	Tl	ppm	< 0.2
Cs	ppm	1.00	Ni	ppm	75	Tm	ppm	0.38
Cu	ppm	172	Pb	ppm	33.0	U	ppm	0.38
Dy	ppm	4.08	Pr	ppm	2.07	V	ppm	300
Er	ppm	2.60	Rb	ppm	14.1	W	ppm	32.8
Eu	ppm	0.99	Re	ppm	< 0.01	Y	ppm	23.0
Ga	ppm	15.8	Sb	ppm	1.85	Yb	ppm	2.53
Gd	ppm	3.52	Sc	ppm	39.5	Zn	ppm	153
Ge	ppm	1.43	Se	ppm	< 5	Zr	ppm	72

SI unit equivalents: ppm (parts per million) ≡ mg/kg ≡ µg/g ≡ 0.0001 wt.% ≡ 1000 ppb (parts per billion).

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

INTRODUCTION

OREAS reference materials are intended to provide a low-cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

OREAS reference materials enable users to successfully achieve process control of these tasks because the observed variance from repeated analysis has its origin almost exclusively in the analytical process rather than the reference material itself. In evaluating laboratory performance with this CRM, the section headed 'Instructions for correct use' should be read carefully.

Table 1 provides performance gate intervals for the certified values based on their pooled 1SD's. Table 2 shows indicative values including major and trace element characterisation by Bureau Veritas in Perth, Western Australia which includes:

- Major oxides by lithium borate fusion with X-ray fluorescence;
- LOI at 1000°C by thermogravimetric analyser;
- Total Carbon and Sulphur by infrared combustion furnace;
- Trace elements by laser ablation (on the fused bead) with ICP-MS finish.

Table 3 provides some indicative physical properties and Table 4 presents the 95% confidence and tolerance limits for all certified values. Gold homogeneity (via INAA) is shown in Table 5 and is also demonstrated by a nested ANOVA program using fire assay (see '**nested ANOVA**' section).

Tabulated results of all elements (including Au INAA analyses) together with uncorrected means, medians, standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**OREAS 236-DataPack.1.1.211029_175256.xlsx**).

Results are also presented in scatter plots for gold by fire assay, aqua regia digestion, cyanide leach and photon assay (Figures 1 to 4, respectively) together with $\pm 3SD$ (magenta) and $\pm 5\%$ (yellow) control lines and certified value (green line). Accepted individual results are coloured blue and individual and dataset outliers are identified in red and violet, respectively.

SOURCE MATERIAL

OREAS 236 was prepared from a blend of gold ore and barren greenstone. The ore was sourced from the Frogs Leg Gold Mine located 19km west of Kalgoorlie in Western Australia. The Cambrian greenstone was sourced from a quarry 145km north of Melbourne, Australia.

PERFORMANCE GATES

Table 1 above shows intervals calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned (also see 'Intended Use' section below). Westgard Rules extend the basics of single-rule QC monitoring using multi-rules (for more information visit www.westgard.com/mltirule.htm). A second method utilises a 5% window calculated directly from the certified value.

Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow. One approach used at commercial laboratories is to set the acceptance criteria at twice the detection level (DL) $\pm 10\%$.

i.e., Certified Value $\pm 10\% \pm 2DL$ (adapted from Govett, 1983).

COMMINUTION AND HOMOGENISATION PROCEDURES

The material constituting OREAS 236 was prepared in the following manner:

- Drying the gold ore and greenstone to constant mass at 105°C;
- Crushing and multi stage milling of gold ore to 100% minus 30 microns;
- Crushing and multi stage milling of greenstone to >98% minus 75 microns;
- Final homogenisation;
- Packaging in 1kg units in plastic jars.

PHYSICAL PROPERTIES

OREAS 236 was tested at ORE Research & Exploration Pty Ltd's onsite facility for various physical properties. Table 3 presents these findings that should be used for informational purposes only.

Table 3. Physical properties of OREAS 236.

Bulk Density (g/L)	Moisture%	Munsell Notation [‡]	Munsell Color [‡]
824	0.70	5GY 6/1	Greenish Gray

[‡]The Munsell Rock Color Chart helps geologists and archeologists communicate with colour more effectively by cross-referencing ISCC-NBS colour names with unique Munsell alpha-numeric colour notations for rock colour samples.

ANALYTICAL PROGRAM

Thirty-one commercial analytical laboratories participated in the program to certify the elements reported in Table 1. The following methods were employed:

- Gold by fire assay (25-50g charge weight) with AAS (21 laboratories) and ICP-OES (5 laboratories) finish;
- Gold by aqua regia digestion (15-50g sample weight) with ICP-OES and/or ICP-MS (22 laboratories) finish;
- Gold by cyanide leach; a variety of cyanide leach methods were undertaken by the participating laboratories including the use of LeachWELL tablets, alkaline added sodium cyanide solution as well as sodium cyanide liquor with LeachWELL powder. The sample weights included: 20g (1 laboratory by AAS finish), 30g (4 laboratories by AAS finish), 50g (3 laboratories by ICP-MS finish and 1 laboratory by AAS

finish), 60g (1 laboratory by ICP-MS finish) and 200g (5 laboratories by AAS and 1 laboratory by ICP-MS finish).

- Gold by x-ray photon assay on ~350g sample weights (6 Chrysos PhotonAssay units at 4 installations with two rounds of data reported from each unit);
- Full ICP-OES and ICP-MS elemental suites by 4-acid ($\text{HNO}_3\text{-HF-HClO}_4\text{-HCl}$) digestion (up to 23 laboratories depending on the element);
- Full ICP-OES and ICP-MS elemental suites by aqua regia digestion (up to 24 laboratories depending on the element).

To confirm homogeneity, gold by instrumental neutron activation analysis (INAA) was undertaken on 20 x 85mg subsamples by the Australian Nuclear Science and Technology Organisation (ANSTO) located in Lucas Heights, NSW, Australia (see Table 5 in the 'Homogeneity Evaluation' section below).

For the round robin program twenty 3kg test units were taken at predetermined intervals during the bagging stage, immediately following homogenisation and are considered representative of the entire prepared batch. Six pulp samples were submitted to each laboratory for analysis (the weight provided depended on whether the laboratory was anticipated to undertake assays by gold cyanide leach). The samples received by each laboratory were obtained by taking two samples from each of three separate 3kg test units. This format enabled a nested ANOVA treatment of the results to evaluate homogeneity, i.e., to ascertain whether between-unit variance is greater than within-unit variance.

STATISTICAL ANALYSIS

Standard Deviation intervals (see Table 1) provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability.

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program (see 'Instructions for correct use' section for more detail).

The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e., after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e., the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. ***The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.***

Certified Values, Standard Deviations, Confidence Limits and Tolerance Limits (Table 4) have been determined for each analyte following removal of individual, laboratory dataset (batch) and 3SD outliers (single iteration).

For individual outliers within a laboratory batch the z-score test is used in combination with a second method that determines the per cent deviation of the individual value from the batch median. Outliers in general are selected on the basis of z-scores > 2.5 and with per cent deviations (i) > 3 and (ii) more than three times the average absolute per cent deviation for the batch. In certain instances, statistician's prerogative has been employed in discriminating outliers.

Each laboratory data set mean is tested for outlying status based on z-score discrimination and rejected if > 2.5 . After individual and laboratory data set (batch) outliers have been eliminated a non-iterative 3 standard deviation filter is applied, with those values lying outside this window also relegated to outlying status.

Certified Values are the means of accepted laboratory means after outlier filtering. The INAA data (see Table 5) is omitted from determination of the certified value for Au and is used solely for the calculation of Tolerance Limits and homogeneity evaluation of OREAS 236 (see 'Homogeneity Evaluation' section below).

95% Confidence Limits are inversely proportional to the number of participating laboratories and inter-laboratory agreement. It is a measure of the reliability of the certified value. A 95% confidence interval indicates a 95% probability that the true value of the analyte under consideration lies between the upper and lower limits. **95% Confidence Limits should not be used as control limits for laboratory performance.**

Indicative (uncertified) values (Table 2) are present where the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification or where inter-laboratory consensus is poor.

Homogeneity Evaluation

For analytes other than gold, the tolerance limits (ISO 16269:2014) shown in Table 4 were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for copper by 4-acid digestion, where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($p=0.95$) will have concentrations lying between 166 and 173 ppm. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

Please note that tolerance limits pertain to the homogeneity of the CRM only and should not be used as control limits for laboratory performance.

Table 4. 95% Confidence & Tolerance Limits for OREAS 236.

Constituent	Certified	95% Confidence Limits		95% Tolerance Limits	
	Value	Low	High	Value	Low
Pb Fire Assay					
Au, Gold (ppm)	1.85	1.83	1.87	1.84*	1.86*
Aqua Regia Digestion (sample weights 10-50g)					
Au, Gold (ppm)	1.75	1.71	1.79	1.74*	1.76*
Cyanide Leach					
Au, Gold (ppm)	1.79	1.77	1.82	1.79*	1.80*
X-ray Photon Assay					
Au, Gold (ppm)	1.78	1.74	1.83	1.68	1.88
4-Acid Digestion					
Ag, Silver (ppm)	0.478	0.441	0.515	0.452	0.504
Al, Aluminium (wt.%)	6.59	6.53	6.65	6.49	6.69
As, Arsenic (ppm)	68	66	70	66	69
Ba, Barium (ppm)	246	242	250	242	250
Be, Beryllium (ppm)	0.46	0.44	0.47	0.42	0.50
Bi, Bismuth (ppm)	0.061	0.058	0.065	IND	IND
Ca, Calcium (wt.%)	5.93	5.82	6.04	5.84	6.03
Cd, Cadmium (ppm)	0.62	0.60	0.65	0.59	0.65
Ce, Cerium (ppm)	14.0	13.2	14.7	13.5	14.4
Co, Cobalt (ppm)	41.5	40.5	42.5	40.6	42.4
Cr, Chromium (ppm)	86	84	88	84	89
Cs, Caesium (ppm)	1.01	0.97	1.05	0.96	1.05
Cu, Copper (ppm)	170	167	172	166	173
Dy, Dysprosium (ppm)	3.94	3.78	4.10	3.78	4.09
Er, Erbium (ppm)	2.43	2.31	2.55	2.35	2.51
Eu, Europium (ppm)	0.96	0.94	0.98	0.93	1.00
Fe, Iron (wt.%)	8.00	7.88	8.13	7.87	8.14
Ga, Gallium (ppm)	16.1	15.3	17.0	15.7	16.5
Gd, Gadolinium (ppm)	3.47	3.30	3.64	3.33	3.62
Hf, Hafnium (ppm)	1.80	1.76	1.84	1.70	1.90
Ho, Holmium (ppm)	0.86	0.83	0.89	0.83	0.88
In, Indium (ppm)	0.080	0.076	0.083	0.073	0.086
K, Potassium (wt.%)	0.559	0.550	0.568	0.550	0.568
La, Lanthanum (ppm)	5.99	5.73	6.25	5.81	6.16
Li, Lithium (ppm)	10.5	10.2	10.8	10.2	10.8
Lu, Lutetium (ppm)	0.37	0.35	0.40	0.35	0.39
Mg, Magnesium (wt.%)	3.40	3.35	3.44	3.35	3.44
Mn, Manganese (wt.%)	0.133	0.130	0.136	0.131	0.135

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb (parts per billion).

*Gold Tolerance Limits for typical 30g fire assay, 25g aqua regia digestion and 200g cyanide leach methods are determined from 20 x 85mg INAA results and the Sampling Constant (Ingamells & Switzer, 1973).

Note: intervals may appear asymmetric due to rounding.

Table 4 continued.

Constituent	Certified	95% Confidence Limits		95% Tolerance Limits	
	Value	Low	High	Value	Low
4-Acid Digestion continued					
Mo, Molybdenum (ppm)	1.56	1.46	1.66	1.48	1.64
Na, Sodium (wt.%)	2.15	2.13	2.18	2.12	2.19
Nb, Niobium (ppm)	3.63	3.48	3.77	3.48	3.77
Nd, Neodymium (ppm)	9.01	8.69	9.33	8.82	9.20
Ni, Nickel (ppm)	68	67	70	67	70
P, Phosphorus (wt.%)	0.045	0.044	0.047	0.044	0.046
Pb, Lead (ppm)	30.5	29.6	31.4	29.6	31.4
Pr, Praseodymium (ppm)	1.94	1.86	2.02	1.88	2.00
Rb, Rubidium (ppm)	14.1	13.7	14.5	13.7	14.4
Re, Rhenium (ppm)	0.003	0.002	0.003	IND	IND
S, Sulphur (wt.%)	0.444	0.436	0.452	0.434	0.454
Sb, Antimony (ppm)	1.76	1.69	1.84	1.67	1.85
Sc, Scandium (ppm)	38.5	37.6	39.4	37.3	39.7
Se, Selenium (ppm)	< 5	IND	IND	IND	IND
Sm, Samarium (ppm)	2.71	2.59	2.82	2.62	2.80
Sn, Tin (ppm)	1.08	1.01	1.15	IND	IND
Sr, Strontium (ppm)	95	93	97	93	97
Ta, Tantalum (ppm)	0.25	0.23	0.27	0.23	0.27
Tb, Terbium (ppm)	0.62	0.59	0.64	0.59	0.64
Te, Tellurium (ppm)	0.11	0.10	0.12	IND	IND
Th, Thorium (ppm)	1.10	1.05	1.15	1.05	1.15
Ti, Titanium (wt.%)	0.639	0.626	0.651	0.623	0.654
Tl, Thallium (ppm)	0.24	0.23	0.25	0.23	0.25
Tm, Thulium (ppm)	0.36	0.34	0.38	0.34	0.37
U, Uranium (ppm)	0.35	0.33	0.36	0.32	0.37
V, Vanadium (ppm)	279	272	286	271	288
W, Tungsten (ppm)	30.5	29.8	31.3	29.5	31.6
Y, Yttrium (ppm)	21.7	21.3	22.0	21.3	22.0
Yb, Ytterbium (ppm)	2.32	2.21	2.43	2.28	2.37
Zn, Zinc (ppm)	144	141	147	141	146
Zr, Zirconium (ppm)	55	53	56	53	57
Aqua Regia Digestion					
Ag, Silver (ppm)	0.488	0.474	0.502	0.467	0.508
Al, Aluminium (wt.%)	3.16	3.08	3.23	3.09	3.22
As, Arsenic (ppm)	67	65	68	65	68
B, Boron (ppm)	90	84	96	88	92
Ba, Barium (ppm)	35.7	34.3	37.1	34.7	36.7
Be, Beryllium (ppm)	0.26	0.25	0.28	0.23	0.29

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb (parts per billion).

Note: intervals may appear asymmetric due to rounding.

Table 4 continued.

Constituent	Certified	95% Confidence Limits		95% Tolerance Limits	
	Value	Low	High	Value	Low
Aqua Regia Digestion continued					
Bi, Bismuth (ppm)	0.062	0.059	0.065	IND	IND
Ca, Calcium (wt.%)	2.64	2.54	2.73	2.57	2.70
Cd, Cadmium (ppm)	0.61	0.60	0.63	0.58	0.65
Ce, Cerium (ppm)	10.6	10.4	10.8	10.4	10.9
Co, Cobalt (ppm)	30.8	29.8	31.8	29.9	31.7
Cr, Chromium (ppm)	32.8	32.0	33.6	32.0	33.6
Cs, Caesium (ppm)	0.73	0.71	0.74	0.71	0.74
Cu, Copper (ppm)	169	167	172	166	173
Dy, Dysprosium (ppm)	2.58	2.34	2.83	2.45	2.72
Er, Erbium (ppm)	1.52	1.31	1.74	1.31	1.74
Eu, Europium (ppm)	0.58	0.48	0.68	0.54	0.62
Fe, Iron (wt.%)	5.95	5.86	6.05	5.86	6.04
Ga, Gallium (ppm)	11.6	11.3	11.9	11.2	12.0
Gd, Gadolinium (ppm)	2.24	2.07	2.41	2.12	2.36
Ge, Germanium (ppm)	0.15	0.13	0.16	IND	IND
Hf, Hafnium (ppm)	0.54	0.51	0.57	0.52	0.56
Hg, Mercury (ppm)	0.046	0.037	0.056	0.027	0.066
Ho, Holmium (ppm)	0.53	0.45	0.60	IND	IND
In, Indium (ppm)	0.039	0.038	0.040	0.034	0.043
K, Potassium (wt.%)	0.134	0.130	0.138	0.130	0.139
La, Lanthanum (ppm)	4.72	4.59	4.86	4.59	4.85
Li, Lithium (ppm)	9.28	9.02	9.54	9.03	9.53
Lu, Lutetium (ppm)	0.18	0.17	0.20	IND	IND
Mg, Magnesium (wt.%)	1.72	1.70	1.74	1.70	1.75
Mn, Manganese (wt.%)	0.071	0.070	0.073	0.070	0.072
Mo, Molybdenum (ppm)	1.49	1.46	1.52	1.43	1.54
Na, Sodium (wt.%)	0.265	0.258	0.273	0.257	0.273
Nb, Niobium (ppm)	0.16	0.12	0.19	IND	IND
Nd, Neodymium (ppm)	6.89	6.50	7.27	6.68	7.10
Ni, Nickel (ppm)	48.8	47.4	50.3	47.8	49.9
P, Phosphorus (wt.%)	0.045	0.044	0.046	0.044	0.046
Pb, Lead (ppm)	30.5	29.6	31.3	29.3	31.6
Pr, Praseodymium (ppm)	1.43	1.26	1.60	1.32	1.54
Rb, Rubidium (ppm)	5.87	5.63	6.11	5.65	6.09
Re, Rhenium (ppm)	0.002	0.002	0.002	IND	IND
S, Sulphur (wt.%)	0.445	0.434	0.457	0.434	0.456
Sb, Antimony (ppm)	0.90	0.74	1.05	0.82	0.98
Sc, Scandium (ppm)	6.47	6.11	6.83	6.22	6.73

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb (parts per billion).

Note: intervals may appear asymmetric due to rounding.

Table 4 continued.

Constituent	Certified	95% Confidence Limits		95% Tolerance Limits	
	Value	Low	High	Value	Low
Aqua Regia Digestion continued					
Se, Selenium (ppm)	< 1	IND	IND	IND	IND
Sm, Samarium (ppm)	1.89	1.67	2.11	1.76	2.01
Sn, Tin (ppm)	0.68	0.66	0.71	IND	IND
Sr, Strontium (ppm)	29.7	28.6	30.9	28.9	30.6
Ta, Tantalum (ppm)	< 0.01	IND	IND	IND	IND
Tb, Terbium (ppm)	0.39	0.37	0.41	0.37	0.41
Te, Tellurium (ppm)	0.11	0.10	0.11	IND	IND
Th, Thorium (ppm)	0.88	0.85	0.90	0.83	0.92
Ti, Titanium (wt.%)	0.387	0.359	0.415	0.375	0.399
Tl, Thallium (ppm)	0.13	0.12	0.13	IND	IND
Tm, Thulium (ppm)	0.20	0.17	0.22	IND	IND
U, Uranium (ppm)	0.24	0.24	0.25	0.23	0.25
V, Vanadium (ppm)	158	153	163	154	162
W, Tungsten (ppm)	22.6	21.1	24.1	21.8	23.4
Y, Yttrium (ppm)	12.9	12.5	13.3	12.5	13.3
Yb, Ytterbium (ppm)	1.29	1.17	1.41	1.17	1.41
Zn, Zinc (ppm)	133	130	136	130	136
Zr, Zirconium (ppm)	17.8	16.8	18.9	17.0	18.6

SI unit equivalents: ppm (parts per million) \equiv mg/kg \equiv μ g/g \equiv 0.0001 wt.% \equiv 1000 ppb (parts per billion).

Note: intervals may appear asymmetric due to rounding.

Table 5. Neutron Activation Analysis of Au (in ppm) on 20 x 85mg subsamples and showing the equivalent results scaled to a 30g sample mass typical of fire assay determination.

Replicate No	Au 85mg actual	Au 30g equivalent*
1	1.853	1.901
2	1.904	1.904
3	1.943	1.906
4	1.951	1.906
5	1.822	1.899
6	1.782	1.897
7	1.937	1.906
8	1.859	1.901
9	1.998	1.909
10	1.953	1.906
11	1.905	1.904
12	1.930	1.905
13	1.894	1.903
14	1.987	1.908
15	1.906	1.904
16	1.884	1.903
17	1.969	1.907
18	1.858	1.901
19	1.852	1.901
20	1.887	1.903
Mean	1.904	1.904
Median	1.905	1.904
Std Dev.	0.056	0.003
Rel.Std.Dev.	2.95%	0.158%

*Results calculated for a 30g equivalent sample mass using the formula: $x^{30g Eq} = \frac{(x^{INAA} - \bar{X}) \times RSD@30g}{RSD@85mg} + \bar{X}$
 where $x^{30g Eq}$ = equivalent result calculated for a 30g sample mass
 (x^{INAA}) = raw INAA result at 85mg
 \bar{X} = mean of 85mg INAA results

Table 5 below shows the gold INAA data determined on 20 x 85mg subsamples of OREAS 230. An equivalent scaled version of the results is also provided to demonstrate the level of repeatability that would be achieved if 30g fire assay determinations were undertaken without the normal measurement error associated with this methodology. The homogeneity of gold has been determined by INAA using the reduced analytical subsample method which utilises the known relationship between standard deviation and analytical subsample weight (Ingamells and Switzer, 1973). In this approach the sample aliquot is substantially reduced to a point where most of the variability in replicate assays should be due to inhomogeneity of the reference material (i.e., sampling error) and measurement error becomes negligible. In this instance a subsample weight of 85 milligrams was employed and the 1RSD of 0.158% was calculated for a 30g fire assay sample (2.95% at 85mg weights) and confirms the high level of gold homogeneity in OREAS 236.

The homogeneity of OREAS 236 has also been evaluated in a **nested ANOVA** of the round robin program. Each of the forty-two round robin laboratories received six samples per CRM and these samples were made up of paired samples from three different, non-

adjacent sampling intervals. The purpose of the ANOVA evaluation is to test that no statistically significant difference exists in the variance between units to that of the variance within units. This allows an assessment of homogeneity across the entire prepared batch of OREAS 236. The test was performed using the following parameters:

- Gold fire assay – 156 samples (26 laboratories each providing analyses on 3 pairs of samples);
- Gold aqua regia digestion – 132 samples (22 laboratories each providing analyses on 3 pairs of samples);
- Gold cyanide leach – 108 samples (18 laboratories each providing analyses on 3 pairs of samples);
- Null Hypothesis, H_0 : Between-unit variance is no greater than within-unit variance (reject H_0 if p -value < 0.05);
- Alternative Hypothesis, H_1 : Between-unit variance is greater than within-unit variance.

P -values are a measure of probability where values less than 0.05 indicate a greater than 95% probability that the observed differences in within-unit and between-unit variances are real. The datasets were filtered for both individual and laboratory data set (batch) outliers prior to the calculation of the p -value.

This process derived p -values of 0.981 for Au by fire assay, 0.995 for Au by aqua regia digestion and 0.526 for Au by cyanide leach. All p -values are insignificant and the Null Hypothesis is retained. Additionally, none of the other certified values showed significant p -values.

Only results for constituents present in concentrations well above the detection levels (i.e. $>20 \times$ Lower Limit of Detection) for the various methods undertaken were considered for the objective of evaluating homogeneity. It is important to note that ANOVA is not an absolute measure of homogeneity. Rather, it establishes whether or not the analytes are distributed in a similar manner throughout the packaging run of OREAS 236 and whether the variance between two subsamples from the same unit is statistically distinguishable from the variance of two subsamples taken from any two separate units. A reference material therefore can possess poor absolute homogeneity yet still pass a relative homogeneity (ANOVA) test if the within-unit heterogeneity is large and similar across all units.

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS 236 is fit-for-purpose as a certified reference material (see 'Intended Use' below).

PREPARER AND SUPPLIER

Certified reference material OREAS 236 was prepared, certified and supplied by:



ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.oreas.com
Email: info@ore.com.au

PARTICIPATING LABORATORIES

1. Actlabs, Ancaster, Ontario, Canada
2. Alex Stewart International, Mendoza, Argentina
3. ALS, Lima, Peru
4. ALS, Loughrea, Galway, Ireland
5. ALS, Perth, WA, Australia
6. ALS, Vancouver, BC, Canada
7. ANSTO, Lucas Heights, NSW, Australia
8. Bureau Veritas Commodities Canada Ltd, Vancouver, BC, Canada
9. Bureau Veritas Geoanalytical, Perth, WA, Australia
10. CRS Laboratories Oy, Kempele, Northern Ostrobothnia, Finland
11. ESAN Istanbul, Istanbul, Turkey
12. Inspectorate (BV), Lima, Peru
13. Intertek Genalysis, Perth, WA, Australia
14. Intertek Genalysis, Perth, WA, Australia
15. Intertek Tarkwa, Tarkwa, Ghana
16. Intertek Testing Services Philippines, Cupang, Muntinlupa, Philippines
17. MinAnalytical Services, Kalgoorlie, WA, Australia
18. MinAnalytical Services, Perth, WA, Australia
19. MSALABS, Vancouver, BC, Canada
20. On Site Laboratory Services, Bendigo, VIC, Australia
21. Ostrea Mineral Laboratories, Inc., Laguna, Philippines
22. PT Geoservices Ltd, Cikarang, Jakarta Raya, Indonesia
23. PT Intertek Utama Services, Jakarta Timur, DKI Jakarta, Indonesia
24. Reminex Centre de Recherche, Marrakesh, Marrakesh-Safi, Morocco
25. SGS, Randfontein, Gauteng, South Africa
26. SGS Canada Inc., Vancouver, BC, Canada
27. SGS del Peru, Lima, Peru
28. SGS Tarkwa, Tarkwa, Western Region, Ghana
29. Shiva Analyticals Ltd, Bangalore North, Karnataka, India
30. Skyline Assayers & Laboratories, Tucson, Arizona, USA

Please note: To preserve anonymity, the above numbered alphabetical list of participating laboratories does not correspond with the Lab ID numbering on the scatter plots below.

Figure 1. Au by Pb Fire Assay in OREAS 236

SPC.1573.RR Au Phase 6.OREAS 236.4.Fire Assay.Au.Lab.210917.001911.SN




Figure 2. Au by Aqua Regia Digestion (sample weights 10-50g) in OREAS 236

SPC.1573.RR Au Phase 6.OREAS 236.4.AR Digest 10-50g.Au.Lab.210917.025213.SN




Figure 3. Au by Cyanide Leach in OREAS 236

SPC.1573.RR Au Phase 6.OREAS 236.4.CNL.Au.Lab.210917.002125.SS





Figure 4. Au by X-ray Photon Assay in OREAS 236

SPC.1573.RR Au Phase 6.OREAS 236.3.XRPA.Au.Lab.210921.140100.SN



METROLOGICAL TRACEABILITY

The analytical samples were selected in a manner representative of the entire batch of the prepared CRM. This 'representivity' was maintained in each submitted laboratory sample batch and ensures the user that the data is traceable from sample selection through to the analytical results that underlie the consensus values. Each analytical data set has been validated by its assayer through the inclusion of internal reference materials and QC checks during analysis.

The laboratories were chosen on the basis of their competence (from past performance in inter-laboratory programs undertaken by ORE Pty Ltd) for a particular analytical method, analyte or analyte suite and sample matrix. Most of these laboratories have and maintain ISO 17025 accreditation. The certified values presented in this report are calculated from the means of accepted data following robust statistical treatment, as detailed in this report.

Guide ISO/TR 16476:2016, section 5.3.1 describes metrological traceability in reference materials as it pertains to the transformation of the measurand. In this section it states, *"Although the determination of the property value itself can be made traceable to appropriate units through, for example, calibration of the measurement equipment used, steps like the transformation of the sample from one physical (chemical) state to another cannot. Such transformations may only be compared with a reference (when available), or among themselves. For some transformations, reference methods have been defined and may be used in certification projects to evaluate the uncertainty associated with such a transformation. In other cases, **only a comparison among different laboratories using the same method is possible. In this case, certification takes place on the basis of agreement among independent measurement results** (see ISO Guide 35:2006, Clause 10)."*

COMMUTABILITY

The measurements of the results that underlie the certified values contained in this report were undertaken by methods involving pre-treatment (digestion/fusion) of the sample. This served to reduce the sample to a simple and well understood form permitting calibration using simple solutions of the CRM. Due to these methods being well understood and highly effective, commutability is not an issue for this CRM. All OREAS CRMs are sourced from natural ore minerals meaning they will display similar behaviour as routine 'field' samples in the relevant measurement process. Care should be taken to ensure 'matrix matching' as close as practically achievable. The matrix and mineralisation style of the CRM is described in the 'Source Material' section and users should select appropriate CRMs matching these attributes to their field samples.

INTENDED USE

OREAS 236 is intended to cover all activities needed to produce a measurement result. This includes extraction, possible separation steps and the actual measurement process (the signal producing step). OREAS 236 may be used to calibrate the entire procedure by producing a pure substance CRM transformed into a calibration solution.

OREAS 236 is intended for the following uses:

- For the monitoring of laboratory performance in the analysis of analytes reported in Table 1 in geological samples;

- For the verification of analytical methods for analytes reported in Table 1;
- For the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 236 is low in reactive sulphide (0.38 wt.% S) and in its unopened state and under normal conditions of storage has a shelf life beyond ten years. Its stability will be monitored at regular intervals and purchasers notified if any changes are observed.

Single-use sachets

Following analysis of the CRM subsample it is the manufacturers' expectation that any remaining material is discarded. The stability of the material after opening the sachet is not within the scope of proper use. However, if opened sachets are resealed after opening, then under ordinary* storage conditions the CRM will have a shelf-life beyond ten years.

**ordinary storage conditions: means storage not in direct sunlight in a dry, clean, well ventilated area at temperatures between -5° and 50°C.*

Repeat-use packaging (e.g., 1kg plastic jars)

The stability of the CRM after opening the lid of the plastic jar is only affected by local atmospheric conditions with regard to oxidation and hygroscopic change. There is no segregation affect (please see our [Technical Note on Particle Segregation](#)).

The primary cause of change through oxidation is in relation to the breakdown of sulphide minerals to sulphates and is negligible for OREAS 236 given its low sulphur concentration (0.38 wt.% S).

Hygroscopic change is the amount of absorbed moisture (weakly held H₂O- molecules on the surface of exposed material) following exposure to the local atmosphere. Usually, equilibration of material to the local atmosphere will only occur if the material is spread into a thin (~2mm thick) layer and left exposed for a period of 2 hours. OREAS 236 contains a non-hygroscopic matrix and therefore, exposure to a local atmosphere that is significantly different (in terms of temperature and humidity) from the climate during manufacturing will have negligible impact on the precision of results. The 'Physical Properties' section indicates the approximate moisture concentration.

INSTRUCTIONS FOR CORRECT USE

The certified values for OREAS 236 refer to the concentration level in its packaged state. It should not be dried prior to weighing and analysis. 1kg jars permit repeated sampling as long as the lid is promptly re-secured to prevent airborne contamination.

Minimum sample size

As a practical guide, the minimum mass of sample used should match the typical mass that the laboratories used in the interlaboratory (round robin) certification program. This means that different sample masses should be used depending on the operationally defined methodology.

- Au by fire assay: $\geq 25\text{g}$;
- Au by aqua regia digestion: $\geq 15\text{g}$;
- Au by cyanide leach: $\geq 20\text{g}$;
- Au by PhotonAssay: $\sim 350\text{g}$;
- 4-acid digestion with ICP-OES and/or MS finish: $\geq 0.25\text{g}$;
- Aqua regia digestion with ICP-OES and/or MS finish: $\geq 0.5\text{g}$.

QC monitoring using multiples of the Standard Deviation (SD)

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program.

The majority of data generated in the round robin program was produced by a selection of world class laboratories. The SD's thus generated are more constrained than those that would be produced across a randomly selected group of laboratories. To produce more generally achievable SD's the 'pooled' SD's provided in this report include inter-laboratory bias. This 'one size fits all' approach may require revision at the discretion of the QC manager concerned following careful scrutiny of QC control charts.

The performance gates shown in Table 1 are intended only to be used as a first principle guide as to what a laboratory may be able to achieve. Over a period of time monitoring your own laboratory's data for this CRM, SDs should be calculated directly from your own laboratory's process. This will enable you to establish more specific performance gates that are fit for purpose for your application as well as the ability to monitor bias. If your long-term trend analysis shows an average value that is within the 95% confidence interval then generally there is no cause for concern in regard to bias.

It is important to note that in the analytical industry there is no standardisation of the aqua regia digestion process. This method is a partial empirical digest and differences in recoveries for various analytes are commonplace. These are caused by variations in the digest conditions and can include the ratio of nitric to hydrochloric acids, acid strength, temperatures, leach times and secondary digestions. Recoveries for sulphide-hosted base metal sulphides approach total values, however, other analytes, in particular the lithophile elements, show greater sensitivity to method parameters. This can result in lack of consensus in an inter-laboratory certification program for these elements.

The approach applied here is to report certified values in those instances where reasonable agreement exists amongst a majority of participating laboratories. The results of specific laboratories may differ significantly from the certified values, but will, nonetheless, be valid and reproducible in the context of the specifics of the aqua regia method in use. Users of this reference material should, therefore, be mindful of this limitation when applying the certified values in a quality control program.

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions including the use of safety glasses and dust masks are advised.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

DOCUMENT HISTORY

Revision No.	Date	Changes applied
1	29 th Oct, 2021	Corrected list of 'Participating Laboratories'.
0	22 nd Sep, 2021	First publication.

CERTIFYING OFFICER



29th Oct, 2021

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

QMS CERTIFICATION

ORE Pty Ltd is ISO 9001:2015 certified by Lloyd's Register Quality Assurance Ltd for its quality management system including development, manufacturing, certification and supply of CRMs.



REFERENCES

Govett, G.J.S. (1983). Handbook of Exploration Geochemistry, Volume 2: Statistics and Data Analysis in Geochemical Prospecting (Variations of accuracy and precision).

Ingamells, C. O. and Switzer, P. (1973). Talanta 20, 547-568.

ISO Guide 30:2015. Terms and definitions used in connection with reference materials.

ISO Guide 31:2015. Reference materials – Contents of certificates and labels.

ISO Guide 35:2017. Certification of reference materials - General and statistical principals.

ISO 16269:2014. Statistical interpretation of data – Part 6: Determination of statistical tolerance intervals.

ISO/TR 16476:2016, Reference Materials – Establishing and expressing metrological traceability of quantity values assigned to reference materials.

ISO 17025:2005, General requirements for the competence of testing and calibration laboratories.

Munsell Rock Color Book (2014). Rock-Color Chart Committee, Geological Society of America (GSA), 4300 44th Street SE, Grand Rapids, MI 49512.