



ORE RESEARCH & EXPLORATION P/L ABN 28 006 859 856
37A Hosie Street · Bayswater North · VIC 3153 · AUSTRALIA
☎ 61 3 9729 0333 📠 61 3 9729 8338
📧 info@ore.com.au 🌐 www.oreas.com

CERTIFICATE OF ANALYSIS FOR

Gold Ore (Frogs Leg Gold Mine, Western Australia)

CERTIFIED REFERENCE MATERIAL OREAS 234


Table 1. Certified Values and Performance Gates for OREAS 234.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Pb Fire Assay											
Au, ppm	1.20	0.030	1.14	1.26	1.12	1.29	2.46%	4.92%	7.38%	1.14	1.26
Aqua Regia Digestion (sample mass 10-50g)											
Au, ppm	1.12	0.058	1.00	1.23	0.94	1.29	5.19%	10.37%	15.56%	1.06	1.17
Cyanide Leach											
Au, ppm	1.17	0.064	1.04	1.29	0.97	1.36	5.48%	10.95%	16.43%	1.11	1.22
Photon Assay (recommended gross mass 510-540 g)											
Au, ppm	1.19	0.047	1.09	1.28	1.05	1.33	3.95%	7.90%	11.85%	1.13	1.25
Aqua Regia Digestion											
Ag, ppm	0.341	0.029	0.283	0.399	0.254	0.428	8.51%	17.01%	25.52%	0.324	0.358
Al, wt. %	3.53	0.171	3.18	3.87	3.01	4.04	4.85%	9.69%	14.54%	3.35	3.70
As, ppm	55	2.0	51	59	49	61	3.59%	7.18%	10.77%	52	58
B, ppm	19.8	3.9	12.0	27.5	8.2	31.3	19.51%	39.03%	58.54%	18.8	20.7
Ba, ppm	29.6	2.07	25.5	33.8	23.4	35.8	6.98%	13.96%	20.94%	28.2	31.1
Be, ppm	0.27	0.021	0.22	0.31	0.20	0.33	7.90%	15.80%	23.69%	0.25	0.28

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt. % (weight per cent) \equiv % (mass fraction).

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.



Document: COA-1495-OREAS234-R3

(Template: BUP-70-10-01 Rev: 2.0)

4-Jun-2025

Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Bi, ppm	0.045	0.005	0.034	0.056	0.029	0.061	12.08%	24.17%	36.25%	0.043	0.047
Ca, wt. %	2.87	0.38	2.11	3.64	1.72	4.02	13.35%	26.69%	40.04%	2.73	3.02
Cd, ppm	0.54	0.028	0.49	0.60	0.46	0.63	5.07%	10.14%	15.20%	0.52	0.57
Ce, ppm	10.1	0.56	9.0	11.2	8.4	11.8	5.59%	11.17%	16.76%	9.6	10.6
Co, ppm	29.3	1.43	26.4	32.1	25.0	33.6	4.88%	9.76%	14.64%	27.8	30.7
Cr, ppm	21.7	1.74	18.2	25.1	16.4	26.9	8.03%	16.06%	24.09%	20.6	22.7
Cs, ppm	0.67	0.045	0.58	0.76	0.53	0.80	6.70%	13.41%	20.11%	0.63	0.70
Cu, ppm	174	7	161	187	154	194	3.85%	7.71%	11.56%	165	183
Dy, ppm	2.06	0.180	1.70	2.42	1.52	2.60	8.76%	17.52%	26.28%	1.96	2.16
Er, ppm	1.28	0.18	0.91	1.64	0.73	1.82	14.24%	28.47%	42.71%	1.21	1.34
Eu, ppm	0.42	0.06	0.31	0.53	0.25	0.59	13.53%	27.06%	40.59%	0.40	0.44
Fe, wt. %	5.39	0.194	5.00	5.77	4.80	5.97	3.61%	7.22%	10.83%	5.12	5.65
Ga, ppm	10.1	0.88	8.4	11.9	7.5	12.8	8.71%	17.41%	26.12%	9.6	10.6
Gd, ppm	1.97	0.24	1.49	2.45	1.24	2.70	12.30%	24.60%	36.91%	1.87	2.07
Ge, ppm	0.11	0.02	0.06	0.15	0.04	0.17	21.30%	42.59%	63.89%	0.10	0.11
Hf, ppm	0.51	0.09	0.34	0.69	0.25	0.77	16.83%	33.66%	50.49%	0.49	0.54
Ho, ppm	0.42	0.04	0.33	0.51	0.28	0.55	10.57%	21.14%	31.71%	0.40	0.44
In, ppm	0.036	0.004	0.027	0.045	0.023	0.049	12.26%	24.53%	36.79%	0.034	0.038
K, wt. %	0.157	0.013	0.131	0.182	0.118	0.195	8.17%	16.34%	24.51%	0.149	0.165
La, ppm	4.37	0.189	3.99	4.74	3.80	4.93	4.32%	8.63%	12.95%	4.15	4.58
Li, ppm	10.1	0.76	8.6	11.6	7.9	12.4	7.48%	14.95%	22.43%	9.6	10.6
Lu, ppm	0.16	0.02	0.12	0.20	0.10	0.22	12.09%	24.19%	36.28%	0.15	0.17
Mg, wt. %	1.63	0.063	1.50	1.75	1.44	1.82	3.87%	7.74%	11.61%	1.55	1.71
Mn, wt. %	0.074	0.004	0.065	0.082	0.060	0.087	6.06%	12.11%	18.17%	0.070	0.077
Mo, ppm	1.39	0.061	1.26	1.51	1.20	1.57	4.40%	8.80%	13.20%	1.32	1.45
Na, wt. %	0.217	0.014	0.189	0.244	0.176	0.257	6.26%	12.52%	18.78%	0.206	0.227
Nd, ppm	6.02	0.65	4.71	7.32	4.06	7.98	10.85%	21.69%	32.54%	5.72	6.32
Ni, ppm	55	4.7	46	65	41	69	8.43%	16.86%	25.30%	53	58
P, wt. %	0.039	0.002	0.035	0.043	0.033	0.045	5.19%	10.38%	15.57%	0.037	0.041
Pb, ppm	26.2	1.82	22.6	29.9	20.8	31.7	6.92%	13.84%	20.76%	24.9	27.6
Pr, ppm	1.32	0.119	1.09	1.56	0.97	1.68	8.96%	17.93%	26.89%	1.26	1.39
Pt, ppb	13.9	0.9	12.2	15.7	11.3	16.6	6.34%	12.68%	19.03%	13.2	14.6
Rb, ppm	6.39	0.620	5.15	7.63	4.53	8.25	9.70%	19.40%	29.10%	6.07	6.71
Re, ppm	0.002	0.000	0.001	0.003	0.000	0.003	27.49%	54.98%	82.47%	0.002	0.002
S, wt. %	0.370	0.026	0.319	0.421	0.293	0.447	6.95%	13.91%	20.86%	0.351	0.388
Sb, ppm	0.81	0.24	0.34	1.28	0.10	1.52	29.14%	58.27%	87.41%	0.77	0.85
Sc, ppm	6.46	0.505	5.45	7.47	4.95	7.97	7.82%	15.63%	23.45%	6.14	6.78
Sm, ppm	1.56	0.116	1.33	1.79	1.22	1.91	7.41%	14.81%	22.22%	1.48	1.64
Sn, ppm	0.62	0.08	0.45	0.79	0.37	0.87	13.63%	27.25%	40.88%	0.59	0.65
Sr, ppm	48.8	7.7	33.4	64.1	25.7	71.8	15.75%	31.49%	47.24%	46.3	51.2

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt. % (weight per cent) \equiv % (mass fraction).

Note 1: intervals may appear asymmetric due to rounding;

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Ta, ppm	< 0.01	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tb, ppm	0.32	0.026	0.27	0.37	0.25	0.40	7.97%	15.94%	23.91%	0.31	0.34
Te, ppm	0.094	0.010	0.075	0.114	0.065	0.124	10.53%	21.05%	31.58%	0.090	0.099
Th, ppm	0.83	0.09	0.66	1.01	0.57	1.10	10.58%	21.17%	31.75%	0.79	0.88
Ti, wt. %	0.325	0.049	0.226	0.423	0.177	0.472	15.18%	30.37%	45.55%	0.308	0.341
Tl, ppm	0.12	0.007	0.11	0.14	0.10	0.15	5.91%	11.83%	17.74%	0.12	0.13
Tm, ppm	0.18	0.02	0.14	0.22	0.12	0.23	10.63%	21.26%	31.90%	0.17	0.19
U, ppm	0.20	0.011	0.18	0.22	0.17	0.23	5.21%	10.41%	15.62%	0.19	0.21
V, ppm	136	16	105	167	89	183	11.52%	23.04%	34.55%	129	143
W, ppm	18.1	2.8	12.5	23.8	9.7	26.6	15.47%	30.93%	46.40%	17.2	19.1
Y, ppm	11.6	1.3	9.0	14.1	7.8	15.3	10.88%	21.76%	32.64%	11.0	12.1
Yb, ppm	1.12	0.12	0.88	1.37	0.76	1.49	10.87%	21.74%	32.60%	1.07	1.18
Zn, ppm	123	5	113	132	109	137	3.78%	7.57%	11.35%	117	129
Zr, ppm	17.7	1.59	14.6	20.9	13.0	22.5	8.96%	17.92%	26.88%	16.9	18.6
4-Acid Digestion											
Ag, ppm	0.338	0.015	0.308	0.368	0.293	0.382	4.41%	8.82%	13.24%	0.321	0.355
Al, wt. %	7.05	0.175	6.70	7.41	6.53	7.58	2.48%	4.97%	7.45%	6.70	7.41
As, ppm	55	3.6	48	63	45	66	6.54%	13.07%	19.61%	53	58
Ba, ppm	129	4	122	137	118	140	2.84%	5.68%	8.52%	123	136
Be, ppm	0.42	0.029	0.36	0.48	0.34	0.51	6.96%	13.91%	20.87%	0.40	0.44
Bi, ppm	0.047	0.009	0.029	0.065	0.020	0.074	19.00%	38.01%	57.01%	0.045	0.049
Ca, wt. %	7.08	0.285	6.51	7.65	6.23	7.94	4.03%	8.06%	12.09%	6.73	7.44
Cd, ppm	0.57	0.030	0.51	0.63	0.48	0.66	5.24%	10.48%	15.72%	0.54	0.59
Ce, ppm	12.9	0.72	11.5	14.3	10.7	15.0	5.56%	11.12%	16.68%	12.2	13.5
Co, ppm	41.2	2.17	36.9	45.6	34.7	47.8	5.27%	10.55%	15.82%	39.2	43.3
Cr, ppm	110	12	87	133	75	145	10.53%	21.05%	31.58%	104	115
Cs, ppm	0.92	0.040	0.84	1.00	0.80	1.04	4.33%	8.66%	12.98%	0.88	0.97
Cu, ppm	175	6	164	187	158	192	3.28%	6.57%	9.85%	166	184
Dy, ppm	3.60	0.191	3.22	3.98	3.03	4.18	5.30%	10.60%	15.90%	3.42	3.78
Er, ppm	2.17	0.087	1.99	2.34	1.91	2.43	4.03%	8.05%	12.08%	2.06	2.28
Eu, ppm	0.90	0.047	0.81	1.00	0.76	1.05	5.24%	10.49%	15.73%	0.86	0.95
Fe, wt. %	7.53	0.225	7.08	7.98	6.85	8.20	2.99%	5.98%	8.97%	7.15	7.90
Ga, ppm	15.5	0.65	14.2	16.8	13.6	17.5	4.18%	8.35%	12.53%	14.8	16.3
Gd, ppm	3.18	0.233	2.72	3.65	2.48	3.88	7.32%	14.64%	21.96%	3.02	3.34
Hf, ppm	1.64	0.103	1.44	1.85	1.34	1.95	6.25%	12.50%	18.75%	1.56	1.73
Ho, ppm	0.76	0.052	0.66	0.86	0.61	0.92	6.77%	13.55%	20.32%	0.72	0.80
In, ppm	0.074	0.009	0.056	0.092	0.047	0.100	12.04%	24.09%	36.13%	0.070	0.078
K, wt. %	0.460	0.018	0.424	0.496	0.406	0.514	3.95%	7.89%	11.84%	0.437	0.483
La, ppm	5.51	0.313	4.88	6.13	4.57	6.45	5.68%	11.36%	17.04%	5.23	5.78
Li, ppm	11.0	0.81	9.4	12.7	8.6	13.5	7.36%	14.73%	22.09%	10.5	11.6

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt. % (weight per cent) \equiv % (mass fraction).

Note 1: intervals may appear asymmetric due to rounding; IND: indeterminate.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 1 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
Lu, ppm	0.31	0.019	0.28	0.35	0.26	0.37	5.95%	11.90%	17.85%	0.30	0.33
Mg, wt. %	3.59	0.125	3.34	3.84	3.21	3.97	3.49%	6.99%	10.48%	3.41	3.77
Mn, wt. %	0.130	0.004	0.122	0.138	0.118	0.142	3.09%	6.18%	9.27%	0.123	0.136
Mo, ppm	1.49	0.108	1.28	1.71	1.17	1.82	7.21%	14.42%	21.62%	1.42	1.57
Na, wt. %	1.64	0.069	1.51	1.78	1.44	1.85	4.22%	8.44%	12.65%	1.56	1.73
Nb, ppm	3.36	0.226	2.91	3.81	2.68	4.04	6.73%	13.46%	20.19%	3.19	3.53
Nd, ppm	8.32	0.370	7.58	9.06	7.21	9.43	4.45%	8.90%	13.35%	7.90	8.73
Ni, ppm	81	3.9	74	89	70	93	4.77%	9.55%	14.32%	77	85
P, wt. %	0.041	0.002	0.037	0.045	0.036	0.046	4.40%	8.80%	13.20%	0.039	0.043
Pb, ppm	26.4	1.36	23.7	29.1	22.3	30.5	5.16%	10.32%	15.48%	25.1	27.7
Pr, ppm	1.75	0.088	1.57	1.93	1.49	2.01	5.02%	10.05%	15.07%	1.66	1.84
Rb, ppm	14.0	0.75	12.5	15.4	11.7	16.2	5.34%	10.68%	16.02%	13.3	14.6
S, wt. %	0.376	0.028	0.320	0.431	0.293	0.459	7.37%	14.75%	22.12%	0.357	0.395
Sb, ppm	1.50	0.100	1.30	1.70	1.20	1.80	6.69%	13.39%	20.08%	1.42	1.57
Sc, ppm	38.7	1.70	35.3	42.1	33.6	43.8	4.40%	8.80%	13.20%	36.8	40.7
Sm, ppm	2.43	0.097	2.24	2.62	2.14	2.72	3.99%	7.98%	11.96%	2.31	2.55
Sn, ppm	0.98	0.096	0.78	1.17	0.69	1.26	9.85%	19.69%	29.54%	0.93	1.02
Sr, ppm	211	10	192	230	182	240	4.59%	9.18%	13.78%	200	221
Ta, ppm	0.23	0.02	0.18	0.28	0.15	0.30	10.94%	21.88%	32.81%	0.22	0.24
Tb, ppm	0.55	0.040	0.47	0.63	0.43	0.67	7.33%	14.66%	21.99%	0.52	0.57
Te, ppm	0.096	0.015	0.065	0.127	0.049	0.142	16.14%	32.28%	48.42%	0.091	0.101
Th, ppm	1.03	0.073	0.89	1.18	0.81	1.25	7.07%	14.14%	21.20%	0.98	1.08
Ti, wt. %	0.587	0.022	0.543	0.631	0.521	0.653	3.75%	7.51%	11.26%	0.558	0.616
Tl, ppm	0.23	0.013	0.21	0.26	0.20	0.27	5.46%	10.91%	16.37%	0.22	0.25
Tm, ppm	0.31	0.015	0.28	0.34	0.27	0.36	4.91%	9.82%	14.74%	0.30	0.33
U, ppm	0.29	0.020	0.25	0.33	0.23	0.35	7.06%	14.12%	21.18%	0.28	0.30
V, ppm	263	9	244	281	235	290	3.45%	6.91%	10.36%	249	276
W, ppm	26.2	1.62	23.0	29.5	21.4	31.1	6.19%	12.38%	18.57%	24.9	27.5
Y, ppm	19.5	0.93	17.6	21.3	16.7	22.2	4.76%	9.52%	14.28%	18.5	20.4
Yb, ppm	2.14	0.112	1.92	2.37	1.81	2.48	5.25%	10.49%	15.74%	2.04	2.25
Zn, ppm	135	7	120	150	113	157	5.53%	11.06%	16.60%	128	142
Zr, ppm	55	4.5	46	63	41	68	8.20%	16.41%	24.61%	52	57

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt. % (weight per cent) \equiv % (mass fraction).

Note 1: intervals may appear asymmetric due to rounding.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

TABLE OF CONTENTS

INTRODUCTION	6
SOURCE MATERIAL	7
PERFORMANCE GATES	7
COMMUNITION AND HOMOGENISATION PROCEDURES	8
PHYSICAL PROPERTIES	8
ANALYTICAL PROGRAM	8
STATISTICAL ANALYSIS	9
Homogeneity Evaluation	10
PREPARER AND SUPPLIER	16
PARTICIPATING LABORATORIES	16
METROLOGICAL TRACEABILITY	22
COMMUTABILITY	22
INTENDED USE	22
INSTRUCTIONS FOR CORRECT USE	23
HANDLING INSTRUCTIONS	24
LEGAL NOTICE	24
DOCUMENT HISTORY	24
QMS CERTIFICATION	24
CERTIFYING OFFICER	25
REFERENCES	25

LIST OF TABLES

Table 1. Certified Values and Performance Gates for OREAS 234.	1
Table 2. Indicative Values for OREAS 234.	6
Table 3. Physical properties of OREAS 234.	8
Table 4. Certified Values, Uncertainty & Tolerance Intervals for OREAS 234.	11
Table 5. Neutron Activation Analysis of Au on 20 x 85mg subsamples	15

LIST OF FIGURES

Figure 1. Au by Fire Assay in OREAS 234	18
Figure 2. Au by aqua regia digestion in OREAS 234	19
Figure 3. Au by cyanide leach in OREAS 234	20
Figure 4. Au by x-ray PhotonAssay in OREAS 234	21

Table 2. Indicative Values for OREAS 234.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Pb Fire Assay								
Pd	ppb	10.0	Pt	ppb	15.0			
Aqua Regia Digestion								
Hg	ppm	0.037	Pd	ppb	11.8	Si	wt. %	0.110
Nb	ppm	0.19	Se	ppm	0.72			
Borate Fusion XRF								
Al ₂ O ₃	wt. %	13.43	MgO	wt. %	6.15	SiO ₂	wt. %	51.87
CaO	wt. %	10.18	MnO	wt. %	0.170	SO ₃	wt. %	0.904
Fe ₂ O ₃	wt. %	10.97	Na ₂ O	wt. %	2.16	TiO ₂	wt. %	1.01
K ₂ O	wt. %	0.547	P ₂ O ₅	wt. %	0.096			
4-Acid Digestion								
B	ppm	1157	Hg	ppm	< 2	Se	ppm	0.94
Ge	ppm	0.17	Re	ppm	0.002			
Thermogravimetry								
LOI ¹⁰⁰⁰	wt. %	3.35						
Infrared Combustion								
C	wt. %	0.125	S	wt. %	0.340			
Laser Ablation ICP-MS								
Ag	ppm	0.400	Hf	ppm	2.05	Sm	ppm	2.52
As	ppm	55	Ho	ppm	0.81	Sn	ppm	1.00
Ba	ppm	135	In	ppm	0.050	Sr	ppm	209
Be	ppm	0.60	La	ppm	5.73	Ta	ppm	0.22
Bi	ppm	0.050	Lu	ppm	0.34	Tb	ppm	0.59
Cd	ppm	0.65	Mn	wt. %	0.135	Te	ppm	< 0.2
Ce	ppm	12.7	Mo	ppm	1.40	Th	ppm	1.07
Co	ppm	43.6	Nb	ppm	3.54	Ti	wt. %	0.605
Cr	ppm	137	Nd	ppm	8.92	Tl	ppm	< 0.2
Cs	ppm	0.89	Ni	ppm	91	Tm	ppm	0.34
Cu	ppm	191	Pb	ppm	28.0	U	ppm	0.32
Dy	ppm	3.64	Pr	ppm	1.84	V	ppm	282
Er	ppm	2.36	Rb	ppm	14.0	W	ppm	27.0
Eu	ppm	0.92	Re	ppm	< 0.01	Y	ppm	20.5
Ga	ppm	15.5	Sb	ppm	1.65	Yb	ppm	2.31
Gd	ppm	3.26	Sc	ppm	39.3	Zn	ppm	140
Ge	ppm	1.48	Se	ppm	< 5	Zr	ppm	65

SI unit equivalents: ppb (parts per billion; 1×10^{-9}) \equiv $\mu\text{g/kg}$; ppm (parts per million; 1×10^{-6}) \equiv mg/kg ; wt. % (weight per cent) \equiv % (mass fraction).

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

INTRODUCTION

OREAS reference materials are intended to provide a low-cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical

equipment, assessing new techniques and routinely monitoring in-house procedures. OREAS reference materials enable users to successfully achieve process control of these tasks because the observed variance from repeated analysis has its origin almost exclusively in the analytical process rather than the reference material itself. In evaluating laboratory performance with this CRM, the section headed 'Instructions for correct use' should be read carefully.

Table 1 provides performance gate intervals for the certified values based on their pooled 1SD's. Table 2 shows indicative values including major and trace element characterisation by Bureau Veritas in Perth, Western Australia which includes:

- Major oxides by lithium borate fusion with X-ray fluorescence;
- LOI at 1000°C by thermogravimetric analyser;
- Total Carbon and Sulphur by Infrared combustion furnace;
- Trace element characterisation by laser ablation with ICP-MS finish.

Table 3 provides some indicative physical properties and Table 4 presents the 95% confidence and tolerance limits for all certified values. Gold homogeneity (via INAA) is shown in Table 5 and is also demonstrated by a nested ANOVA program using fire assay (see '**nested ANOVA**' section).

Tabulated results of all elements (including Au INAA analyses) together with uncorrected means, medians, standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**OREAS 234-DataPack.1.2.230609_113424.xlsx**).

Results are also presented in scatter plots for gold by fire assay, aqua regia digestion, cyanide leach and PhotonAssay (Figures 1 to 4, respectively) together with $\pm 3SD$ (magenta) and $\pm 5\%$ (yellow) control lines and certified value (green line). Accepted individual results are coloured blue and individual and dataset outliers are identified in red and violet, respectively.

SOURCE MATERIAL

Certified Reference Material (CRM) OREAS 234 was prepared from a blend of gold-bearing ore and barren greenstone. The ore was sourced from the Frogs Leg Gold Mine located 19km west of Kalgoorlie in Western Australia. The Cambrian greenstone was sourced from a quarry 145km north of Melbourne, Australia.

PERFORMANCE GATES

Table 1 above shows intervals calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned (also see 'Intended Use' section below). Westgard Rules extend the basics of single-rule QC monitoring using multi-rules (for more information visit www.westgard.com/mltirule.htm). A second method utilises a 5% window calculated directly from the certified value.

Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow. One approach used at commercial laboratories is to set the acceptance criteria at twice the detection level (DL) \pm 10%.

i.e., Certified Value \pm 10% \pm 2DL (adapted from Govett, 1983).

COMMINUTION AND HOMOGENISATION PROCEDURES

The material constituting OREAS 234 was prepared in the following manner:

- Drying the gold ore and greenstone to constant mass at 105°C;
- Crushing and multi stage milling of gold ore to 100% minus 30 microns;
- Crushing and multi stage milling of greenstone to >98% minus 75 microns;
- Final homogenisation;
- Packaging in 60g units sealed in laminated foil pouches and 1kg units in plastic jars.

PHYSICAL PROPERTIES

OREAS 234 was tested at ORE Research & Exploration Pty Ltd's onsite facility for various physical properties. Table 3 presents these findings that should be used for informational purposes only.

Table 3. Physical properties of OREAS 234.

Bulk Density (g/L)	Moisture%	Munsell Notation [‡]	Munsell Color [‡]
928.1	0.7	5GY 6/1	Greenish Gray

[‡]The Munsell Rock Color Chart helps geologists and archeologists communicate with colour more effectively by cross-referencing ISCC-NBS colour names with unique Munsell alpha-numeric colour notations for rock colour samples.

ANALYTICAL PROGRAM

Thirty-one commercial analytical laboratories participated in the program to certify the elements reported in Table 1. The following methods were employed:

- Gold by fire assay (15-40g charge weight) with AAS (19 laboratories), ICP-OES (11 laboratories) or ICP-MS finish (1 laboratory);
- Gold by aqua regia digestion (15-50g sample weight) with ICP-MS (14 laboratories), AAS (7 laboratories) or ICP-OES finish (1 laboratory);
- Gold by cyanide leach; a variety of cyanide leach methods were undertaken by the participating laboratories including the use of LeachWELL tablets, alkaline added sodium cyanide solution as well as sodium cyanide liquor with LeachWELL powder. The sample weights included: 20g (1 laboratory by AAS finish), 30g (7 laboratories by AAS finish), 50g (3 laboratories by ICP finish and 1 laboratory by AAS finish), 60g

(1 laboratory by ICP finish) and 200g (6 laboratories by AAS and 1 laboratory by ICP finish).

- Gold by x-ray PhotonAssay with recommended gross mass 510-540 g (12 Chrysos PhotonAssay units at 7 laboratories with two rounds of data reported from each unit);
- Full ICP-OES and ICP-MS elemental suites by aqua regia digestion (up to 25 laboratories depending on the element);
- Full ICP-OES and ICP-MS elemental suites by 4-acid (HNO_3 -HF- HClO_4 -HCl) digestion (up to 25 laboratories depending on the element).

To confirm homogeneity, gold by instrumental neutron activation analysis (INAA) was undertaken on 20 x 85mg subsamples by the Australian Nuclear Science and Technology Organisation (ANSTO) located in Lucas Heights, NSW, Australia (see Table 5 in the 'Homogeneity Evaluation' section below).

For the round robin characterisation program, twenty 3kg test units were taken at predetermined intervals during the bagging stage, immediately following homogenisation and are considered representative of the entire prepared batch. For all analytical methods except for Au by PhotonAssay, six pulp samples were submitted to each laboratory for analysis (the weight provided depended on whether the laboratory was anticipated to undertake assays by gold cyanide leach). The samples received by each laboratory were obtained by taking two samples from each of three separate 3kg test units. This format enabled a nested ANOVA treatment of the results to evaluate homogeneity, i.e., to ascertain whether between-unit variance is greater than within-unit variance.

For the Au by PhotonAssay (PA) characterisation program, a 1kg sample was provided for analysis to each PA equipped laboratory. Each 1kg sample underwent the following preparation and analysis:

1. Send 1kg of each candidate reference material to each PA equipped laboratory.
2. From the 1kg sample provided, Chrysos staff prepare two PA jars (~350g each), conduct weight/fill measurements and run both samples through PA machine three times to get a total of 6 measurements.
3. Material is returned to 1kg tub.
4. Steps 2-3 are repeated for each machine operating at that laboratory (3 machines for Intertek Perth, 2 machines at ALS Perth, 3 machines at ALS Kalgoorlie; 1 machine for the other laboratories).
5. 1kg tub of material is then handed over to the internal staff to repeat steps 2-4.

For certification purposes, the steps above generate a total of 144 results from seven participating PA equipped laboratories.

STATISTICAL ANALYSIS

Certified Values and their uncertainty intervals (Table 4 below) have been determined for each analyte following removal of individual, laboratory dataset (batch) and 3SD outliers (single iteration).

For individual outliers within a laboratory batch the z-score test is used in combination with a second method that determines the per cent deviation of the individual value from the batch median. Outliers in general are selected on the basis of z-scores > 2.5 and with per cent deviations (i) > 3 and (ii) more than three times the average absolute per cent deviation for the batch. Each laboratory data set mean is tested for outlying status based on z-score

discrimination and rejected if > 2.5 . After individual and laboratory data set (batch) outliers have been eliminated a non-iterative 3 standard deviation filter is applied, with those values lying outside this window also relegated to outlying status. However, while statistics are taken into account, the exercise of a statistician's prerogative plays a significant role in identifying outliers.

Certified Values are the means of accepted laboratory means after outlier filtering and are the present best estimate of the true value. The INAA data (Table 5) is omitted from determination of the certified value for Au and is used solely for the calculation of Tolerance Limits and homogeneity evaluation of OREAS 234 (see 'Homogeneity Evaluation' section below).

The 95% Expanded Uncertainty provides a 95% probability that the true value of the analyte under consideration lies between the upper and lower limits and is calculated according to the method in ISO Guides [6,16]. All known or suspected sources of bias have been investigated or taken into account.

Indicative (uncertified) values (Table 2) are present where the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification. These major and trace element characterisation values are presented for informational purposes only.

Standard Deviation intervals (Table 1) provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability.

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program (see 'Intended Use' section for more detail).

The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e., after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e., the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM.

The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.

Homogeneity Evaluation

For analytes other than gold, the tolerance limits (ISO 16269:2014) shown in Table 4 were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for copper by 4-acid digestion, where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($p=0.95$) will have concentrations lying between 170 and 178 ppm. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

Please note that tolerance limits pertain to the homogeneity of the CRM only and should not be used as control limits for laboratory performance.

Table 4. Certified Values, Uncertainty & Tolerance Intervals for OREAS 234.

Constituent	Certified	95% Expanded Uncertainty		95% Tolerance Limits	
	Value	Low	High	Value	Low
Pb Fire Assay					
Au, Gold (ppm)	1.204	1.194	1.214	1.199*	1.209*
Aqua Regia Digestion (sample weights 10-50g)					
Au, Gold (ppm)	1.116	1.091	1.142	1.111*	1.122*
Cyanide Leach					
Au, Gold (ppm)	1.166	1.135	1.197	1.161*	1.171*
PhotonAssay (recommended gross mass 510-540 g)					
Au, Gold (ppm)	1.186	1.176	1.197	1.185*	1.188*
Aqua Regia Digestion					
Ag, Silver (ppm)	0.341	0.316	0.366	0.324	0.358
Al, Aluminium (wt.%)	3.53	3.41	3.64	3.46	3.60
As, Arsenic (ppm)	55	53	57	54	56
B, Boron (ppm)	19.8	16.5	23.0	IND	IND
Ba, Barium (ppm)	29.6	28.0	31.3	28.7	30.5
Be, Beryllium (ppm)	0.27	0.22	0.31	0.23	0.30
Bi, Bismuth (ppm)	0.045	0.037	0.053	IND	IND
Ca, Calcium (wt.%)	2.87	2.68	3.07	2.81	2.94
Cd, Cadmium (ppm)	0.54	0.51	0.57	0.52	0.57
Ce, Cerium (ppm)	10.1	9.8	10.4	9.9	10.3
Co, Cobalt (ppm)	29.3	28.6	30.0	28.6	30.0
Cr, Chromium (ppm)	21.7	20.7	22.7	21.0	22.3
Cs, Caesium (ppm)	0.67	0.64	0.69	0.65	0.69
Cu, Copper (ppm)	174	170	178	170	178
Dy, Dysprosium (ppm)	2.06	1.87	2.25	1.99	2.13
Er, Erbium (ppm)	1.28	1.10	1.45	1.20	1.35
Eu, Europium (ppm)	0.42	0.35	0.49	0.40	0.44
Fe, Iron (wt.%)	5.39	5.24	5.53	5.29	5.48
Ga, Gallium (ppm)	10.1	9.6	10.7	9.8	10.4
Gd, Gadolinium (ppm)	1.97	1.74	2.20	1.89	2.05
Ge, Germanium (ppm)	0.11	0.08	0.13	IND	IND

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt.% (weight per cent) \equiv % (mass fraction).

*Gold Tolerance Limits for typical 30g fire assay, 25g aqua regia digestion, 200g cyanide leach and 350g PhotonAssay methods are determined from 20 x 85mg INAA results and the Sampling Constant (Ingamells & Switzer, 1973).

IND: indeterminate (due to limited reading resolution of the methods employed).

Note: intervals may appear asymmetric due to rounding.

Table 4 continued.

Constituent	Certified	95% Expanded Uncertainty		95% Tolerance Limits	
	Value	Low	High	Value	Low
Aqua Regia Digestion continued					
Hf, Hafnium (ppm)	0.51	0.46	0.57	0.49	0.54
Ho, Holmium (ppm)	0.42	0.37	0.46	0.40	0.43
In, Indium (ppm)	0.036	0.031	0.041	0.030	0.042
K, Potassium (wt.%)	0.157	0.149	0.165	0.154	0.160
La, Lanthanum (ppm)	4.37	4.23	4.50	4.27	4.46
Li, Lithium (ppm)	10.1	9.7	10.6	9.8	10.5
Lu, Lutetium (ppm)	0.16	0.14	0.18	IND	IND
Mg, Magnesium (wt.%)	1.63	1.59	1.67	1.60	1.66
Mn, Manganese (wt.%)	0.074	0.071	0.076	0.072	0.075
Mo, Molybdenum (ppm)	1.39	1.32	1.45	1.32	1.45
Na, Sodium (wt.%)	0.217	0.208	0.225	0.209	0.224
Nd, Neodymium (ppm)	6.02	5.42	6.61	5.81	6.23
Ni, Nickel (ppm)	55	53	58	54	57
P, Phosphorus (wt.%)	0.039	0.038	0.040	0.038	0.040
Pb, Lead (ppm)	26.2	25.1	27.4	25.5	27.0
Pr, Praseodymium (ppm)	1.32	1.19	1.46	1.28	1.37
Pt, Platinum (ppb)	13.9	12.4	15.5	IND	IND
Rb, Rubidium (ppm)	6.39	6.05	6.74	6.23	6.56
Re, Rhenium (ppm)	0.002	0.001	0.003	IND	IND
S, Sulphur (wt.%)	0.370	0.355	0.385	0.360	0.380
Sb, Antimony (ppm)	0.81	0.68	0.94	0.78	0.85
Sc, Scandium (ppm)	6.46	6.08	6.84	6.24	6.68
Sm, Samarium (ppm)	1.56	1.44	1.69	1.51	1.61
Sn, Tin (ppm)	0.62	0.56	0.68	0.60	0.64
Sr, Strontium (ppm)	48.8	44.8	52.8	47.2	50.4
Ta, Tantalum (ppm)	< 0.01	IND	IND	IND	IND
Tb, Terbium (ppm)	0.32	0.30	0.35	0.31	0.33
Te, Tellurium (ppm)	0.094	0.079	0.110	IND	IND
Th, Thorium (ppm)	0.83	0.75	0.91	0.82	0.85
Ti, Titanium (wt.%)	0.325	0.298	0.352	0.315	0.334
Tl, Thallium (ppm)	0.12	0.12	0.13	IND	IND
Tm, Thulium (ppm)	0.18	0.16	0.20	0.17	0.19
U, Uranium (ppm)	0.20	0.19	0.22	0.19	0.22
V, Vanadium (ppm)	136	127	145	133	138
W, Tungsten (ppm)	18.1	16.8	19.5	17.7	18.6
Y, Yttrium (ppm)	11.6	10.8	12.3	11.2	11.9

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt.% (weight per cent) \equiv % (mass fraction).

IND: indeterminate (due to limited reading resolution of the methods employed; for practical purposes the 95% Expanded Uncertainty can be set between zero and a two times multiple of an upper bound/non-detect limit value).

Note: intervals may appear asymmetric due to rounding.

Table 4 continued.

Constituent	Certified	95% Expanded Uncertainty		95% Tolerance Limits	
	Value	Low	High	Value	Low
Aqua Regia Digestion continued					
Yb, Ytterbium (ppm)	1.12	0.99	1.25	1.06	1.18
Zn, Zinc (ppm)	123	120	126	120	125
Zr, Zirconium (ppm)	17.7	16.5	19.0	17.2	18.3
4-Acid Digestion					
Ag, Silver (ppm)	0.338	0.322	0.354	0.316	0.359
Al, Aluminium (wt.%)	7.05	6.89	7.22	6.94	7.17
As, Arsenic (ppm)	55	53	58	53	58
Ba, Barium (ppm)	129	126	133	125	133
Be, Beryllium (ppm)	0.42	0.37	0.48	0.37	0.47
Bi, Bismuth (ppm)	0.047	0.039	0.055	IND	IND
Ca, Calcium (wt.%)	7.08	6.89	7.27	6.98	7.18
Cd, Cadmium (ppm)	0.57	0.54	0.60	0.54	0.59
Ce, Cerium (ppm)	12.9	12.3	13.5	12.6	13.2
Co, Cobalt (ppm)	41.2	39.9	42.6	40.3	42.1
Cr, Chromium (ppm)	110	103	117	106	114
Cs, Caesium (ppm)	0.92	0.88	0.97	0.87	0.97
Cu, Copper (ppm)	175	169	181	171	179
Dy, Dysprosium (ppm)	3.60	3.46	3.74	3.48	3.72
Er, Erbium (ppm)	2.17	2.10	2.24	2.10	2.24
Eu, Europium (ppm)	0.90	0.85	0.96	0.88	0.93
Fe, Iron (wt.%)	7.53	7.33	7.73	7.40	7.66
Ga, Gallium (ppm)	15.5	14.8	16.2	15.1	16.0
Gd, Gadolinium (ppm)	3.18	2.96	3.40	3.06	3.31
Hf, Hafnium (ppm)	1.64	1.53	1.76	1.57	1.72
Ho, Holmium (ppm)	0.76	0.71	0.82	0.73	0.79
In, Indium (ppm)	0.074	0.064	0.083	0.067	0.080
K, Potassium (wt.%)	0.460	0.446	0.474	0.450	0.470
La, Lanthanum (ppm)	5.51	5.27	5.75	5.37	5.65
Li, Lithium (ppm)	11.0	10.4	11.7	10.6	11.5
Lu, Lutetium (ppm)	0.31	0.29	0.34	0.30	0.33
Mg, Magnesium (wt.%)	3.59	3.49	3.69	3.53	3.65
Mn, Manganese (wt.%)	0.130	0.127	0.133	0.128	0.132
Mo, Molybdenum (ppm)	1.49	1.40	1.58	1.38	1.60
Na, Sodium (wt.%)	1.64	1.60	1.69	1.62	1.67
Nb, Niobium (ppm)	3.36	3.17	3.54	3.23	3.48
Nd, Neodymium (ppm)	8.32	7.93	8.70	8.10	8.53
Ni, Nickel (ppm)	81	79	84	80	83

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt.% (weight per cent) \equiv % (mass fraction).

IND: indeterminate (due to limited reading resolution of the methods employed).

Note: intervals may appear asymmetric due to rounding.

Table 4 continued.

Constituent	Certified	95% Expanded Uncertainty		95% Tolerance Limits	
	Value	Low	High	Value	Low
4-Acid Digestion continued					
P, Phosphorus (wt.%)	0.041	0.039	0.042	0.040	0.042
Pb, Lead (ppm)	26.4	25.3	27.5	25.7	27.1
Pr, Praseodymium (ppm)	1.75	1.65	1.85	1.69	1.81
Rb, Rubidium (ppm)	14.0	13.5	14.4	13.6	14.3
S, Sulphur (wt.%)	0.376	0.360	0.391	0.366	0.385
Sb, Antimony (ppm)	1.50	1.41	1.58	1.44	1.56
Sc, Scandium (ppm)	38.7	37.3	40.2	37.5	40.0
Sm, Samarium (ppm)	2.43	2.30	2.56	2.35	2.51
Sn, Tin (ppm)	0.98	0.90	1.05	IND	IND
Sr, Strontium (ppm)	211	205	217	206	216
Ta, Tantalum (ppm)	0.23	0.21	0.25	0.21	0.25
Tb, Terbium (ppm)	0.55	0.51	0.59	0.53	0.57
Te, Tellurium (ppm)	0.096	0.073	0.119	IND	IND
Th, Thorium (ppm)	1.03	0.95	1.11	1.00	1.06
Ti, Titanium (wt.%)	0.587	0.571	0.603	0.570	0.604
Tl, Thallium (ppm)	0.23	0.22	0.25	0.22	0.25
Tm, Thulium (ppm)	0.31	0.29	0.33	0.30	0.33
U, Uranium (ppm)	0.29	0.27	0.31	0.28	0.30
V, Vanadium (ppm)	263	253	272	254	271
W, Tungsten (ppm)	26.2	25.2	27.2	25.7	26.8
Y, Yttrium (ppm)	19.5	18.7	20.3	19.0	19.9
Yb, Ytterbium (ppm)	2.14	2.03	2.25	2.06	2.22
Zn, Zinc (ppm)	135	130	140	132	138
Zr, Zirconium (ppm)	55	51	58	52	57

SI unit equivalents: ppm (parts per million; 1×10^{-6}) \equiv mg/kg; wt.% (weight per cent) \equiv % (mass fraction).

IND: indeterminate (due to limited reading resolution of the methods employed).

Note: intervals may appear asymmetric due to rounding.

Table 5 below shows the gold INAA data determined on 20 x 85mg subsamples of OREAS 234. An equivalent scaled version of the results is also provided to demonstrate the level of repeatability that would be achieved if 30g fire assay determinations were undertaken without the normal measurement error associated with this methodology. The homogeneity of gold has been determined by INAA using the reduced analytical subsample method which utilises the known relationship between standard deviation and analytical subsample weight (Ingamells and Switzer, 1973). In this approach the sample aliquot is substantially reduced to a point where most of the variability in replicate assays should be due to inhomogeneity of the reference material (i.e., sampling error) and measurement error becomes negligible. In this instance a subsample weight of 85 milligrams was employed and the 1RSD of 0.135% was calculated for a 30g fire assay sample (2.52% at 85mg weights) and confirms the high level of gold homogeneity in OREAS 234.

Table 5. Neutron Activation Analysis of Au (in ppm) on 20 x 85mg subsamples and showing the equivalent results scaled to a 30g sample mass typical of fire assay determination.

Replicate No	Au 85mg actual	Au 30g equivalent*
1	1.239	1.211
2	1.198	1.209
3	1.224	1.210
4	1.166	1.207
5	1.216	1.210
6	1.238	1.211
7	1.207	1.210
8	1.222	1.210
9	1.226	1.211
10	1.155	1.207
11	1.198	1.209
12	1.235	1.211
13	1.216	1.210
14	1.160	1.207
15	1.252	1.212
16	1.168	1.207
17	1.216	1.210
18	1.178	1.208
19	1.258	1.212
20	1.221	1.210
Mean	1.210	1.210
Median	1.216	1.210
Std Dev.	0.031	0.002
Rel.Std.Dev.	2.52%	0.135%

*Results calculated for a 30g equivalent sample mass using the formula: $x^{30g Eq} = \frac{(x^{INAA} - \bar{X}) \times RSD@30g}{RSD@85mg} + \bar{X}$
where $x^{30g Eq}$ = equivalent result calculated for a 30g sample mass
 (x^{INAA}) = raw INAA result at 85mg
 \bar{X} = mean of 85mg INAA results

The homogeneity of OREAS 234 has also been evaluated in a **nested ANOVA** of the round robin program. Each of the forty-two round robin laboratories received six samples per CRM and these samples were made up of paired samples from three different, non-adjacent sampling intervals. The purpose of the ANOVA evaluation is to test that no statistically significant difference exists in the variance between units to that of the variance within units. This allows an assessment of homogeneity across the entire prepared batch of OREAS 234. The test was performed using the following parameters:

- Gold fire assay – 186 samples (31 laboratories each providing analyses on 3 pairs of samples);
- Gold aqua regia digestion – 132 samples (22 laboratories each providing analyses on 3 pairs of samples);
- Gold cyanide leach – 120 samples (20 laboratories each providing analyses on 3 pairs of samples);
- Gold PhotonAssay – 48 samples (Chrysos and internal staff both conduct triplicate analysis of 2 PA jars across 12 PA machines [installed across 7 laboratories]);

- Null Hypothesis, H_0 : Between-unit variance is no greater than within-unit variance (reject H_0 if p -value < 0.05);
- Alternative Hypothesis, H_1 : Between-unit variance is greater than within-unit variance.

P -values are a measure of probability where values less than 0.05 indicate a greater than 95% probability that the observed differences in within-unit and between-unit variances are real. The datasets were filtered for both individual and laboratory data set (batch) outliers prior to the calculation of the p -value.

This process derived p -values of 0.99 for Au by fire assay, 0.57 for Au by aqua regia digestion, 0.27 for Au by cyanide leach and 0.687 for Au by PhotonAssay. All p -values are insignificant and the Null Hypothesis is retained. Additionally, none of the other certified values showed significant p -values.

Only results for constituents present in concentrations well above the detection levels (i.e., >20 x Lower Limit of Detection) for the various methods undertaken were considered for the objective of evaluating homogeneity. It is important to note that ANOVA is not an absolute measure of homogeneity. Rather, it establishes whether or not the analytes are distributed in a similar manner throughout the packaging run of OREAS 234 and whether the variance between two subsamples from the same unit is statistically distinguishable from the variance of two subsamples taken from any two separate units. A reference material therefore can possess poor absolute homogeneity yet still pass a relative homogeneity (ANOVA) test if the within-unit heterogeneity is large and similar across all units.

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS 234 is fit-for-purpose as a certified reference material (see 'Intended Use' below).

PREPARER AND SUPPLIER

Certified reference material OREAS 211 was prepared, certified and supplied by:



ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.oreas.com
Email: info@ore.com.au

PARTICIPATING LABORATORIES

1. Actlabs, Ancaster, Ontario, Canada
2. AGAT Laboratories, Mississauga, Ontario, Canada
3. Alex Stewart International, Mendoza, Argentina
4. ALS (formerly MinAnalytical Services), Canning Vale, WA, Australia
5. ALS, Kalgoorlie, WA, Australia
6. ALS, Lima, Peru
7. ALS, Loughrea, Galway, Ireland
8. ALS, Perth, WA, Australia

9. ALS, Reno, Nevada, USA
10. ALS, Vancouver, BC, Canada
11. ANSTO, Lucas Heights, NSW, Australia
12. Bureau Veritas Commodities and Trade, Inc., Sparks, Nevada, USA
13. Bureau Veritas Commodities Canada Ltd, Vancouver, BC, Canada
14. Bureau Veritas Geoanalytical, Adelaide, SA, Australia
15. Bureau Veritas Geoanalytical, Perth, WA, Australia
16. ESAN Istanbul, Istanbul, Turkey
17. Inspectorate (BV), Lima, Peru
18. Intertek Genalysis, Adelaide, SA, Australia
19. Intertek Genalysis, Perth, WA, Australia
20. Intertek Tarkwa, Tarkwa, Ghana
21. Intertek Testing Services Philippines, Cupang, Muntinlupa, Philippines
22. MSA ENVAL Laboratories, Yamoussoukro, Côte d'Ivoire
23. MSALABS, Val-d'Or, Quebec, Canada
24. MSALABS, Vancouver, BC, Canada
25. Nagrom, Perth, WA, Australia
26. On Site Laboratory Services, Bendigo, VIC, Australia
27. PT Geoservices Ltd, Cikarang, Jakarta Raya, Indonesia
28. PT Intertek Utama Services, Jakarta Timur, DKI Jakarta, Indonesia
29. Ravenswood Gold, Ravenswood, QLD, Australia
30. Saskatchewan Research Council, Saskatoon, Saskatchewan, Canada
31. SGS, Randfontein, Gauteng, South Africa
32. SGS Australia Mineral Services, Kalgoorlie, WA, Australia
33. SGS Australia Mineral Services, Perth, WA, Australia
34. SGS Canada Inc., Vancouver, BC, Canada
35. SGS del Peru, Lima, Peru
36. SGS Tarkwa, Tarkwa, Western Region, Ghana
37. Skyline Assayers & Laboratories, Tucson, Arizona, USA

Please note: To preserve anonymity, the above numbered alphabetical list of participating laboratories does not correspond with the Lab ID numbering on the scatter plots below.

Figure 1. Au by Fire Assay in OREAS 234

SPC.1495.RR1.OREAS 234.4.Fire Assay.Au.Lab.210514.013827.SN




Figure 2. Au by AR Digest 10-50g in OREAS 234

SPC.1495.RR1.OREAS 234.4.AR Digest 10-50g.Au.Lab.210514.013919.SN




Figure 3. Au by CNL in OREAS 234

SPC.1495.RR1.OREAS 234.4.CNL.Au.Lab.210514.013955.SN





Figure 4. Au by PhotonAssay in OREAS 234

SPC.1757.RR1.OREAS 234.3.PA.Au.Lab.230620.185445.SN



METROLOGICAL TRACEABILITY

The analytical samples were selected in a manner representative of the entire batch of the prepared CRM. This 'representivity' was maintained in each submitted laboratory sample batch and ensures the user that the data is traceable from sample selection through to the analytical results that underlie the consensus values. Each analytical data set has been validated by its assayer through the inclusion of internal reference materials and QC checks during analysis.

The laboratories were chosen on the basis of their competence (from past performance in inter-laboratory programs undertaken by ORE Pty Ltd) for a particular analytical method, analyte or analyte suite and sample matrix. Most of these laboratories have and maintain ISO 17025 accreditation. The certified values presented in this report are calculated from the means of accepted data following robust statistical treatment, as detailed in this report.

Guide ISO/TR 16476:2016, section 5.3.1 describes metrological traceability in reference materials as it pertains to the transformation of the measurand. In this section it states, *"Although the determination of the property value itself can be made traceable to appropriate units through, for example, calibration of the measurement equipment used, steps like the transformation of the sample from one physical (chemical) state to another cannot. Such transformations may only be compared with a reference (when available), or among themselves. For some transformations, reference methods have been defined and may be used in certification projects to evaluate the uncertainty associated with such a transformation. In other cases, only a comparison among different laboratories using the same procedure is possible. In this case, it is impossible to demonstrate absence of method bias; therefore, the result is an operationally defined measurand (ISO Guide 35:2017, 9.2.4c)."* Certification takes place on the basis of agreement among operationally defined, independent measurement results.

COMMUTABILITY

The measurements of the results that underlie the certified values contained in this report were undertaken by methods involving pre-treatment (digestion/fusion) of the sample. This served to reduce the sample to a simple and well understood form permitting calibration using simple solutions of the CRM. Due to these methods being well understood and highly effective, commutability is not an issue for this CRM. All OREAS CRMs are sourced from natural ore minerals meaning they will display similar behaviour as routine 'field' samples in the relevant measurement process. Care should be taken to ensure 'matrix matching' as close as practically achievable. The matrix and mineralisation style of the CRM is described in the 'Source Material' section and users should select appropriate CRMs matching these attributes to their field samples.

INTENDED USE

OREAS 234 is intended to cover all activities needed to produce a measurement result. This includes extraction, possible separation steps and the actual measurement process (the signal producing step). OREAS 234 may be used to calibrate the entire procedure by producing a pure substance CRM transformed into a calibration solution.

OREAS 234 is intended for the following uses:

- For the monitoring of laboratory performance in the analysis of analytes reported in Table 1 in geological samples;
- For the verification of analytical methods for analytes reported in Table 1;
- For the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

QC monitoring using multiples of the Standard Deviation (SD)

In the application of SD's in monitoring performance it is important to note that not all laboratories function at the same level of proficiency and that different methods in use at a particular laboratory have differing levels of precision. Each laboratory has its own inherent SD (for a specific concentration level and analyte-method pair) based on the analytical process and this SD is not directly related to the round robin program.

The majority of data generated in the round robin program was produced by a selection of world class laboratories. The SD's thus generated are more constrained than those that would be produced across a randomly selected group of laboratories. To produce more generally achievable SD's the 'pooled' SD's provided in this report include inter-laboratory bias. This 'one size fits all' approach may require revision at the discretion of the QC manager concerned following careful scrutiny of QC control charts.

The performance gates shown in Table 1 are intended only to be used as an initial guide as to what a laboratory may be able to achieve. Over a period of time monitoring your own laboratory's data for this CRM, SDs should be calculated directly from your own laboratory's process. This will enable you to establish more specific performance gates that are fit for purpose for your application as well as the ability to monitor bias. If your long-term trend analysis shows an average value that is within the 95% expanded uncertainty interval then generally there is no cause for concern in regard to bias.

It is important to note that in the analytical industry there is no standardisation of the aqua regia digestion process. This method is a partial empirical digest and differences in recoveries for various analytes are commonplace. These are caused by variations in the digest conditions and can include the ratio of nitric to hydrochloric acids, acid strength, temperatures, leach times and secondary digestions. Recoveries for sulphide-hosted base metal sulphides approach total values, however, other analytes, in particular the lithophile elements, show greater sensitivity to method parameters. This can result in lack of consensus in an inter-laboratory certification program for these elements. The approach applied here is to report certified values in those instances where reasonable agreement exists amongst a majority of participating laboratories. The results of specific laboratories may differ significantly from the certified values, but will, nonetheless, be valid and reproducible in the context of the specifics of the aqua regia method in use. Users of this reference material should, therefore, be mindful of this limitation when applying the certified values in a quality control program.

INSTRUCTIONS FOR CORRECT USE

The certified values for OREAS 234 refer to the concentration level in its packaged state. It should not be dried prior to weighing and analysis.

Minimum sample size

As a practical guide, the minimum mass of sample used should match the typical mass that the laboratories used in the interlaboratory (round robin) certification program. This means

that different sample masses should be used depending on the operationally defined methodology.

- Au by fire assay: $\geq 25\text{g}$;
- Au by aqua regia digestion: $\geq 15\text{g}$;
- Au by cyanide leach: $\geq 20\text{g}$;
- Au by PhotonAssay: recommended gross mass* 510-540 g;
- 4-acid digestion with ICP-OES and/or MS finish: $\geq 0.25\text{g}$;
- Aqua regia digestion with ICP-OES and/or MS finish: $\geq 0.5\text{g}$.

**Gross mass refers to the mass of the entire jar assembly, including jar base, jar lid and contents. These value ranges were developed using a ~40g empty jar mass but should be achievable for any jar-lid combination.*

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions including the use of safety glasses and dust masks are advised.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

DOCUMENT HISTORY

Revision No.	Date	Changes applied
3	4 th June, 2025	Updated the recommended gross mass for use in PhotonAssay analysis.
2	29 th June, 2023	Revised the Au by PhotonAssay Certified Value and it's associated uncertainty (following the commissioning of more instruments available for round robin since the initial publication).
1	24 th May, 2020	Restructured PhotonAssay results.
0	14 th May, 2020	First publication.

QMS CERTIFICATION

ORE Pty Ltd is accredited for compliance with ISO 17034.



ORE Pty Ltd is ISO 9001:2015 certified by Lloyd's Register Quality Assurance Ltd for its quality management system including development, manufacturing, certification and supply of CRMs.



CERTIFYING OFFICER

A handwritten signature in blue ink, appearing to read 'Craig Hamlyn'.

4th June, 2025

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

REFERENCES

- [1] Govett, G.J.S. (1983). Handbook of Exploration Geochemistry, Volume 2: Statistics and Data Analysis in Geochemical Prospecting (Variations of accuracy and precision).
- [2] Ingamells, C. O. and Switzer, P. (1973). A Proposed Sampling Constant for Use in Geochemical Analysis, Talanta 20, 547-568.
- [3] ISO Guide 30:2015. Terms and definitions used in connection with reference materials.
- [4] ISO Guide 31:2015. Reference materials – Contents of certificates and labels.
- [5] ISO Guide 35:2017. Certification of reference materials - General and statistical principals.
- [6] ISO Guide 98-3:2008. Guide to the expression of uncertainty in measurement (GUM:1995).
- [7] ISO 16269-6:2014, Statistical interpretation of data – Determination of statistical tolerance intervals.
- [8] ISO/TR 16476:2016, Reference Materials – Establishing and expressing metrological traceability of quantity values assigned to reference materials.
- [9] ISO 17025:2017, General requirements for the competence of testing and calibration laboratories.
- [10] ISO Guide 17034:2016. General requirements for the competence of reference material producers.
- [11] Munsell Rock Color Book (2014). Rock-Color Chart Committee, Geological Society of America (GSA), Minnesota (USA).
- [12] OREAS-BUP-70-09-11: Statistical Analysis - OREAS Evaluation Method.
- [13] OREAS-TN-04-1498: Stability under transport; an experimental study of OREAS CRMs.
- [14] OREAS-TN-05-1674: Long-term storage stability; an experimental study of OREAS CRMs.

- [15] Thompson, A.; Taylor, B.N.; Guide for the Use of the International System of Units (SI); NIST Special Publication 811; U.S. Government Printing Office: Washington, DC (2008); available at: <https://physics.nist.gov/cuu/pdf/sp811.pdf> (accessed Nov 2021).
- [16] Van der Veen AMH and Pauwels, J. (2001). Uncertainty calculations in the certification of reference materials, Accred Qual Assur 6: 290-294.