

CERTIFICATE OF ANALYSIS FOR
GOLD BEARING REFERENCE MATERIAL
OREAS 4Pb

SUMMARY STATISTICS

Recommended value and 95% confidence interval

Constituent	Recommended value	95% Confidence interval	
		Low	High
Gold, Au (ppb)	49	48	50

Recommended value and tolerance interval

Constituent	Recommended value	Tolerance interval $1-\alpha=0.99, \rho=0.95$	
		Low	High
Gold, Au (ppb)	49	48	50

Prepared by:
Ore Research & Exploration Pty Ltd
August, 2004

INTRODUCTION

OREAS certified reference materials (CRMs) are intended to provide a low cost method of evaluating and improving the quality of precious and base metal analysis of geological samples. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration, from the grass roots level through to prospect evaluation, and in grade control at mining operations.

As a rule only source materials exhibiting a high level of homogeneity of the element(s) of interest are used in the preparation of these materials. This has enabled Ore Research & Exploration to produce a range of gold ore CRMs exhibiting homogeneity that matches or exceeds that of currently available international reference materials. In certain instances CRMs produced from a single source are sufficiently homogeneous to produce a relatively coarse-grained form designed to simulate drill chip samples. These have a grain size of minus 3mm and are designated with a "C" suffix to the CRM identification number. These standards are packaged in 1kg units following homogenisation and are intended for submission to analytical laboratories in subsample sizes of as little as 250g. They offer the added advantages of providing a check on both sample preparation and analytical procedures while acting as a blind standard to the assay laboratory. The more conventional pulped standards have a grain size of minus 20 to minus 75 microns and a higher degree of homogeneity. These standards are distinguished by a "P" suffix to the standard identification number. In line with ISO recommendations successive batch numbers are now designated by the lower case suffixes "a", "b", "c", "d", etc.

SOURCE MATERIALS

The gold ore standard OREAS 4Pb was prepared from low grade disseminated ore material containing approximately 200ppb Au combined with barren siltstone material. The gold-bearing material was taken from a mineralised shear zone within Ordovician flysch sediments in the Blackwood area of central Victoria. The sedimentary succession hosting the shear zone consists predominantly of medium-grained greywackes together with subordinate interbedded siltstone and slate. Hydrothermal alteration in the vicinity of the mineralisation is indicated by the development of phyllite. The shear zone, in which gold grades attain a maximum, is manifested by foliated sericitic and chloritic fault gouge and goethitic quartz veins.

Although no ore mineragraphy or scanning electron microscopy has been undertaken to determine the nature of occurrence of the gold, the very homogeneous distribution on a mesoscopic scale and uniform concentration gradient away from the ore zone suggests the gold is extremely fine-grained and evenly disseminated. Limited percussion drilling indicates that sulphides are rare to absent in the shear zone.

The approximate major and trace element composition of this oxidised, quartz-veined metagreywacke comprising gold ore standard OREAS 4Pb is given in Table 1. The constituents SiO₂ to Zr are the means of duplicate XRF analyses determined using a borate fusion method, while the remaining constituents, As to Yb, are means of twenty-four representative samples determined via INAA.

COMMINUTION AND HOMOGENISATION PROCEDURES

OREAS 4Pb was prepared from a blend of a gold-bearing greywacke sample and a barren siltstone sample in the following manner:

- a) *drying each sample to constant mass at 105^o C;*
- b) *crushing and screening each sample;*
- c) *milling gold-bearing greywacke to 100% minus 25 microns;*
- d) *milling barren siltstone to 98% minus 75 microns;*
- e) *thorough homogenisation*
- f) *bagging into 20kg sublots*
- g) *packaging into 60g laminated foil pouches.*

Throughout the bagging stage twenty-four 1kg test units were taken at regular intervals, sealed in laminated plastic bags and set aside for analysis.

ANALYSIS OF OREAS 4Pb

To maintain anonymity, the 17 laboratories have been randomly designated the letter codes A through Q. With the exception of Laboratory Q, each laboratory received four 110g samples with instructions to carry out one 30 to 50g fire assay determination for gold on each sample. Apart from Lab C and I (ICPOES finish) and Lab F (ICPMS finish) the remaining laboratories employed a flame AAS finish (Labs A, F, K, N, O, P using solvent extraction AAS).

For each laboratory two 110g subsamples were scoop-split from each of two separate 1kg test units taken during the bagging stage. This two-stage nested design for the interlaboratory programme was amenable to analysis of variance (ANOVA) treatment and enables a comparative assessment of within- and between-unit homogeneity.

For the determination of a statistical tolerance interval, a 10g scoop split was taken from each of the twenty-four random test units and submitted to Laboratory Q for gold assay via instrumental neutron activation analysis on a reduced analytical subsample weight of 4g.

Individual assay results for the fire assay and INAA methods are presented in Tables 2 and 3, respectively, together with the mean, median and standard deviation (absolute and relative) and bias (expressed as PDM³ – percent deviation of laboratory mean from corrected mean of means) for each data set. Interlaboratory agreement of the means of all but two data sets is good, lying within 9.2% relative of the recommended value of 49 ppb Au. The exception to this is Lab H and N, which have been relegated to outlying status with both having a negative bias of 18.3%.

STATISTICAL EVALUATION OF ANALYTICAL DATA FOR OREAS 4Pb

Recommended Value and Confidence Limits

The recommended value was determined from the mean of means of accepted replicate values of accepted laboratory data sets A to G, I to M and O to Q according to the formulae

$$\bar{x}_i = \frac{1}{n_i} \sum_{j=1}^{n_i} x_{ij}$$

$$\bar{x} = \frac{1}{p} \sum_{i=1}^p \bar{x}_i$$

where

- x_{ij} is the j th result reported by laboratory i ;
- p is the number of participating laboratories;
- n_i is the number of results reported by laboratory i ;
- \bar{x}_i is the mean for laboratory i ;
- \bar{x} is the mean of means.

The confidence limits were obtained by calculation of the variance of the consensus value (mean of means) and reference to Student's- t distribution with degrees of freedom $(p-1)$

$$\hat{V}(\bar{x}) = \frac{1}{p(p-1)} \sum_{i=1}^p (\bar{x}_i - \bar{x})^2$$

$$\text{Confidence limits} = \bar{x} \pm t_{1-x/2}(p-1) \left(\hat{V}(\bar{x}) \right)^{1/2}$$

where $t_{1-x/2}(p-1)$ is the $1-x/2$ fractile of the t -distribution with $(p-1)$ degrees of freedom.

The distribution of the values are assumed to be symmetrical about the mean in the calculation of the confidence limits.

The test for rejection of individual outliers was based on the test criterion, T , and reference to tables of critical values of T at the 1% level of significance (ASTM E 178-94) as follows:

$$T_{ij} = \left| (x_{ij} - \bar{x}_i) \right| / s_i$$

where

- T_{ij} is the test criterion for the j th result of laboratory i ;
- s_i is the standard deviation of laboratory i .

The same principles were applied in testing for outlying laboratory means. Individual and mean outliers are shown in bold type in Table 2 and have been omitted in the determination of recommended values.

Table 1. Indicative major and trace element composition of gold ore reference material OREAS 4Pb; SiO₂ to Total as weight percent; rest in ppm; SiO₂ to LOI by fusion XRF; As to Yb by INAA.

Constituent	Concentration (XRF)	Constituent	Concentration (INAA)
SiO ₂	85.9	As	25
TiO ₂	0.45	Ba	255
Al ₂ O ₃	6.91	Ce	37
Fe ₂ O ₃	3.47	Co	3
MnO	0.01	Cr	56
MgO	0.28	Cs	4
CaO	< 0.01	Eu	0.5
Na ₂ O	0.13	Hf	4
K ₂ O	1.06	La	19
P ₂ O ₅	0.02	Rb	59
SO ₃	0.04	Sb	11
LOI	1.95	Sc	7
Total	100.2	Sm	3
		Th	8
		Yb	1

Table 2. Analytical results for gold in OREAS standard 4Pb (Std.Dev. and Rel.Std.Dev. are one sigma values; PDM³ - percent deviation of lab mean from corrected mean of means; outliers in bold; values in ppb).

Sample No.	Lab A	Lab B	Lab C	Lab D	Lab E	Lab F	Lab G	Lab H	Lab I	Lab J	Lab K
1	48	50	50	53	49	49	50	58	47	52	53
2	49	41	52	52	49	50	54	61	48	50	51
3	47	49	52	54	51	49	50	56	47	52	46
4	46	50	53	55	50	49	48	57	48	50	48
Mean	47.5	47.5	51.8	53.5	49.8	49.4	50.5	58.0	47.5	51.0	49.5
Median	47.5	49.5	52.0	53.5	49.5	49.4	50.0	57.5	47.5	51.0	49.5
Std.Dev.	1.3	4.4	1.3	1.3	1.0	0.4	2.5	2.2	0.6	1.2	3.1
Rel.Std.Dev.	2.72%	9.18%	2.43%	2.41%	1.92%	0.83%	4.98%	3.72%	1.22%	2.26%	6.28%
PDM ³	-3.12%	-3.12%	5.55%	9.12%	1.47%	0.81%	3.00%	18.3%	-3.12%	4.02%	0.96%

Table 2. continued

Sample No.	Lab L	Lab M	Lab N	Lab O	Lab P
1	48	48	67	43	47
2	47	48	52	45	45
3	48	45	65	46	45
4	48	47	48	44	46
Mean	47.8	47.0	58.0	44.5	45.8
Median	48.0	47.5	58.5	44.5	45.5
Std.Dev.	0.5	1.4	9.4	1.3	1.0
Rel.Std.Dev.	1.05%	3.01%	16.2%	2.90%	2.09%
PDM ³	-2.61%	-4.14%	18.3%	-9.24%	-6.69%

Table 3. Analytical results for gold (ppb) in OREAS 4Pb by instrumental neutron activation analysis on 4 g analytical subsample weights (abbreviations as for Table 2).

Sample No.	Lab Q
1	49.2
2	49.0
3	51.8
4	48.2
5	49.7
6	53.1
7	48.0
8	49.7
9	47.5
10	50.1
11	50.6
12	50.5
13	50.7
14	51.9
15	51.1
16	50.4
17	51.4
18	50.8
19	50.5
20	51.3
21	51.6
22	51.5
23	51.5
24	52.5
Mean	50.5
Median	50.7
Std.Dev.	1.4
Rel.Std.Dev.	2.78%
PDM ³	3.05%

Table 4. Recommended value and 95% confidence interval

Constituent	Recommended value	95% Confidence interval	
		Low	High
Gold, Au (ppb)	49	48	50

Statement of Homogeneity

The variability of replicate assays from each laboratory is a result of both measurement and subsampling errors. In the determination of a statistical tolerance interval it is therefore necessary to eliminate, or at least substantially minimise, those errors attributable to measurement. One way of achieving this is by substantially reducing the analytical subsample weight to a point where most of the variability in replicate assays is due to inhomogeneity of the reference material and measurement error becomes negligible. This approach was adopted in the INAA data set (Table 3) where a 4 g subsample weight was

employed. The homogeneity was determined from tables of factors for two-sided tolerance limits for normal distributions (ISO Guide 3207) in which

$$\text{Lower limit is } \bar{x} - k'_2(n, p, 1 - \alpha)s$$

$$\text{Upper limit is } \bar{x} + k'_2(n, p, 1 - \alpha)s$$

where

n is the number of results reported by laboratory Q;

1 - α is the confidence level;

p is the proportion of results expected within the tolerance limits;

k'₂ is the factor for two-sided tolerance limits (*m, σ* unknown);

and *s* is computed according to the formula

$$s = \left[\frac{\sum_{j=1}^n (x_j - \bar{x})^2}{n - 1} \right]^{1/2}$$

No individual outliers were removed from the results prior to the calculation of tolerance intervals.

From the INAA data set an estimated tolerance interval of ±1 ppb at an analytical subsample weight of 50g was obtained (using the sampling constant relationship of Ingamells and Switzer, (1973) and is considered to reflect the actual homogeneity of the material under test. The meaning of this tolerance interval may be illustrated for gold (refer Table 5), where 99% of the time at least 95% of 50g-sized subsamples will have concentrations lying between 48 and 50 ppb. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

Table 5. Recommended value and tolerance interval.

Constituent	Recommended value	Tolerance interval 1-α=0.99, ρ=0.95	
		Low	High
Gold, Au (ppb)	49	48	50

Performance Gates

Performance gates provide an indication of a level of performance that might reasonably be expected from a routine laboratory being monitored by this standard in a QA/QC program. They incorporate errors attributable to bias, precision and inhomogeneity and are simply calculated from the standard deviation of the pooled individual analyses (fire assay

data only) generated from the certification program. All individual and lab dataset (batch) outliers are removed prior to determination of the standard deviation. These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM.

Table 6. Proposed performance gates for 4Pb

Constituent	Recommended value	Performance Gates					
		1 σ		2 σ		3 σ	
		Low	High	Low	High	Low	High
Gold, Au (ppb)	49	47	51	44	54	42	56

Performance gates have been calculated for one, two and three standard deviations of the accepted pool of certification data and are presented in Table 6. As a guide these intervals may be regarded as informational (1 σ), warning or rejection for multiple outliers (2 σ), or rejection for individual outliers (3 σ) in QC monitoring although their precise application should be at the discretion of the QC manager concerned.

PARTICIPATING LABORATORIES

Acme Analytical Laboratories Ltd, Vancouver, Ontario, Canada
 Acme Analytical Laboratories Ltd, Santiago, Chile
 Activation Laboratories, Ancaster, Ontario, Canada
 ALS Chemex Laboratories Pty Ltd, North Vancouver, Ontario, Canada
 ALS Chemex Laboratories Pty Ltd, Perth, WA, Australia
 ALS Chemex Laboratories Pty Ltd, Garbutt, QLD, Australia
 ALS Chemex Laboratories Pty Ltd, Lima, Peru
 Amdel Laboratories Ltd, Thebarton, SA, Australia
 Aminya Laboratories, Wendouree, VIC, Australia
 Becquerel Laboratories, Lucas Heights, NSW, Australia
 Genalysis Laboratory Services Pty Ltd, Maddington, WA, Australia
 Intertek Testing Services, Jakarta Selatan, Indonesia
 Lakefield-Geosol Ltd, Belo Horizonte, Brazil
 McPhar Laboratories, Makati City, Philippines
 OMAC Laboratories, Loughrea, Ireland
 SGS Analabs, Welshpool, WA, Australia
 Ultra Trace, Bentley, WA, Australia

PREPARER AND SUPPLIER OF THE REFERENCE MATERIAL

The gold ore reference material, OREAS 4Pb has been prepared and certified and is supplied by:

Ore Research & Exploration Pty Ltd
 6-8 Gatwick Road
 Bayswater North VIC 3153
 AUSTRALIA

Telephone	(03) 9729 0333	International	+613-9729 0333
Facsimile	(03) 9729 4777	International	+613-9729 4777
Email	info@ore.com.au	Web	www.ore.com.au

It is available in unit sizes of 60g laminated foil packets and 500g jars.

INTENDED USE

OREAS 4Pb is a reference material intended for the following:

- i) for the calibration of instruments used in the determination of the concentration of gold;
- ii) for the verification of analytical methods for gold;
- iii) for the preparation of secondary reference materials of similar composition;
- iv) as an arbitration sample for commercial transactions.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 4Pb has been prepared from gold-bearing metasediments within the oxidised zone of a mineralised shear zone. It is therefore considered to have long-term stability under normal storage conditions.

INSTRUCTIONS FOR THE CORRECT USE OF THE REFERENCE MATERIAL

The recommended value for OREAS 4Pb refers to the concentration level of gold after removal of hygroscopic moisture by drying in air to constant mass at 105⁰ C. If the reference material is not dried by the user prior to analysis, the recommended value should be corrected to the moisture-bearing basis.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

CERTIFYING OFFICER: Dr Paul Hamlyn

ACKNOWLEDGMENTS

The cooperation of all participating laboratories is gratefully acknowledged.

REFERENCES

ASTM E178-94 (1994), Standard practice for dealing with outlying observations.

Ingamells, C. O. and Switzer, P. (1973), *Talanta* 20, 547-568.

ISO Guide 35 (1985), Certification of reference materials - General and statistical principals.

ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.