

CERTIFICATE OF ANALYSIS FOR

LOW GRADE COPPER ORE REFERENCE MATERIAL

OREAS 924

Table 1. Certified Values, SDs, 95% Confidence and Tolerance Limits for OREAS 924

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
4-Acid Digestion					
Ag, Silver (ppm)	2.03	1.91	2.16	1.66	2.40
Al, Aluminium (wt.%)	7.49	7.31	7.67	7.29	7.69
As, Arsenic (ppm)	8.49	8.12	8.85	7.55	9.43
Ba, Barium (ppm)	442	435	450	430	455
Be, Beryllium (ppm)	2.42	2.28	2.56	2.26	2.58
Bi, Bismuth (ppm)	27.3	26.2	28.4	22.4	32.2
Ca, Calcium (wt.%)	0.469	0.459	0.478	0.454	0.483
Cd, Cadmium (ppm)	0.48	0.45	0.52	0.45	0.52
Ce, Cerium (ppm)	85	83	86	81	88
Co, Cobalt (ppm)	23.4	22.8	24.0	22.6	24.2
Cr, Chromium (ppm)	74	71	77	69	79
Cs, Caesium (ppm)	6.73	6.57	6.89	6.54	6.92
Cu, Copper (wt.%)	0.512	0.500	0.523	0.494	0.529
Dy, Dysprosium (ppm)	5.10	4.90	5.29	4.87	5.32
Er, Erbium (ppm)	2.89	2.79	3.00	2.73	3.06
Eu, Europium (ppm)	1.36	1.33	1.39	1.29	1.43
Fe, Iron (wt.%)	6.46	6.26	6.66	6.28	6.63
Ga, Gallium (ppm)	21.2	20.5	21.8	20.4	21.9
Gd, Gadolinium (ppm)	5.78	5.60	5.97	5.46	6.11
Ge, Germanium (ppm)	< 2	IND	IND	IND	IND
Hf, Hafnium (ppm)	3.33	3.22	3.44	3.17	3.49
Ho, Holmium (ppm)	0.98	0.94	1.03	0.93	1.04
In, Indium (ppm)	0.59	0.57	0.61	0.57	0.62
K, Potassium (wt.%)	2.61	2.58	2.65	2.53	2.70
La, Lanthanum (ppm)	42.5	41.6	43.4	41.2	43.9
Li, Lithium (ppm)	31.7	30.7	32.6	30.3	33.0
Lu, Lutetium (ppm)	0.39	0.38	0.41	0.38	0.41
Mg, Magnesium (wt.%)	1.72	1.68	1.76	1.68	1.76
Mn, Manganese (wt.%)	0.095	0.093	0.097	0.093	0.097
Mo, Molybdenum (ppm)	0.94	0.90	0.98	0.80	1.08

Table 1 continued.

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
4-Acid Digestion continued					
Na, Sodium (wt.%)	0.323	0.315	0.331	0.311	0.334
Nb, Niobium (ppm)	14.0	13.5	14.6	13.5	14.6
Nd, Neodymium (ppm)	36.0	35.3	36.7	34.7	37.4
Ni, Nickel (ppm)	36.0	34.8	37.3	34.6	37.5
P, Phosphorus (wt.%)	0.064	0.062	0.065	0.061	0.066
Pb, Lead (ppm)	92	90	94	88	96
Pr, Praseodymium (ppm)	9.62	9.48	9.77	9.33	9.91
Rb, Rubidium (ppm)	172	167	177	167	177
Re, Rhenium (ppb)	< 2	IND	IND	IND	IND
S, Sulphur (wt.%)	0.804	0.790	0.819	0.772	0.837
Sb, Antimony (ppm)	1.33	1.30	1.37	1.22	1.44
Sc, Scandium (ppm)	13.2	12.8	13.6	12.4	14.0
Se, Selenium (ppm)	7.86	7.20	8.51	6.74	8.98
Sm, Samarium (ppm)	6.74	6.50	6.99	6.52	6.96
Sn, Tin (ppm)	13.6	13.3	14.0	13.0	14.3
Sr, Strontium (ppm)	40.4	39.7	41.0	39.3	41.4
Ta, Tantalum (ppm)	1.11	1.03	1.19	1.04	1.18
Tb, Terbium (ppm)	0.86	0.82	0.90	0.82	0.90
Te, Tellurium (ppm)	< 0.05	IND	IND	IND	IND
Th, Thorium (ppm)	16.6	16.0	17.1	16.0	17.2
Ti, Titanium (wt.%)	0.402	0.391	0.412	0.387	0.416
Tl, Thallium (ppm)	0.90	0.88	0.93	0.86	0.94
Tm, Thulium (ppm)	0.40	0.39	0.41	0.37	0.43
U, Uranium (ppm)	3.06	2.96	3.15	2.93	3.19
V, Vanadium (ppm)	92	89	95	89	95
W, Tungsten (ppm)	5.41	5.16	5.66	4.97	5.84
Y, Yttrium (ppm)	26.4	25.6	27.2	25.3	27.6
Yb, Ytterbium (ppm)	2.58	2.49	2.67	2.45	2.70
Zn, Zinc (ppm)	380	374	387	369	391
Zr, Zirconium (ppm)	109	105	113	106	112
Aqua Regia Digestion					
Ag, Silver (ppm)	2.06	1.95	2.16	1.66	2.45
Al, Aluminium (wt.%)	2.76	2.69	2.83	2.68	2.84
As, Arsenic (ppm)	7.80	7.49	8.12	7.34	8.27
Au, Gold (ppb)	< 5	IND	IND	IND	IND
Ba, Barium (ppm)	55	53	58	53	58
Be, Beryllium (ppm)	0.60	0.54	0.65	0.55	0.64
Bi, Bismuth (ppm)	25.7	24.8	26.6	22.9	28.4
Ca, Calcium (wt.%)	0.318	0.306	0.330	0.307	0.330
Cd, Cadmium (ppm)	0.46	0.44	0.48	0.42	0.50
Ce, Cerium (ppm)	60	55	64	58	61
Co, Cobalt (ppm)	22.7	22.1	23.4	21.9	23.6
Cr, Chromium (ppm)	38.3	37.7	39.0	37.3	39.3

Table 1 continued.

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
Aqua Regia Digestion continued					
Cs, Caesium (ppm)	1.60	1.45	1.75	1.52	1.68
Cu, Copper (wt.%)	0.516	0.506	0.525	0.498	0.533
Dy, Dysprosium (ppm)	< 5	IND	IND	IND	IND
Er, Erbium (ppm)	< 3	IND	IND	IND	IND
Eu, Europium (ppm)	< 1.5	IND	IND	IND	IND
Fe, Iron (wt.%)	5.88	5.79	5.98	5.75	6.01
Ga, Gallium (ppm)	7.88	7.64	8.13	7.65	8.12
Gd, Gadolinium (ppm)	4.02	3.23	4.81	3.87	4.18
Ge, Germanium (ppm)	< 0.2	IND	IND	IND	IND
Hf, Hafnium (ppm)	0.62	0.54	0.70	0.58	0.67
Hg, Mercury (ppm)	< 0.05	IND	IND	IND	IND
Ho, Holmium (ppm)	< 0.8	IND	IND	IND	IND
In, Indium (ppm)	0.50	0.49	0.51	0.48	0.53
K, Potassium (wt.%)	0.325	0.299	0.352	0.313	0.337
La, Lanthanum (ppm)	30.2	28.5	32.0	29.4	31.1
Li, Lithium (ppm)	23.4	22.8	24.1	22.7	24.2
Lu, Lutetium (ppm)	< 0.3	IND	IND	IND	IND
Mg, Magnesium (wt.%)	1.45	1.42	1.48	1.41	1.49
Mn, Manganese (wt.%)	0.084	0.083	0.086	0.083	0.086
Mo, Molybdenum (ppm)	0.85	0.79	0.91	0.80	0.91
Na, Sodium (wt.%)	< 0.03	IND	IND	IND	IND
Nb, Niobium (ppm)	< 0.5	IND	IND	IND	IND
Nd, Neodymium (ppm)	25.3	21.2	29.4	24.3	26.3
Ni, Nickel (ppm)	32.6	32.0	33.2	31.5	33.7
P, Phosphorus (wt.%)	0.062	0.059	0.064	0.059	0.064
Pb, Lead (ppm)	92	91	94	88	97
Pr, Praseodymium (ppm)	6.75	5.64	7.87	6.53	6.97
Rb, Rubidium (ppm)	20.3	18.4	22.3	19.7	20.9
Re, Rhenium (ppb)	< 1	IND	IND	IND	IND
S, Sulphur (wt.%)	0.810	0.792	0.828	0.779	0.840
Sb, Antimony (ppm)	0.60	0.54	0.66	0.55	0.65
Sc, Scandium (ppm)	3.15	2.88	3.43	3.00	3.31
Se, Selenium (ppm)	7.32	6.97	7.67	6.63	8.01
Sm, Samarium (ppm)	4.38	3.64	5.12	4.24	4.52
Sn, Tin (ppm)	6.72	6.40	7.04	6.35	7.09
Sr, Strontium (ppm)	13.0	12.6	13.3	12.5	13.4
Ta, Tantalum (ppm)	< 0.05	IND	IND	IND	IND
Tb, Terbium (ppm)	0.51	0.45	0.57	0.48	0.54
Te, Tellurium (ppm)	< 0.05	IND	IND	IND	IND
Th, Thorium (ppm)	14.6	14.1	15.1	14.2	15.1
Ti, Titanium (wt.%)	< 0.2	IND	IND	IND	IND
Tl, Thallium (ppm)	0.13	0.11	0.15	IND	IND
Tm, Thulium (ppm)	< 0.4	IND	IND	IND	IND

Table 1 continued.

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
Aqua Regia Digestion continued					
U, Uranium (ppm)	1.87	1.74	2.00	1.81	1.93
V, Vanadium (ppm)	29.1	27.8	30.4	28.0	30.3
W, Tungsten (ppm)	2.26	2.08	2.44	1.89	2.63
Y, Yttrium (ppm)	13.6	12.1	15.1	13.0	14.1
Yb, Ytterbium (ppm)	< 2	IND	IND	IND	IND
Zn, Zinc (ppm)	370	364	377	361	380
Zr, Zirconium (ppm)	22.2	20.3	24.2	20.8	23.7
Peroxide Fusion ICP					
Al, Aluminium (wt.%)	7.53	7.33	7.73	7.33	7.74
As, Arsenic (ppm)	< 10	IND	IND	IND	IND
Ba, Barium (ppm)	459	451	466	447	470
Be, Beryllium (ppm)	< 3	IND	IND	IND	IND
Bi, Bismuth (ppm)	29.3	26.3	32.3	25.5	33.1
Ca, Calcium (wt.%)	0.498	0.465	0.531	0.452	0.544
Cd, Cadmium (ppm)	< 1	IND	IND	IND	IND
Ce, Cerium (ppm)	85	81	89	82	88
Co, Cobalt (ppm)	24.4	23.6	25.2	22.7	26.2
Cr, Chromium (ppm)	89	82	96	82	96
Cs, Caesium (ppm)	7.00	6.87	7.12	6.74	7.26
Cu, Copper (wt.%)	0.520	0.507	0.533	0.491	0.549
Dy, Dysprosium (ppm)	5.31	5.17	5.45	5.11	5.51
Er, Erbium (ppm)	3.14	2.85	3.42	2.99	3.29
Eu, Europium (ppm)	1.40	1.34	1.46	IND	IND
Fe, Iron (wt.%)	6.66	6.55	6.77	6.48	6.84
Ga, Gallium (ppm)	20.9	19.9	22.0	19.8	22.1
Gd, Gadolinium (ppm)	6.32	5.88	6.77	6.04	6.61
Hf, Hafnium (ppm)	5.29	4.56	6.02	IND	IND
Ho, Holmium (ppm)	1.11	1.03	1.18	IND	IND
In, Indium (ppm)	0.62	0.60	0.64	IND	IND
K, Potassium (wt.%)	2.69	2.64	2.74	2.56	2.81
La, Lanthanum (ppm)	43.7	42.2	45.1	42.0	45.4
Li, Lithium (ppm)	31.2	29.0	33.4	29.5	33.0
Lu, Lutetium (ppm)	0.45	0.38	0.52	IND	IND
Mg, Magnesium (wt.%)	1.76	1.72	1.80	1.72	1.80
Mn, Manganese (wt.%)	0.098	0.094	0.101	0.094	0.101
Mo, Molybdenum (ppm)	< 1	IND	IND	IND	IND
Nb, Niobium (ppm)	14.8	13.7	16.0	14.1	15.6
Nd, Neodymium (ppm)	36.9	36.2	37.6	35.9	37.9
Ni, Nickel (ppm)	38.5	32.6	44.4	32.1	44.9
P, Phosphorus (wt.%)	0.062	0.058	0.067	0.057	0.067
Pb, Lead (ppm)	96	91	101	88	104
Pr, Praseodymium (ppm)	10.1	9.8	10.3	9.8	10.3
Rb, Rubidium (ppm)	173	169	177	169	177

Table 1 continued.

Constituent	Certified Value	95% Confidence Limits		95% Tolerance Limits	
		Low	High	Low	High
Peroxide Fusion ICP continued					
S, Sulphur (wt.%)	0.821	0.793	0.849	0.757	0.885
Sb, Antimony (ppm)	< 1.8	IND	IND	IND	IND
Si, Silicon (wt.%)	29.25	28.67	29.83	28.59	29.91
Sm, Samarium (ppm)	6.84	6.64	7.05	6.49	7.19
Sn, Tin (ppm)	16.7	14.2	19.2	14.4	19.0
Sr, Strontium (ppm)	40.4	39.2	41.7	36.8	44.1
Ta, Tantalum (ppm)	1.30	1.15	1.45	IND	IND
Tb, Terbium (ppm)	0.96	0.89	1.03	IND	IND
Th, Thorium (ppm)	16.9	16.1	17.8	16.2	17.6
Ti, Titanium (wt.%)	0.408	0.397	0.420	0.394	0.422
Tl, Thallium (ppm)	0.96	0.88	1.03	IND	IND
Tm, Thulium (ppm)	0.45	0.42	0.49	IND	IND
U, Uranium (ppm)	3.30	3.17	3.42	3.20	3.39
V, Vanadium (ppm)	94	91	96	90	97
W, Tungsten (ppm)	5.21	4.79	5.63	4.14	6.28
Y, Yttrium (ppm)	28.4	27.3	29.5	27.4	29.4
Yb, Ytterbium (ppm)	2.74	2.59	2.89	2.56	2.92
Zn, Zinc (ppm)	389	383	394	369	409

Note: intervals may appear asymmetric due to rounding

INTRODUCTION

OREAS reference materials are intended to provide a low cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

SOURCE MATERIAL

OREAS 924 is one of a suite of sixteen copper CRMs (OREAS 920 to OREAS 935) prepared from material from the CSA mine located near the town of Cobar in central western New South Wales, Australia. The copper ore body is hosted by the Early Devonian CSA Siltstone, a thinly bedded turbiditic sequence of carbonaceous siltstones and mudstones with minor coarser units. The CSA Siltstone is part of the Cobar Supergroup, consisting of lower syn-rift sediments and upper post-rift sag phase sediments. The mineralisation is structurally controlled and confined to a number of steeply dipping bodies within a major shear zone on the eastern margin of the Early Devonian Cobar Basin. It is characterised by low-grade greenschist alteration and epigenetic low-grade mineralisation enveloping higher-grade shoots of vein complexes or sub-massive to massive sulphides. The sulphides include chalcopyrite, pyrrhotite, pyrite,

sphalerite, galena, bornite and cubanite. Iron-rich chlorite and silica are prominent alterations in the siltstone host.

COMMINUATION AND HOMOGENISATION PROCEDURES

The material constituting OREAS 924 was prepared in the following manner:

- drying to constant mass at 105°C;
- preliminary blending of copper ores and barren siltstone materials;
- multi-stage milling to approximately 99% less than 75 microns;
- final homogenisation;
- packaging in 10g units in laminated foil pouches.

ANALYTICAL PROGRAM

Twenty two commercial analytical laboratories participated in the program to characterise the analytes reported in Table 1. The following methods were employed for method specific certification:

- Four acid (HCl-HNO₃-HF-HClO₄) digestion with ICP-OES, ICP-MS or AAS finish (19 laboratories);
- Aqua regia digestion with ICP-OES, ICP-MS or AAS finish (19 laboratories);
- Peroxide fusion with ICP-OES, ICP-MS or AAS finish (12 laboratories).

For the round robin program ten 300g test units were taken at predetermined intervals during the bagging stage, immediately following final homogenisation, and are considered representative of the entire batch. The six samples received by each laboratory were obtained by taking two 20g scoop splits from each of three separate 300g test units. This format enabled nested ANOVA treatment of the results to evaluate homogeneity, i.e. to ascertain whether between-unit variance is greater than within-unit variance. Table 1 presents the certified values together with their associated 1SD's, 95% confidence and tolerance limits and Table 2 shows indicative values. Table 3 provides performance gate intervals for the certified values of each analytical method group based on their pooled 1SD's. Tabulated results of all elements together with uncorrected means, medians, standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**OREAS 924-DataPack.1.1.250703_130125.xlsx**).

STATISTICAL ANALYSIS

Certified Values, Standard Deviations, Confidence and Tolerance Limits have been determined for each analytical method following removal of individual and laboratory outliers (Table 1). Certified Values are the mean of means after outlier filtering. The 95% Confidence Limit is a measure of the reliability of the certified value, i.e. the narrower the Confidence Interval the greater the certainty in the Certified Value. It should not be used as a control limit for laboratory performance. Indicative values (Table 2) are provided where i) the number of laboratories reporting a particular analyte is insufficient (< 5) to

support certification; ii) interlaboratory consensus is poor; or iii) a significant proportion of results are outlying or results are multimodal.

Table 2. Indicative Values for OREAS 924

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
4-Acid Digestion								
B	ppm	7.58	Hg	ppm	< 1	Ru	ppm	< 0.1
Aqua Regia Digestion								
B	ppm	< 10	Pt	ppb	< 5			
Pd	ppb	12.2	Ru	ppb	< 5			
Infrared Combustion								
S	wt. %	0.866						
Peroxide Fusion ICP								
Ag	ppm	4.35	Re	ppm	< 0.1	Te	ppm	< 6
B	ppm	24.6	Sc	ppm	12.0	Zr	ppm	167
Ge	ppm	2.40	Se	ppm	5.55			

Standard Deviation values (1SDs) are reported in Table 1 and provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability. The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e. after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.

Performance Gates (Table 3) are calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned.

A second method utilises a 5% window calculated directly from the certified value. Standard deviation is also shown in relative per cent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow.

Tolerance Limits (ISO Guide 3207) were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for copper by 4-acid digestion, where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($p=0.95$) will have concentrations lying between 0.494 and 0.529 wt.%. Put more precisely, this means that if the same number of

subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

The homogeneity of OREAS 924 has also been evaluated in an ANOVA study for all certified analytes. This study tests the null hypothesis that no statistically significant difference exists between the *between-unit variance* and the *within-unit variance* (i.e. p-values <0.05 indicate rejection of the null hypothesis). Of the 175 certified values, no failures were observed indicating no evidence to reject the null hypothesis.

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS 924 is fit-for-purpose as a certified reference material (see 'Intended Use' below).

PARTICIPATING LABORATORIES

1. Accurassay, Thunder Bay, Ontario, Canada
2. Acme (BV), Santiago, Chile
3. Actlabs, Ancaster, Ontario, Canada
4. Actlabs, Kamloops, BC, Canada
5. Actlabs, Thunder Bay, Ontario, Canada
6. ALS, Brisbane, QLD, Australia
7. ALS, Vancouver, BC, Canada
8. Intertek Genalysis, Adelaide, SA, Australia
9. Intertek Genalysis, Johannesburg, South Africa
10. Intertek Genalysis, Perth, WA, Australia
11. Intertek Testing Services, Cupang, Muntinlupa, Philippines
12. Intertek Testing Services, Jakarta, Indonesia
13. Intertek Testing Services, Shunyi, Beijing, China
14. Labtium Oy, Saarenkylä, Rovaniemi, Finland
15. OMAC, Loughrea, Galway, Ireland
16. PT Geoservices Ltd, Cikarang, Jakarta Raya, Indonesia
17. SGS Canada Inc., Vancouver, BC, Canada
18. SGS Lakefield Research Ltd, Lakefield, Ontario, Canada
19. SGS South Africa Pty Ltd, Booysens, Gauteng, South Africa
20. Shiva Analyticals Ltd, Bangalore North, Karnataka, India
21. Ultra Trace Pty Ltd (BV), Perth, WA, Australia

Table 3. Performance Gates for OREAS 924

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion											
Ag, ppm	2.03	0.36	1.32	2.75	0.96	3.10	17.55%	35.11%	52.66%	1.93	2.13
Al, wt. %	7.49	0.357	6.77	8.20	6.42	8.56	4.77%	9.54%	14.31%	7.11	7.86
As, ppm	8.49	1.10	6.29	10.68	5.19	11.78	12.94%	25.88%	38.82%	8.06	8.91
Ba, ppm	442	16	410	474	394	490	3.62%	7.24%	10.86%	420	465
Be, ppm	2.42	0.29	1.85	2.99	1.56	3.28	11.82%	23.65%	35.47%	2.30	2.54
Bi, ppm	27.3	3.2	21.0	33.6	17.8	36.8	11.61%	23.22%	34.83%	25.9	28.7
Ca, wt. %	0.469	0.019	0.430	0.508	0.410	0.527	4.14%	8.29%	12.43%	0.445	0.492
Cd, ppm	0.48	0.06	0.36	0.60	0.30	0.67	12.45%	24.90%	37.35%	0.46	0.51
Ce, ppm	85	3.2	78	91	75	94	3.76%	7.52%	11.28%	80	89
Co, ppm	23.4	1.37	20.7	26.2	19.3	27.5	5.86%	11.73%	17.59%	22.2	24.6
Cr, ppm	74	6.7	61	88	54	94	9.10%	18.20%	27.30%	70	78
Cs, ppm	6.73	0.310	6.11	7.35	5.80	7.66	4.61%	9.21%	13.82%	6.39	7.07
Cu, wt. %	0.512	0.028	0.456	0.568	0.428	0.596	5.46%	10.92%	16.38%	0.486	0.537
Dy, ppm	5.10	0.297	4.50	5.69	4.21	5.99	5.83%	11.66%	17.49%	4.84	5.35
Er, ppm	2.89	0.146	2.60	3.19	2.45	3.33	5.05%	10.11%	15.16%	2.75	3.04
Eu, ppm	1.36	0.055	1.25	1.47	1.19	1.53	4.08%	8.15%	12.23%	1.29	1.43
Fe, wt. %	6.46	0.400	5.66	7.26	5.26	7.65	6.19%	12.38%	18.57%	6.13	6.78
Ga, ppm	21.2	1.37	18.4	23.9	17.0	25.3	6.48%	12.96%	19.43%	20.1	22.2
Gd, ppm	5.78	0.287	5.21	6.36	4.92	6.64	4.96%	9.91%	14.87%	5.49	6.07
Ge, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	3.33	0.214	2.90	3.76	2.69	3.97	6.41%	12.83%	19.24%	3.16	3.50
Ho, ppm	0.98	0.067	0.85	1.12	0.78	1.19	6.85%	13.70%	20.56%	0.93	1.03
In, ppm	0.59	0.043	0.51	0.68	0.46	0.72	7.30%	14.61%	21.91%	0.56	0.62
K, wt. %	2.61	0.103	2.41	2.82	2.30	2.92	3.95%	7.89%	11.84%	2.48	2.74
La, ppm	42.5	1.91	38.7	46.4	36.8	48.3	4.50%	8.99%	13.49%	40.4	44.7
Li, ppm	31.7	1.76	28.1	35.2	26.4	37.0	5.57%	11.13%	16.70%	30.1	33.2
Lu, ppm	0.39	0.023	0.35	0.44	0.33	0.46	5.84%	11.67%	17.51%	0.37	0.41
Mg, wt. %	1.72	0.079	1.56	1.88	1.48	1.96	4.61%	9.23%	13.84%	1.64	1.81
Mn, wt. %	0.095	0.004	0.087	0.102	0.084	0.106	3.93%	7.86%	11.80%	0.090	0.100
Mo, ppm	0.94	0.090	0.76	1.12	0.67	1.21	9.56%	19.12%	28.69%	0.89	0.99
Na, wt. %	0.323	0.017	0.289	0.357	0.272	0.374	5.30%	10.59%	15.89%	0.307	0.339
Nb, ppm	14.0	0.95	12.1	16.0	11.2	16.9	6.78%	13.57%	20.35%	13.3	14.8

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
Nd, ppm	36.0	0.98	34.1	38.0	33.1	39.0	2.73%	5.47%	8.20%	34.2	37.8
Ni, ppm	36.0	2.59	30.9	41.2	28.3	43.8	7.19%	14.38%	21.56%	34.2	37.8
P, wt. %	0.064	0.004	0.056	0.071	0.053	0.074	5.62%	11.25%	16.87%	0.060	0.067
Pb, ppm	92	5.0	82	102	77	107	5.40%	10.81%	16.21%	87	97
Pr, ppm	9.62	0.220	9.18	10.06	8.96	10.28	2.29%	4.58%	6.87%	9.14	10.10
Rb, ppm	172	9	154	191	144	200	5.41%	10.83%	16.24%	164	181
Re, ppb	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt. %	0.804	0.033	0.738	0.871	0.705	0.904	4.13%	8.25%	12.38%	0.764	0.845
Sb, ppm	1.33	0.093	1.15	1.52	1.05	1.61	6.95%	13.89%	20.84%	1.27	1.40
Sc, ppm	13.2	0.87	11.5	14.9	10.6	15.8	6.57%	13.15%	19.72%	12.5	13.9
Se, ppm	7.86	1.29	5.28	10.43	3.99	11.72	16.40%	32.81%	49.21%	7.46	8.25
Sm, ppm	6.74	0.340	6.06	7.42	5.72	7.76	5.04%	10.07%	15.11%	6.40	7.08
Sn, ppm	13.6	0.87	11.9	15.4	11.0	16.2	6.36%	12.73%	19.09%	13.0	14.3
Sr, ppm	40.4	1.21	37.9	42.8	36.7	44.0	3.00%	6.00%	9.00%	38.3	42.4
Ta, ppm	1.11	0.15	0.82	1.40	0.67	1.55	13.19%	26.38%	39.56%	1.06	1.17
Tb, ppm	0.86	0.063	0.73	0.99	0.67	1.05	7.30%	14.61%	21.91%	0.82	0.90
Te, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	16.6	1.14	14.3	18.9	13.2	20.0	6.87%	13.74%	20.61%	15.8	17.4
Ti, wt. %	0.402	0.020	0.361	0.442	0.341	0.462	5.05%	10.10%	15.15%	0.381	0.422
Tl, ppm	0.90	0.053	0.79	1.01	0.74	1.06	5.91%	11.82%	17.72%	0.86	0.95
Tm, ppm	0.40	0.021	0.36	0.44	0.34	0.46	5.31%	10.62%	15.93%	0.38	0.42
U, ppm	3.06	0.181	2.70	3.42	2.51	3.60	5.93%	11.85%	17.78%	2.90	3.21
V, ppm	92	6.1	80	105	74	111	6.57%	13.14%	19.71%	88	97
W, ppm	5.41	0.55	4.32	6.50	3.77	7.04	10.08%	20.17%	30.25%	5.14	5.68
Y, ppm	26.4	1.52	23.4	29.5	21.9	31.0	5.75%	11.51%	17.26%	25.1	27.7
Yb, ppm	2.58	0.130	2.32	2.84	2.19	2.97	5.04%	10.08%	15.13%	2.45	2.71
Zn, ppm	380	15	351	410	336	424	3.89%	7.77%	11.66%	361	399
Zr, ppm	109	7	95	123	88	129	6.27%	12.55%	18.82%	104	114
Aqua Regia Digestion											
Ag, ppm	2.06	0.41	1.24	2.87	0.83	3.28	19.82%	39.63%	59.45%	1.95	2.16
Al, wt. %	2.76	0.142	2.48	3.04	2.34	3.19	5.14%	10.28%	15.42%	2.62	2.90
As, ppm	7.80	0.79	6.23	9.38	5.44	10.17	10.09%	20.18%	30.27%	7.41	8.19

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Au, ppb	< 5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ba, ppm	55	3.7	48	63	44	66	6.63%	13.26%	19.89%	53	58
Be, ppm	0.60	0.09	0.41	0.79	0.32	0.88	15.72%	31.45%	47.17%	0.57	0.63
Bi, ppm	25.7	2.7	20.2	31.2	17.5	33.9	10.68%	21.36%	32.03%	24.4	27.0
Ca, wt. %	0.318	0.020	0.278	0.358	0.258	0.378	6.31%	12.61%	18.92%	0.302	0.334
Cd, ppm	0.46	0.040	0.38	0.54	0.34	0.58	8.61%	17.22%	25.82%	0.44	0.48
Ce, ppm	60	8	43	76	35	84	13.60%	27.21%	40.81%	57	63
Co, ppm	22.7	1.39	20.0	25.5	18.6	26.9	6.12%	12.24%	18.35%	21.6	23.9
Cr, ppm	38.3	1.55	35.2	41.5	33.7	43.0	4.05%	8.10%	12.15%	36.4	40.3
Cs, ppm	1.60	0.25	1.10	2.10	0.85	2.36	15.70%	31.40%	47.11%	1.52	1.68
Cu, wt. %	0.516	0.023	0.469	0.562	0.446	0.586	4.52%	9.04%	13.56%	0.490	0.542
Dy, ppm	< 5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Er, ppm	< 3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Eu, ppm	< 1.5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Fe, wt. %	5.88	0.210	5.46	6.30	5.25	6.51	3.57%	7.14%	10.71%	5.59	6.18
Ga, ppm	7.88	0.414	7.06	8.71	6.64	9.13	5.25%	10.49%	15.74%	7.49	8.28
Gd, ppm	4.02	0.81	2.41	5.64	1.60	6.45	20.09%	40.19%	60.28%	3.82	4.22
Ge, ppm	< 0.2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	0.62	0.10	0.42	0.83	0.32	0.93	16.27%	32.54%	48.82%	0.59	0.66
Hg, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ho, ppm	< 0.8	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
In, ppm	0.50	0.022	0.46	0.55	0.44	0.57	4.44%	8.89%	13.33%	0.48	0.53
K, wt. %	0.325	0.050	0.225	0.426	0.175	0.476	15.44%	30.87%	46.31%	0.309	0.342
La, ppm	30.2	3.2	23.9	36.6	20.7	39.8	10.51%	21.01%	31.52%	28.7	31.8
Li, ppm	23.4	1.29	20.8	26.0	19.5	27.3	5.53%	11.06%	16.58%	22.2	24.6
Lu, ppm	< 0.3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Mg, wt. %	1.45	0.065	1.32	1.58	1.26	1.65	4.46%	8.93%	13.39%	1.38	1.52
Mn, wt. %	0.084	0.004	0.077	0.092	0.073	0.096	4.42%	8.84%	13.26%	0.080	0.089
Mo, ppm	0.85	0.10	0.65	1.06	0.54	1.17	12.20%	24.41%	36.61%	0.81	0.90
Na, wt. %	< 0.03	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nb, ppm	< 0.5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nd, ppm	25.3	4.7	16.0	34.7	11.3	39.3	18.47%	36.94%	55.41%	24.0	26.6

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Ni, ppm	32.6	1.29	30.0	35.2	28.8	36.5	3.95%	7.91%	11.86%	31.0	34.3
P, wt. %	0.062	0.004	0.054	0.070	0.050	0.074	6.51%	13.02%	19.53%	0.059	0.065
Pb, ppm	92	4.2	84	101	80	105	4.50%	9.00%	13.51%	88	97
Pr, ppm	6.75	1.13	4.49	9.01	3.37	10.14	16.72%	33.44%	50.15%	6.41	7.09
Rb, ppm	20.3	3.0	14.4	26.2	11.4	29.2	14.55%	29.11%	43.66%	19.3	21.3
Re, ppb	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt. %	0.810	0.040	0.731	0.889	0.691	0.928	4.88%	9.76%	14.65%	0.769	0.850
Sb, ppm	0.60	0.09	0.41	0.79	0.32	0.88	15.57%	31.15%	46.72%	0.57	0.63
Sc, ppm	3.15	0.42	2.32	3.98	1.90	4.40	13.20%	26.40%	39.60%	2.99	3.31
Se, ppm	7.32	0.81	5.69	8.94	4.88	9.76	11.10%	22.21%	33.31%	6.95	7.69
Sm, ppm	4.38	0.76	2.87	5.89	2.11	6.64	17.25%	34.49%	51.74%	4.16	4.60
Sn, ppm	6.72	0.580	5.56	7.88	4.98	8.46	8.63%	17.26%	25.89%	6.38	7.06
Sr, ppm	13.0	0.72	11.5	14.4	10.8	15.1	5.53%	11.06%	16.58%	12.3	13.6
Ta, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tb, ppm	0.51	0.08	0.35	0.67	0.27	0.74	15.40%	30.81%	46.21%	0.48	0.53
Te, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	14.6	0.85	12.9	16.3	12.1	17.2	5.78%	11.56%	17.35%	13.9	15.3
Ti, wt. %	< 0.2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tl, ppm	0.13	0.02	0.08	0.18	0.06	0.20	18.64%	37.28%	55.92%	0.12	0.14
Tm, ppm	< 0.4	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
U, ppm	1.87	0.22	1.43	2.31	1.21	2.53	11.83%	23.66%	35.50%	1.78	1.96
V, ppm	29.1	2.35	24.4	33.8	22.1	36.2	8.07%	16.14%	24.22%	27.7	30.6
W, ppm	2.26	0.38	1.51	3.01	1.13	3.39	16.68%	33.37%	50.05%	2.15	2.37
Y, ppm	13.6	2.5	8.5	18.7	5.9	21.2	18.76%	37.52%	56.29%	12.9	14.2
Yb, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Zn, ppm	370	16	339	402	323	418	4.26%	8.51%	12.77%	352	389
Zr, ppm	22.2	3.1	16.1	28.3	13.0	31.4	13.78%	27.56%	41.35%	21.1	23.3
Peroxide Fusion ICP											
Al, wt. %	7.53	0.343	6.85	8.22	6.51	8.56	4.55%	9.10%	13.65%	7.16	7.91
As, ppm	< 10	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ba, ppm	459	14	430	487	416	502	3.11%	6.21%	9.32%	436	482
Be, ppm	< 3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion ICP continued											
Bi, ppm	29.3	4.7	19.9	38.7	15.2	43.4	16.04%	32.09%	48.13%	27.8	30.8
Ca, wt. %	0.498	0.055	0.389	0.607	0.334	0.662	10.96%	21.93%	32.89%	0.473	0.523
Cd, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ce, ppm	85	4.9	75	95	70	100	5.80%	11.60%	17.39%	81	89
Co, ppm	24.4	1.99	20.4	28.4	18.5	30.4	8.15%	16.30%	24.45%	23.2	25.6
Cr, ppm	89	12	66	112	54	124	13.04%	26.08%	39.12%	85	94
Cs, ppm	7.00	0.195	6.61	7.39	6.41	7.58	2.79%	5.57%	8.36%	6.65	7.35
Cu, wt. %	0.520	0.030	0.459	0.581	0.429	0.611	5.84%	11.69%	17.53%	0.494	0.546
Dy, ppm	5.31	0.207	4.90	5.72	4.69	5.93	3.90%	7.79%	11.69%	5.04	5.58
Er, ppm	3.14	0.33	2.48	3.79	2.16	4.12	10.43%	20.86%	31.30%	2.98	3.30
Eu, ppm	1.40	0.085	1.23	1.57	1.14	1.66	6.09%	12.18%	18.27%	1.33	1.47
Fe, wt. %	6.66	0.222	6.22	7.11	6.00	7.33	3.33%	6.66%	9.99%	6.33	7.00
Ga, ppm	20.9	1.59	17.7	24.1	16.1	25.7	7.60%	15.21%	22.81%	19.9	22.0
Gd, ppm	6.32	0.522	5.28	7.37	4.76	7.89	8.26%	16.51%	24.77%	6.01	6.64
Hf, ppm	5.29	0.61	4.07	6.52	3.46	7.13	11.57%	23.13%	34.70%	5.03	5.56
Ho, ppm	1.11	0.097	0.91	1.30	0.82	1.40	8.74%	17.48%	26.22%	1.05	1.16
In, ppm	0.62	0.049	0.52	0.72	0.47	0.76	7.90%	15.79%	23.69%	0.59	0.65
K, wt. %	2.69	0.108	2.47	2.90	2.36	3.01	4.03%	8.06%	12.09%	2.55	2.82
La, ppm	43.7	2.49	38.7	48.7	36.2	51.1	5.69%	11.38%	17.07%	41.5	45.9
Li, ppm	31.2	2.50	26.2	36.2	23.7	38.7	8.00%	16.00%	24.00%	29.7	32.8
Lu, ppm	0.45	0.05	0.34	0.56	0.29	0.61	12.02%	24.04%	36.06%	0.43	0.47
Mg, wt. %	1.76	0.067	1.62	1.89	1.56	1.96	3.79%	7.58%	11.37%	1.67	1.84
Mn, wt. %	0.098	0.005	0.087	0.108	0.082	0.113	5.39%	10.79%	16.18%	0.093	0.102
Mo, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nb, ppm	14.8	1.20	12.4	17.3	11.2	18.5	8.12%	16.23%	24.35%	14.1	15.6
Nd, ppm	36.9	0.77	35.3	38.4	34.6	39.2	2.09%	4.17%	6.26%	35.0	38.7
Ni, ppm	38.5	5.7	27.1	49.9	21.4	55.6	14.80%	29.60%	44.39%	36.6	40.4
P, wt. %	0.062	0.005	0.052	0.073	0.046	0.079	8.67%	17.34%	26.01%	0.059	0.066
Pb, ppm	96	7.0	82	110	75	117	7.27%	14.54%	21.81%	91	101
Pr, ppm	10.1	0.32	9.4	10.7	9.1	11.0	3.16%	6.32%	9.48%	9.5	10.6
Rb, ppm	173	4	165	181	161	185	2.29%	4.57%	6.86%	164	182
S, wt. %	0.821	0.045	0.731	0.912	0.686	0.957	5.49%	10.99%	16.48%	0.780	0.862

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion ICP continued											
Sb, ppm	< 1.8	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Si, wt. %	29.25	0.596	28.06	30.44	27.46	31.04	2.04%	4.07%	6.11%	27.79	30.71
Sm, ppm	6.84	0.299	6.25	7.44	5.95	7.74	4.37%	8.73%	13.10%	6.50	7.19
Sn, ppm	16.7	2.8	11.1	22.3	8.3	25.1	16.71%	33.42%	50.13%	15.9	17.5
Sr, ppm	40.4	2.23	36.0	44.9	33.8	47.1	5.51%	11.01%	16.52%	38.4	42.5
Ta, ppm	1.30	0.17	0.95	1.64	0.78	1.81	13.18%	26.36%	39.55%	1.23	1.36
Tb, ppm	0.96	0.082	0.79	1.12	0.71	1.21	8.60%	17.19%	25.79%	0.91	1.01
Th, ppm	16.9	1.16	14.6	19.2	13.5	20.4	6.83%	13.66%	20.49%	16.1	17.8
Ti, wt. %	0.408	0.022	0.363	0.453	0.341	0.476	5.51%	11.01%	16.52%	0.388	0.429
Tl, ppm	0.96	0.094	0.77	1.15	0.67	1.24	9.85%	19.69%	29.54%	0.91	1.00
Tm, ppm	0.45	0.05	0.36	0.55	0.31	0.60	10.68%	21.36%	32.05%	0.43	0.48
U, ppm	3.30	0.174	2.95	3.64	2.78	3.82	5.26%	10.53%	15.79%	3.13	3.46
V, ppm	94	4.2	85	102	81	106	4.46%	8.92%	13.39%	89	99
W, ppm	5.21	0.99	3.22	7.20	2.23	8.19	19.07%	38.15%	57.22%	4.95	5.47
Y, ppm	28.4	1.48	25.4	31.3	23.9	32.8	5.21%	10.41%	15.62%	27.0	29.8
Yb, ppm	2.74	0.173	2.39	3.09	2.22	3.26	6.30%	12.61%	18.91%	2.60	2.88
Zn, ppm	389	14	361	417	347	431	3.61%	7.21%	10.82%	369	408

Note: intervals may appear asymmetric due to rounding

PREPARER AND SUPPLIER OF THE REFERENCE MATERIAL

Reference material OREAS 924 has been prepared and certified by:

ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Fax: +613-9729 8338
Web: www.ore.com.au
Email: info@ore.com.au

It has been packaged in 10g units in laminated foil pouches.

INTENDED USE

OREAS 924 is intended for the following uses:

- for the monitoring of laboratory performance in the analysis of geological samples for the analytes reported in Table 1;
- for the verification of analytical methods for analytes reported in Table 1;

- for the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 924 has been prepared from mineralised and altered carbonaceous siltstones and mudstones from the CSA mine located near the town of Cobar in central western New South Wales, Australia. It has been packaged in robust foil laminate pouches and under normal storage conditions has long-term stability beyond 10 years.

INSTRUCTIONS FOR THE CORRECT USE OF THE REFERENCE MATERIAL

The certified values for OREAS 924 refer to the concentration level in its packaged state. It should not be dried prior to weighing and analysis.

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions such as the use of safety glasses and dust masks are advised.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

DOCUMENT HISTORY

Revision No.	Date	Changes applied
1	4 th July, 2025	Revision of selected certified values for silver and some trace elements.
0	8 th April, 2014	First publication.

CERTIFYING OFFICER

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager – (ORE P/L)

REFERENCES

ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.

ISO Guide 35 (2006), Certification of reference materials - General and statistical principals.