

CERTIFICATE OF ANALYSIS FOR


CERTIFIED REFERENCE MATERIAL

OREAS 455

Ferruginous Nickel-Cobalt Laterite Ore
Bulong and Murrin Murrin, Western Australia



Accredited for compliance with ISO 17034



COA-2079-OREAS 455-R0

27-Aug-2026

Template ID: BUP-70-10-04 Ver:0.4

Table 1. Certified Values, Uncertainty & Tolerance Intervals in OREAS 455.

Constituent	Certified Value	95% Expanded Uncertainty		95% Tolerance Limits	
		Low	High	Low	High
Borate Fusion XRF					
Al ₂ O ₃ , Aluminium(III) oxide (wt.%)	8.24	8.16	8.32	8.18	8.29
CaO, Calcium oxide (wt.%)	0.232	0.223	0.241	0.226	0.238
Co, Cobalt (ppm)	851	836	866	838	863
Cr ₂ O ₃ , Chromium(III) oxide (wt.%)	1.08	1.07	1.09	1.07	1.09
Cu, Copper (ppm)	66	51	82	IND	IND
Fe ₂ O ₃ , Iron(III) oxide (wt.%)	36.05	35.71	36.39	35.92	36.18
K ₂ O, Potassium oxide (wt.%)	0.134	0.124	0.144	0.131	0.137
MgO, Magnesium oxide (wt.%)	3.97	3.93	4.01	3.95	4.00
MnO, Manganese oxide (wt.%)	0.283	0.278	0.288	0.279	0.287
Na ₂ O, Sodium oxide (wt.%)	0.676	0.645	0.706	0.661	0.690
Ni, Nickel (wt.%)	1.65	1.64	1.67	1.64	1.67
P ₂ O ₅ , Phosphorus(V) oxide (wt.%)	0.010	0.009	0.011	IND	IND
Pb, Lead (ppm)	< 50	IND	IND	IND	IND
SiO ₂ , Silicon dioxide (wt.%)	36.83	36.51	37.15	36.69	36.96
SO ₃ , Sulphur trioxide (wt.%)	0.220	0.202	0.238	0.210	0.230
TiO ₂ , Titanium dioxide (wt.%)	0.303	0.289	0.318	0.294	0.313
V ₂ O ₅ , Vanadium(V) oxide (ppm)	190	150	230	172	208
Zn, Zinc (ppm)	167	157	177	159	174
Thermogravimetry					
LOI ¹⁰⁰⁰ , Loss on ignition @1000 °C (wt.%)	9.70	9.45	9.95	9.61	9.79
Borate / Peroxide Fusion ICP					
Al, Aluminium (wt.%)	4.16	4.03	4.30	4.07	4.26
As, Arsenic (ppm)	< 100	IND	IND	IND	IND
B, Boron (ppm)	56	48	64	49	63
Ba, Barium (ppm)	105	99	112	101	109
Be, Beryllium (ppm)	< 1	IND	IND	IND	IND
Ca, Calcium (wt.%)	0.155	0.129	0.180	0.146	0.163
Cd, Cadmium (ppm)	< 10	IND	IND	IND	IND
Ce, Cerium (ppm)	24.5	23.1	25.9	23.4	25.6
Co, Cobalt (ppm)	824	791	857	805	843
Cr, Chromium (wt.%)	0.708	0.679	0.737	0.695	0.721
Cs, Caesium (ppm)	0.43	0.32	0.55	0.40	0.47
Cu, Copper (ppm)	58	52	65	55	62
Dy, Dysprosium (ppm)	1.02	0.92	1.11	0.96	1.07
Er, Erbium (ppm)	0.60	0.48	0.73	0.56	0.65
Eu, Europium (ppm)	0.31	0.27	0.36	0.29	0.34
Fe, Iron (wt.%)	24.10	23.38	24.81	23.72	24.47
Ga, Gallium (ppm)	7.42	6.38	8.47	7.11	7.74

SI unit equivalents: ppm (parts per million; 1×10^{-6}) $\equiv$ mg/kg; wt.% (weight per cent) $\equiv$ % (mass fraction).

Note: intervals may appear asymmetric due to rounding.

IND = indeterminate (due to limited reading resolution of the methods employed. For practical purposes the 95% Expanded Uncertainty can be set between zero and a two times multiple of the upper bound/non-detect limit value).

Table 1 continued.

Constituent	Certified Value	95% Expanded Uncertainty		95% Tolerance Limits	
		Low	High	Low	High
Borate / Peroxide Fusion ICP continued					
Gd, Gadolinium (ppm)	0.97	0.85	1.09	0.91	1.03
Ho, Holmium (ppm)	0.20	0.17	0.22	0.18	0.21
In, Indium (ppm)	< 0.1	IND	IND	IND	IND
K, Potassium (wt.%)	0.107	0.089	0.126	0.095	0.120
La, Lanthanum (ppm)	3.08	2.84	3.31	2.93	3.22
Li, Lithium (ppm)	7.69	6.00	9.39	7.40	7.99
Lu, Lutetium (ppm)	0.10	0.08	0.12	IND	IND
Mg, Magnesium (wt.%)	2.28	2.22	2.35	2.24	2.33
Mn, Manganese (wt.%)	0.210	0.203	0.218	0.207	0.214
Mo, Molybdenum (ppm)	20.0	18.0	22.0	19.4	20.6
Nd, Neodymium (ppm)	3.93	3.48	4.38	3.75	4.10
Ni, Nickel (wt.%)	1.58	1.54	1.62	1.55	1.60
Pb, Lead (ppm)	< 100	IND	IND	IND	IND
Pr, Praseodymium (ppm)	0.97	0.89	1.04	0.92	1.01
Rb, Rubidium (ppm)	3.84	3.17	4.51	3.59	4.09
Re, Rhenium (ppm)	< 0.1	IND	IND	IND	IND
S, Sulphur (wt.%)	0.090	0.078	0.101	IND	IND
Sb, Antimony (ppm)	0.90	0.68	1.12	IND	IND
Sc, Scandium (ppm)	27.2	25.1	29.2	26.4	28.0
Se, Selenium (ppm)	< 20	IND	IND	IND	IND
Si, Silicon (wt.%)	16.80	16.34	17.27	16.50	17.10
Sm, Samarium (ppm)	0.98	0.85	1.12	0.93	1.04
Sr, Strontium (ppm)	14.4	11.9	17.0	13.8	15.1
Tb, Terbium (ppm)	0.17	0.15	0.18	IND	IND
Te, Tellurium (ppm)	< 1	IND	IND	IND	IND
Th, Thorium (ppm)	0.81	0.74	0.87	0.77	0.85
Ti, Titanium (wt.%)	0.173	0.165	0.180	0.167	0.178
Tm, Thulium (ppm)	0.088	0.070	0.107	IND	IND
U, Uranium (ppm)	0.53	0.48	0.58	0.49	0.56
V, Vanadium (ppm)	104	99	108	101	106
W, Tungsten (ppm)	4.57	3.57	5.57	4.28	4.86
Y, Yttrium (ppm)	3.77	3.54	4.00	3.56	3.97
Yb, Ytterbium (ppm)	0.71	0.64	0.78	0.68	0.74
Zn, Zinc (ppm)	161	151	170	157	164
Zr, Zirconium (ppm)	32.8	25.7	39.9	31.4	34.2
Infrared Combustion					
C, Carbon (wt.%)	0.167	0.150	0.184	0.157	0.176
S, Sulphur (wt.%)	0.085	0.073	0.096	0.081	0.089

SI unit equivalents: ppm (parts per million; 1×10^{-6}) $\equiv$ mg/kg; wt.% (weight per cent) $\equiv$ % (mass fraction).

Note: intervals may appear asymmetric due to rounding.

IND = indeterminate (due to limited reading resolution of the methods employed. For practical purposes the 95% Expanded Uncertainty can be set between zero and a two times multiple of the upper bound/non-detect limit value).

Table 2. Indicative Values for in OREAS 455.

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
Borate Fusion XRF								
As	ppm	11.7	Ge	ppm	< 100	Se	ppm	< 100
BaO	ppm	139	Hf	ppm	< 80	Sn	ppm	< 100
Bi	ppm	< 100	Hg	ppm	< 100	SrO	ppm	< 100
C	wt. %	0.100	In	ppm	< 100	Ta	ppm	< 100
Cd	ppm	< 100	Mo	ppm	< 100	Te	ppm	< 100
Cl	ppm	1479	Rb	ppm	< 100	Tl	ppm	< 100
Cs	ppm	< 100	Sb	ppm	< 100	W	ppm	< 100
Ga	ppm	< 100	Sc	ppm	24.5	ZrO ₂	ppm	57
Thermogravimetry								
H ₂ O-	wt. %	6.88						
Borate / Peroxide Fusion ICP								
Ag	ppm	< 10	Na	wt. %	0.401	Ta	ppm	< 0.5
Bi	ppm	0.081	Nb	ppm	1.48	Tl	ppm	0.083
Ge	ppm	1.44	P	wt. %	0.006			
Hf	ppm	0.79	Sn	ppm	1.14			

SI unit equivalents: ppm (parts per million; 1×10^{-6}) $\equiv$ mg/kg; wt. % (weight per cent) $\equiv$ % (mass fraction).

Note: the number of significant figures reported is not a reflection of the level of certainty of stated values. They are instead an artefact of ORE's in-house CRM-specific LIMS.

TABLE OF CONTENTS

INTRODUCTION	6
INTENDED USE	6
SOURCE MATERIAL	7
MINIMUM SAMPLE SIZE	7
INSTRUCTIONS FOR HANDLING, STORAGE & CORRECT USE	7
PERIOD OF VALIDITY	8
COMMUNITION AND HOMOGENISATION PROCEDURES	9
PHYSICAL PROPERTIES	9
MINERALOGY	9
ANALYTICAL PROGRAM	10
PARTICIPATING LABORATORIES	11
STATISTICAL ANALYSIS	11
Certified Values and their uncertainty intervals	11
Indicative (uncertified) values	12
Homogeneity Evaluation	12
METROLOGICAL TRACEABILITY	13
COMMUTABILITY	14
PERFORMANCE GATES	14
PREPARER AND SUPPLIER	17
CERTIFYING OFFICER	17
ACCREDITATION	17
LEGAL NOTICE	17
DOCUMENT HISTORY	20
REFERENCES	20

LIST OF TABLES

Table 1. Certified Values, Uncertainty & Tolerance Intervals in OREAS 455	2
Table 2. Indicative Values for in OREAS 455.	4
Table 3. Physical properties of in OREAS 455.	9
Table 4. Indicative mineralogy of in OREAS 455 by semi-quantitative XRD analysis	10
Table 5. Performance Gates for OREAS 455.	15

LIST OF FIGURES

Figure 1. Ni by borate fusion XRF in OREAS 455	18
Figure 2. Co by borate fusion XRF in OREAS 455	19

INTRODUCTION

OREAS reference materials are intended to provide a low-cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures. OREAS reference materials enable users to successfully achieve process control of these tasks because the observed variance from repeated analysis has its origin almost exclusively in the analytical process rather than the reference material itself. In evaluating laboratory performance with this CRM, the section headed 'Instructions for handling and correct use' should be read carefully.

Table 1 provides the certified values and their associated 95 % expanded uncertainty and tolerance intervals, Table 2 shows indicative values including major and trace element characterisation, Table 3 provides some indicative physical properties, Table 4 shows indicative mineralogy by semi-quantitative XRD analysis and Table 5 presents the performance gate intervals for all certified values.

Tabulated results of all analytes together with uncorrected means, medians, standard deviations, relative standard deviations and per cent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**OREAS 455-DataPack.1.0.260826_172107.xlsx**). The certified values and uncertainties in this Certificate are the sole authoritative figures. Any additional significant figures in the DataPack are provided for reference only and do not affect the certified results.

Results are also presented in scatter plots for Ni and Co by fusion XRF in Figures 1 to 2 respectively, together with $\pm 3SD$ (magenta) and $\pm 5\%$ (yellow) control lines and certified value (green line). Accepted individual results are coloured blue and individual and dataset outliers are identified in red and violet, respectively.

INTENDED USE

OREAS 455 is intended to cover all activities needed to produce a measurement result. This includes extraction, possible separation steps and the actual measurement process (the signal producing step). OREAS 455 may be used to calibrate the entire procedure by producing a pure substance CRM transformed into a calibration solution.

OREAS 455 is intended for the following uses:

- For the monitoring of laboratory performance in the analysis of analytes reported in Table 1 in geological samples
- For the verification/ validation of analytical methods for analytes reported in Table 1
- For the calibration of instruments used in the determination of the concentration of analytes reported in Table 1. When a value provided in this certificate is used to calibrate a measurement process, the uncertainty associated with that value should be appropriately propagated into the user's uncertainty calculation. Users can determine an approximation of the standard uncertainty by calculating one fourth of the width of the Expanded Uncertainty interval given in this certificate (Expanded Uncertainty intervals are provided in Table 1)

SOURCE MATERIAL

OREAS 455 was prepared predominantly from nontronitic nickel-cobalt laterite ore sourced from Bulong, Western Australia, with lesser additions of other lateritic nickel materials from Murrin Murrin to achieve the target nickel, cobalt and matrix composition.

MINIMUM SAMPLE SIZE

To relate analytical determinations to the values in this certificate, the minimum mass of sample used should match the typical mass that the laboratories used in the interlaboratory (round robin) certification program. This means that different minimum sample masses should be used depending on the operationally defined methodology as follows:

- Borate fusion with X-ray fluorescence finish: ≥ 0.2 g
- Loss on Ignition (LOI) at 1000 °C: ≥ 1 g
- Borate fusion /Sodium peroxide with ICP-OES and/or MS finish: ≥ 0.2 g
- C and S by infrared combustion furnace/CS analyser: ≥ 0.1 g

INSTRUCTIONS FOR HANDLING, STORAGE & CORRECT USE

Fine powders pose a risk to eyes and lungs and therefore standard precautions including the use of safety glasses and dust masks are advised.

Pre-homogenisation of the CRM prior to subsampling and analysis is not necessary as there is no particle segregation under transport [11].

As per routine analysis at commercial laboratories, the certified values derived by borate fusion with XRF finish are on a dry sample basis.

Analytes by all other methods refer to the concentration levels in the packaged state. There is no need for drying prior to weighing and analysis for these methods.

Single-use Sachets

OREAS 455 is packaged in single-use, 10 g laminated foil sachets. Following analysis, it is the manufacturer's expectation that any remaining material is discarded. It is the user's responsibility to prevent contamination and avoid prolonged exposure of the sample to the atmosphere prior to analysis.

Repeat-use packaging (e.g., 500 g plastic jars)

After taking a subsample, users should replace the lid of the jar promptly and securely to prevent accidental spills and airborne contamination. OREAS 455 contains a hygroscopic matrix with an indicative value for moisture provided to enable users to check for changes to stored material by determining moisture in the user's laboratory and comparing the result to the value in Table 3 in this certificate.

Authoritative Source of Information

This Certificate of Analysis constitutes the primary and authoritative document for the certified values, associated expanded uncertainties, and their correct use. While the accompanying DataPack provides supporting information, including raw data and uncertainty estimates with additional significant figures, these extended figures are provided solely for transparency, convenience and statistical reference. Users must rely exclusively on the values stated in this Certificate, rounded to an appropriate number of significant figures, for all metrological and analytical purposes. Any discrepancy between values presented in the DataPack and those in this Certificate shall be resolved in favour of the information provided herein.

Notice on Certificate Updates

The version of the Certificate of Analysis (COA) available on the OREAS website is considered the official and most current version. As COAs may be revised following periodic reviews, re-evaluation of data, or the availability of new information, users are strongly advised to refer to the latest online version prior to each use.

It is the user's responsibility to ensure that the most recent and applicable certificate is used to support the traceability, validity, and fitness-for-purpose of the certified reference material (CRM). Any significant changes to the sections of this certificate will be clearly documented in the revised certificate.

QC Monitoring Using Multiples of the Standard Deviation (SD)

When applying SDs to monitor performance, it is important to recognise that laboratories differ in proficiency, and that different methods have differing levels of precision. Each laboratory has its own inherent SD (specific to an analyte–method–concentration combination), which is not directly comparable to SDs derived from a round robin.

As most data in this round robin came from world-class laboratories, the interlaboratory SDs are narrower than would be expected across a broader mix. To provide more realistic benchmarks, this report presents pooled interlaboratory SDs, incorporating both within-lab variation and between-lab bias. These should be treated as a starting point only, with QC managers refining them against their own control charts.

The performance gates shown in Table 5 are intended only to be used as an initial guide as to what a laboratory may be able to achieve. Over a period of time monitoring your own laboratory's data for this CRM, SDs should be calculated directly from your own laboratory's process. This will enable you to establish more specific performance gates that are fit for purpose for your application as well as the ability to monitor bias. If your long-term trend analysis shows an average value that differs from the certified value, the significance of this bias should be assessed against the combined standard uncertainty of the certified value and the laboratory's own measurement uncertainty. Where the observed difference lies within this combined uncertainty, the bias is generally not considered significant.

PERIOD OF VALIDITY

The certification of OREAS 455 remains valid, within the specified measurement uncertainties, until at least February 2038, provided the CRM is handled and stored in accordance with the instructions given below. This certification is nullified if the CRM is any way changed or contaminated.

Store in a clean and cool dry place away from direct sunlight.

Long-term stability will be monitored at appropriate intervals and purchasers notified if any changes are observed. The period of validity may well be indefinite and will be reassessed prior to expiry with the aim of extending the validity if possible.

COMMUNITION AND HOMOGENISATION PROCEDURES

The materials constituting OREAS 455 was prepared in the following manner:

- Drying to constant mass at 105 °C
- Crushing and multi-stage milling of the ores to 100 % minus 30 microns
- Blending the ores in appropriate proportions to achieve desired grades
- Homogenisation using OREAS' novel processing technologies
- Packaging in 10 g units in laminated foil pouches and 500 g units in plastic wide-mouth jars

PHYSICAL PROPERTIES

OREAS 455 was tested at ORE Research & Exploration Pty Ltd's onsite facility for various physical properties. Table 3 presents these findings that should be used for informational purposes only.

Table 3. Physical properties of in OREAS 455.

Bulk Density (kg/m ³)	Moisture (wt.%)	Munsell Notation [‡]	Munsell Color [‡]
569	4.20	5YR 5/6	Light Brown

[‡]The Munsell Rock Color Chart helps geologists and archeologists communicate with colour more effectively by cross-referencing ISCC-NBS colour names with unique Munsell alpha-numeric colour notations for rock colour samples.

MINERALOGY

The semi-quantitative XRD results shown in Table 4 below were undertaken by ALS Metallurgy in Balcatta, Western Australia. The results have been normalised to 100 % and represent the relative proportion of crystalline material. Totals greater or less than 100 % are due to rounding errors.

'Clay minerals' appear to be mainly vermicullite, smectite, and/or illite. 'Kandite group' appears to be mainly kaolinite. A trevorite reference pattern was used to refine and report the 'Fe or Cr spinel' phase.

Table 4. Indicative mineralogy of in OREAS 455 by semi-quantitative XRD analysis.

Mineral / Mineral Group	% (mass ratio)
Fe or Cr spinels	2
Goethite	38
Clay minerals	31
Serpentine	18
Kandite group	7
Clinopyroxene	1
Quartz	2
Magnesite	< 1
Hydrotalcite group	< 1
Steel	< 1

ANALYTICAL PROGRAM

Twenty-eight commercial analytical laboratories participated in the program to certify the elements reported in Table 1. The following methods were employed:

- Lithium borate fusion whole rock analysis package by X-ray fluorescence (up to 24 laboratories depending on the element)
- Thermogravimetry: Loss on Ignition (LOI) at 1000 °C (12 laboratories used a thermogravimetric analyser, 7 laboratories included LOI with their fusion package and 6 laboratories used a conventional muffle furnace)
- Lithium borate or sodium peroxide fusion with full suite ICP-OES and ICP-MS elemental packages (up to 24 laboratories depending on the element)
- Total C and S by IR combustion furnace (24 laboratories)

For the round robin program, six 1 kg test units were collected at predetermined intervals during the bagging stage, immediately after homogenisation. These units are considered representative of the entire prepared batch. Each participating laboratory received six test portions, obtained by subsampling 10 g from each of the six distinct 1 kg units.

Homogeneity was assessed by submitting 12 pulp samples to a single laboratory for analysis. Paired samples were drawn from each of the six test units, enabling an Analysis of Variance (ANOVA) to compare within-unit and between-unit variances. This statistical method provides a relative measure of homogeneity and tests the null hypothesis that all units derive from the same population distribution (refer to the 'Homogeneity Evaluation' section below).

PARTICIPATING LABORATORIES

1. Actlabs, Ancaster, Ontario, Canada
2. AGAT Laboratories, Calgary, Alberta, Canada
3. Alex Stewart International, Mendoza, Argentina
4. ALS, Brisbane, QLD, Australia
5. ALS, Lima, Peru
6. ALS, Loughrea, Galway, Ireland
7. ALS, Malaga, WA, Australia
8. ALS, Vancouver, BC, Canada
9. American Assay Laboratories, Sparks, Nevada, USA
10. ARGETEST Mineral Processing, Ankara, Central Anatolia, Turkey
11. Bureau Veritas Geoanalytical, Perth, WA, Australia
12. Directorate of Mineral Research & Exploration, Ankara, Ankara, Turkey
13. ESAN Istanbul, Istanbul, Turkey
14. Inspectorate (BV), Lima, Peru
15. Inspectorate Griffith India, Gandhidham, Gujarat, India
16. Inspectorate Griffith India Pvt. Ltd., Bhubaneswar, Odisha, India
17. Intertek, Cupang, Muntinlupa, Philippines
18. Intertek, Perth, WA, Australia
19. Laboratoire LABOMINE SARL, Agadir, Souss-Massa, Morocco
20. Nagrom, Perth, WA, Australia
21. Ni Lab, Pouembout, New Caledonia
22. PT Geoservices Ltd, Cikarang, Jakarta Raya, Indonesia
23. PT Intertek Utama Services, Jakarta Timur, DKI Jakarta, Indonesia
24. SGS Australia Mineral Services, Perth, WA, Australia
25. SGS Geosol Laboratorios Ltda, Vespasiano, Minas Gerais, Brazil
26. Shiva Analyticals Ltd, Bangalore North, Karnataka, India
27. Société le Nickel (SLN), Noumea, New Caledonia
28. Stewart Assay & Environmental Laboratories LLC, Kara-Balta, Chüy, Kyrgyzstan

Please note: To maintain anonymity of participating laboratories, the alphabetical list above does not correspond to the Lab ID numbers shown in the scatter plots below.

STATISTICAL ANALYSIS

Certified Values and their uncertainty intervals (Table 1) have been determined for each analyte following removal of individual, laboratory dataset (batch) and 3SD outliers (single iteration). Outlier evaluation was conducted in accordance with ISO 17034:2016 and ISO 33405:2024. While formal statistical tests were applied, professional statistical judgment was also exercised in determining the validity of potential outliers. Assessment of systematic bias and performance using independent control materials (CRMs) was incorporated to ensure compliance with the referenced standards and to establish metrological traceability of the certified values.

95% Expanded Uncertainty provides a 95 % probability that the true value of the analyte under consideration lies between the upper and lower limits and is calculated according to the method outlined in [5] and [14]. All known or suspected sources of bias have been investigated or taken into account.

Indicative (uncertified) values (Table 2) are present where the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification or where interlaboratory consensus is poor. This data is intended for 'informational purposes' only.

Standard Deviation intervals (see Table 5, 'Performance Gates') provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability.

The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e., after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e., the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. ***The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.***

Homogeneity Evaluation

The tolerance limits (ISO 16269:2014) shown in Table 1 were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for Ni by fusion XRF, where 99 % of the time ($1-\alpha=0.99$) at least 95 % of subsamples ($p=0.95$) will have concentrations lying between 1.64 and 1.67 wt.%. Put more precisely, this means that if the same number of subsamples were taken and analysed in the same manner repeatedly, 99 % of the tolerance intervals so constructed would cover at least 95 % of the total population, and 1 % of the tolerance intervals would cover less than 95 % of the total population. ***Please note that tolerance limits pertain to the homogeneity of the CRM only and should not be used as control limits for laboratory performance.***

Analysis of Variance (ANOVA) Study

In addition to the precision error method outlined above, homogeneity was also evaluated using an ANOVA study. This involved sending 12 × 10 g pulp samples to the Bureau Veritas Geoanalytical (Perth, Australia) laboratory for analysis by lithium borate fusion with X-ray fluorescence finish (code XF201). The 12 samples consisted of paired samples from each of the six sampling units to enable an Analysis of Variance (ANOVA) by comparison of within- and between-unit variances across the six pairs. The samples were randomised prior to submission to minimise potential analytical sequence effects. The ANOVA enables a relative measure of homogeneity and permits a test of the null hypothesis that all 'units' are drawn from the same population distribution. An ANOVA constructed in this way tests that no statistically significant difference exists in the variance between-units to that of the variance within-units. A p -value < 0.05 would indicate rejection of the null hypothesis at the 95 % confidence level (i.e., a significant difference likely does exist; meaning there is evidence of heterogeneity between the sample intervals).

Of the thirteen analytes evaluated by ANOVA, only Fe returned a statistically significant result ($p = 0.039$). However, Fe showed very low dispersion ($RSD = 0.19\%$), with XRF results limited to just two reported values (25.2–25.3% Fe) due to the 0.1% reporting resolution. Round robin Fe results also showed no systematic trend with sampling interval. The Fe p -value result is therefore considered a statistical anomaly rather than evidence of meaningful CRM heterogeneity. It is important to note that ANOVA provides a relative measure of homogeneity and that a CRM having poor absolute homogeneity can still pass these tests if the within-unit heterogeneity is large and similar across all units. Based on the statistical analysis of the results of the interlaboratory certification program, it can be concluded that OREAS 455 is fit-for-purpose as a certified reference material (see 'Intended Use').

METROLOGICAL TRACEABILITY

The measurement scale for the certified values is mass fraction (mass/mass), with the underlying mass measurements metrologically traceable to the International System of Units (SI) through the SI unit of mass [13]. In accordance with common geoanalytical practice, data presented in the tables of this certificate are expressed as mass fractions in either weight percent (wt. %) or parts per million (ppm), with ppm equivalent to milligrams per kilogram (mg/kg).

Samples submitted to the interlaboratory certification program were selected to be representative of the entire prepared batch of CRM, with this representativeness maintained across the laboratory sample sets. Each analytical dataset was subject to the participating laboratory's internal quality-control procedures, including the use of reference materials and other appropriate QC checks.

Participating laboratories were selected on the basis of demonstrated analytical competence, including prior performance in interlaboratory comparison programs conducted by ORE Pty Ltd, with consideration given to their expertise in the relevant analytical methods, measurands and sample matrices. For the measurands reported in this certificate (Table 1), data were obtained from laboratories accredited to ISO/IEC 17025 where applicable. Where formal accreditation was not held for a specific measurand, evidence supporting analytical competence and metrological traceability was obtained through the inclusion of well-characterised, independently certified reference materials as control samples in the round robin study.

Consistent with ISO 33405:2024 [4], clause 9.2.5, and ISO 17034:2016 [8], clause 7.12.4, the metrological traceability and validity of measurement results used for characterisation were evaluated using appropriate supporting evidence. Agreement of measured control-sample values with their certified values provided additional evidence of the validity of results generated by participating laboratories. The certified values were assigned from the means of accepted laboratory datasets following the statistical procedures described in this report.

Operationally Defined Measurands

The certified values assigned to OREAS reference materials are operationally defined. The value obtained is therefore dependent, to some degree, on the measurement approach and conditions under which the measurand is realised and cannot necessarily be defined independently of them. Accordingly, while the mass-fraction measurement scale is underpinned by mass measurements traceable to the SI, metrological traceability of the certified value is established with reference to the applicable operationally defined measurand.

In accordance with ISO 33405:2024 [4], clause 9.5, characterisation is based on results obtained from a network of competent laboratories working within the applicable operational definition, with concordance of the results assessed as part of the value-assignment process. Individual laboratory implementations may vary, and the resulting interlaboratory variation reflects, in part, differences inherent in the practical realisation of the measurand.

The certified value is therefore applicable to measurements consistent with the stated operational definition. Relevant interlaboratory variation is incorporated, as appropriate, into the uncertainty associated with the certified value. This approach provides the basis for metrological traceability appropriate to operationally defined measurands and supports the requirements of ISO 17034:2016 and ISO 33405:2024.

COMMUTABILITY

The certified values reported herein are derived from measurements performed using analytical methods involving sample pre-treatment steps, such as fusion or acid digestion. These processes convert the sample matrix into a chemically simplified and stable form, facilitating calibration traceable to primary standards via solution-based calibration protocols. Due to the established robustness and effectiveness of these pre-treatment methods, issues related to commutability are not expected to impact the suitability of this Certified Reference Material (CRM) for its intended use.

OREAS CRMs are prepared from natural ore materials, ensuring the presence of matrix and mineralogical characteristics representative of typical exploration and process samples. Consistent with ISO 17034:2016 and ISO Guide 30, users are advised to select CRMs with matrix and mineralisation styles closely matching those of their routine samples to minimize matrix effects and enhance analytical comparability. Detailed descriptions of the CRM's source material and mineralogical characteristics are provided in the 'Source Material' section to guide appropriate CRM selection.

PERFORMANCE GATES

Table 5 below shows intervals calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned (also see 'Intended Use' section below). Westgard Rules extend the basics of single-rule QC monitoring using multi-rules (for more information visit www.westgard.com/mltirule.htm). A second method utilises a 5 % window calculated directly from the certified value.

Standard deviation is also shown in relative percent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5 % window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5 % method are too narrow. One approach used at commercial laboratories is to set the acceptance criteria at twice the detection level (DL) ± 10 %.

i.e., Certified Value ± 10 % $\pm 2DL$ [1].

Table 5. Performance Gates for OREAS 455.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5 % window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Borate Fusion XRF											
Al ₂ O ₃ , wt. %	8.24	0.071	8.10	8.38	8.03	8.45	0.86%	1.71%	2.57%	7.83	8.65
CaO, wt. %	0.232	0.011	0.210	0.254	0.199	0.265	4.77%	9.54%	14.31%	0.220	0.244
Co, ppm	851	14	822	879	808	894	1.68%	3.36%	5.04%	808	893
Cr ₂ O ₃ , wt. %	1.08	0.014	1.05	1.11	1.04	1.12	1.32%	2.64%	3.96%	1.02	1.13
Cu, ppm	66	11	44	88	33	99	16.70%	33.40%	50.10%	63	70
Fe ₂ O ₃ , wt. %	36.05	0.366	35.32	36.78	34.95	37.15	1.01%	2.03%	3.04%	34.25	37.85
K ₂ O, wt. %	0.134	0.011	0.113	0.155	0.102	0.166	7.98%	15.95%	23.93%	0.127	0.141
MgO, wt. %	3.97	0.058	3.86	4.09	3.80	4.14	1.45%	2.91%	4.36%	3.77	4.17
MnO, wt. %	0.283	0.006	0.271	0.295	0.264	0.301	2.18%	4.36%	6.54%	0.269	0.297
Na ₂ O, wt. %	0.676	0.054	0.568	0.783	0.515	0.837	7.95%	15.89%	23.84%	0.642	0.710
Ni, wt. %	1.65	0.016	1.62	1.69	1.60	1.70	0.99%	1.99%	2.98%	1.57	1.74
P ₂ O ₅ , wt. %	0.010	0.001	0.008	0.013	0.006	0.014	12.54%	25.07%	37.61%	0.010	0.011
Pb, ppm	< 50	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
SiO ₂ , wt. %	36.83	0.316	36.19	37.46	35.88	37.78	0.86%	1.72%	2.58%	34.99	38.67
SO ₃ , wt. %	0.220	0.019	0.183	0.257	0.164	0.276	8.47%	16.93%	25.40%	0.209	0.231
TiO ₂ , wt. %	0.303	0.019	0.265	0.342	0.246	0.361	6.30%	12.60%	18.90%	0.288	0.319
V ₂ O ₅ , ppm	190	17	157	223	140	240	8.77%	17.54%	26.31%	180	199
Zn, ppm	167	12	143	190	132	202	7.02%	14.05%	21.07%	158	175
Thermogravimetry											
LOI ¹⁰⁰⁰ , wt. %	9.70	0.434	8.83	10.57	8.40	11.00	4.48%	8.96%	13.43%	9.21	10.18
Borate / Peroxide Fusion ICP											
Al, wt. %	4.16	0.136	3.89	4.44	3.76	4.57	3.27%	6.54%	9.82%	3.96	4.37
As, ppm	< 100	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
B, ppm	56	8	39	72	31	81	14.72%	29.44%	44.16%	53	59
Ba, ppm	105	6	94	117	88	123	5.51%	11.02%	16.53%	100	111
Be, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ca, wt. %	0.155	0.029	0.097	0.212	0.068	0.241	18.64%	37.28%	55.92%	0.147	0.162
Cd, ppm	< 10	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ce, ppm	24.5	1.93	20.6	28.3	18.7	30.3	7.90%	15.79%	23.69%	23.3	25.7
Co, ppm	824	31	762	886	732	917	3.75%	7.49%	11.24%	783	865
Cr, wt. %	0.708	0.038	0.633	0.783	0.596	0.821	5.30%	10.60%	15.91%	0.673	0.744
Cs, ppm	0.43	0.07	0.30	0.57	0.23	0.64	15.44%	30.88%	46.32%	0.41	0.46
Cu, ppm	58	7	44	73	37	80	12.47%	24.95%	37.42%	55	61
Dy, ppm	1.02	0.10	0.81	1.22	0.71	1.33	10.08%	20.16%	30.24%	0.97	1.07
Er, ppm	0.60	0.07	0.46	0.75	0.38	0.83	12.26%	24.52%	36.77%	0.57	0.63
Eu, ppm	0.31	0.04	0.23	0.39	0.19	0.43	12.91%	25.81%	38.72%	0.30	0.33
Fe, wt. %	24.10	0.864	22.37	25.82	21.50	26.69	3.59%	7.17%	10.76%	22.89	25.30
Ga, ppm	7.42	1.28	4.86	9.99	3.57	11.27	17.29%	34.58%	51.87%	7.05	7.79
Gd, ppm	0.97	0.11	0.75	1.19	0.64	1.30	11.18%	22.35%	33.53%	0.92	1.02
Ho, ppm	0.20	0.03	0.14	0.25	0.11	0.28	13.98%	27.96%	41.95%	0.19	0.21
In, ppm	< 0.1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
K, wt. %	0.107	0.020	0.067	0.148	0.047	0.168	18.85%	37.69%	56.54%	0.102	0.113
La, ppm	3.08	0.307	2.46	3.69	2.16	4.00	9.96%	19.93%	29.89%	2.92	3.23

SI unit equivalents: ppm (parts per million; 1×10^{-6}) $\equiv$ mg/kg; wt. % (weight per cent) $\equiv$ % (mass fraction).

Note 1: intervals may appear asymmetric due to rounding; IND = indeterminate.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

Table 5 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5 % window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Borate / Peroxide Fusion ICP continued											
Li, ppm	7.69	1.18	5.33	10.05	4.15	11.23	15.34%	30.68%	46.02%	7.31	8.08
Lu, ppm	0.10	0.01	0.08	0.12	0.07	0.14	11.59%	23.18%	34.77%	0.10	0.11
Mg, wt. %	2.28	0.082	2.12	2.45	2.04	2.53	3.58%	7.17%	10.75%	2.17	2.40
Mn, wt. %	0.210	0.008	0.194	0.227	0.185	0.236	3.99%	7.97%	11.96%	0.200	0.221
Mo, ppm	20.0	2.9	14.2	25.8	11.3	28.7	14.52%	29.03%	43.55%	19.0	21.0
Nd, ppm	3.93	0.48	2.96	4.89	2.48	5.38	12.30%	24.59%	36.89%	3.73	4.13
Ni, wt. %	1.58	0.063	1.45	1.71	1.39	1.77	4.02%	8.03%	12.05%	1.50	1.66
Pb, ppm	< 100	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Pr, ppm	0.97	0.052	0.86	1.07	0.81	1.12	5.41%	10.82%	16.22%	0.92	1.02
Rb, ppm	3.84	0.66	2.53	5.16	1.87	5.81	17.10%	34.19%	51.29%	3.65	4.04
Re, ppm	< 0.1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt. %	0.090	0.009	0.072	0.107	0.063	0.116	10.04%	20.07%	30.11%	0.085	0.094
Sb, ppm	0.90	0.20	0.49	1.30	0.29	1.51	22.67%	45.33%	68.00%	0.85	0.94
Sc, ppm	27.2	2.31	22.6	31.8	20.2	34.1	8.49%	16.99%	25.48%	25.8	28.5
Se, ppm	< 20	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Si, wt. %	16.80	0.484	15.83	17.77	15.35	18.25	2.88%	5.76%	8.64%	15.96	17.64
Sm, ppm	0.98	0.095	0.79	1.17	0.70	1.27	9.67%	19.35%	29.02%	0.93	1.03
Sr, ppm	14.4	2.6	9.1	19.7	6.5	22.4	18.31%	36.62%	54.93%	13.7	15.1
Tb, ppm	0.17	0.009	0.15	0.18	0.14	0.19	5.68%	11.36%	17.05%	0.16	0.17
Te, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	0.81	0.061	0.69	0.93	0.62	0.99	7.53%	15.05%	22.58%	0.77	0.85
Ti, wt. %	0.173	0.007	0.158	0.187	0.151	0.194	4.12%	8.24%	12.36%	0.164	0.181
Tm, ppm	0.088	0.017	0.053	0.123	0.036	0.141	19.72%	39.44%	59.16%	0.084	0.093
U, ppm	0.53	0.06	0.40	0.66	0.33	0.72	12.31%	24.62%	36.93%	0.50	0.55
V, ppm	104	7	91	117	84	123	6.30%	12.59%	18.89%	98	109
W, ppm	4.57	0.65	3.26	5.88	2.61	6.53	14.29%	28.58%	42.87%	4.34	4.80
Y, ppm	3.77	0.196	3.37	4.16	3.18	4.35	5.21%	10.42%	15.64%	3.58	3.95
Yb, ppm	0.71	0.055	0.60	0.82	0.55	0.88	7.69%	15.39%	23.08%	0.68	0.75
Zn, ppm	161	10	141	180	132	189	5.99%	11.97%	17.96%	152	169
Zr, ppm	32.8	5.4	22.0	43.6	16.7	48.9	16.41%	32.82%	49.23%	31.2	34.4
Infrared Combustion											
C, wt. %	0.167	0.030	0.108	0.226	0.078	0.256	17.74%	35.47%	53.21%	0.158	0.175
S, wt. %	0.085	0.017	0.051	0.119	0.034	0.136	19.95%	39.90%	59.85%	0.081	0.089

SI unit equivalents: wt. % (weight per cent) $\equiv$ % (mass fraction).

Note 1: intervals may appear asymmetric due to rounding; IND = indeterminate.

Note 2: the number of decimal places quoted does not imply accuracy of the certified value to this level but are given to minimise rounding errors when calculating 2SD and 3SD windows.

PREPARER AND SUPPLIER

Certified reference material OREAS 455 is prepared, certified and supplied by:

ORE Research & Exploration Pty Ltd
37A Hosie Street
Bayswater North VIC 3153
AUSTRALIA

Tel: +613-9729 0333
Web: www.oreas.com
Email: info@ore.com.au

CERTIFYING OFFICER

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager - ORE P/L

ACCREDITATION

ORE Pty Ltd is ISO 9001:2015 certified by Lloyd's Register Quality Assurance Ltd (LRQA) for its quality management system (QMS) encompassing the development, manufacturing, certification and supply of CRMs.



ORE Pty Ltd is ISO 17034:2016 accredited as a reference material producer (RMP) by the National Association of Testing Authorities (NATA) in Australia (accreditation number 20483).



LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

© COPYRIGHT Ore Research & Exploration Pty Ltd.
Unauthorised copying, reproduction, storage or dissemination is prohibited.

Figure 1. Ni by Borate Fusion XRF in OREAS 455

SPC.2079.RR.OREAS 455.2.Fusion XRF.Ni.Lab.260818.132850.SS





Figure 2. Co by Borate Fusion XRF in OREAS 455

SPC.2079.RR.OREAS 455.2.Fusion XRF.Co.Lab.260818.132651.SN



DOCUMENT HISTORY

Revision No.	Date	Changes applied
0	27 th Aug, 2026	First publication.

REFERENCES

- [1] Govett, G.J.S. (1983). Handbook of Exploration Geochemistry, Volume 2: Statistics and Data Analysis in Geochemical Prospecting (Variations of accuracy and precision).
- [2] ISO Guide 30:2015. Terms and definitions used in connection with reference materials.
- [3] ISO 33401:2024-01. Reference materials – Contents of certificates, labels and accompanying documentation.
- [4] ISO 33405:2024-05. Reference materials – Approaches for characterization and assessment of homogeneity and stability.
- [5] ISO Guide 98-3:2008. Guide to the expression of uncertainty in measurement (GUM:1995).
- [6] ISO 16269:2014. Statistical interpretation of data – Part 6: Determination of statistical tolerance intervals.
- [7] ISO 17025:2017, General requirements for the competence of testing and calibration laboratories.
- [8] ISO 17034:2016. General requirements for the competence of reference material producers.
- [9] Munsell Rock Color Book (2014). Rock-Color Chart Committee, Geological Society of America (GSA), Minnesota (USA).
- [10] OREAS-BUP-70-09-11: Statistical Analysis - OREAS Evaluation Method.
- [11] OREAS-TN-04-1498: Stability under transport; an experimental study of OREAS CRMs.
- [12] OREAS-TN-05-1674: Long-term storage stability; an experimental study of OREAS CRMs.
- [13] Thompson, A.; Taylor, B.N. (2008); Guide for the Use of the International System of Units (SI); NIST Special Publication 811; U.S. Government Printing Office: Washington, DC; available at: <https://physics.nist.gov/cuu/pdf/sp811.pdf> (accessed Nov 2021).
- [14] Van der Veen A.M.H. et al. (2001). Uncertainty calculations in the certification of reference materials, Accred Qual Assur 6: 290-294.