

CERTIFICATE OF ANALYSIS FOR
COPPER ORE REFERENCE MATERIAL
OREAS 927

Table 1. Certified Values, SDs, 95% Confidence and Tolerance Limits for OREAS 927

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
4-Acid Digestion						
Ag, Silver (ppm)	4.08	0.45	3.92	4.23	3.68	4.47
Al, Aluminium (wt.%)	6.41	0.309	6.26	6.56	6.16	6.65
As, Arsenic (ppm)	16.3	1.07	15.9	16.7	15.3	17.4
Ba, Barium (ppm)	308	25.4	295	321	295	321
Be, Beryllium (ppm)	1.80	0.165	1.72	1.88	1.68	1.92
Bi, Bismuth (ppm)	57	7	54	60	53	62
Ca, Calcium (wt.%)	0.390	0.017	0.381	0.398	0.377	0.402
Cd, Cadmium (ppm)	1.01	0.11	0.96	1.05	0.96	1.05
Ce, Cerium (ppm)	72	3.5	70	74	71	74
Co, Cobalt (ppm)	28.7	2.08	27.8	29.6	27.6	29.9
Cr, Chromium (ppm)	62	8	58	66	57	67
Cs, Cesium (ppm)	5.19	0.313	5.00	5.38	5.06	5.32
Cu, Copper (wt.%)	1.08	0.024	1.07	1.09	1.05	1.10
Dy, Dysprosium (ppm)	4.08	0.313	3.85	4.32	3.96	4.21
Er, Erbium (ppm)	2.28	0.207	2.11	2.44	2.20	2.36
Eu, Europium (ppm)	1.07	0.069	1.02	1.13	1.04	1.11
Fe, Iron (wt.%)	8.35	0.455	8.13	8.58	8.15	8.56
Ga, Gallium (ppm)	18.1	1.48	17.3	18.9	17.6	18.6
Gd, Gadolinium (ppm)	4.89	0.389	4.59	5.19	4.76	5.02
Ge, Germanium (ppm)	< 2	IND	IND	IND	IND	IND
Hf, Hafnium (ppm)	2.87	0.235	2.74	3.00	2.78	2.96
Ho, Holmium (ppm)	0.76	0.051	0.72	0.80	0.73	0.79
In, Indium (ppm)	1.07	0.066	1.03	1.10	1.03	1.10
K, Potassium (wt.%)	1.79	0.060	1.77	1.82	1.76	1.83
La, Lanthanum (ppm)	36.6	1.51	35.8	37.3	35.6	37.5
Li, Lithium (ppm)	34.5	1.86	33.5	35.5	33.2	35.8
Lu, Lutetium (ppm)	0.31	0.022	0.29	0.32	0.29	0.33
Mg, Magnesium (wt.%)	2.11	0.105	2.06	2.16	2.04	2.17
Mn, Manganese (wt.%)	0.115	0.004	0.113	0.116	0.111	0.118

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
4-Acid Digestion continued						
Mo, Molybdenum (ppm)	1.21	0.15	1.13	1.30	1.06	1.37
Na, Sodium (wt.%)	0.191	0.012	0.185	0.198	0.183	0.200
Nb, Niobium (ppm)	11.1	1.03	10.5	11.6	10.6	11.5
Nd, Neodymium (ppm)	30.8	1.66	29.4	32.1	29.7	31.9
Ni, Nickel (ppm)	29.7	2.08	28.8	30.6	28.5	30.9
P, Phosphorus (wt.%)	0.056	0.003	0.054	0.057	0.053	0.058
Pb, Lead (ppm)	209	8.0	205	212	203	214
Pr, Praseodymium (ppm)	8.25	0.365	7.93	8.56	8.01	8.48
Rb, Rubidium (ppm)	119	8.9	113	124	115	122
Re, Rhenium (ppb)	< 2	IND	IND	IND	IND	IND
S, Sulphur (wt.%)	1.75	0.106	1.70	1.80	1.71	1.79
Sb, Antimony (ppm)	1.65	0.159	1.58	1.73	1.56	1.75
Sc, Scandium (ppm)	11.3	1.3	10.7	12.0	11.0	11.7
Se, Selenium (ppm)	15.7	1.50	14.9	16.5	14.6	16.8
Sm, Samarium (ppm)	5.80	0.486	5.43	6.18	5.64	5.97
Sn, Tin (ppm)	20.7	1.02	20.3	21.2	19.9	21.6
Sr, Strontium (ppm)	28.3	1.17	27.7	28.9	27.1	29.5
Ta, Tantalum (ppm)	0.86	0.078	0.81	0.91	0.82	0.91
Tb, Terbium (ppm)	0.71	0.063	0.67	0.75	0.69	0.73
Te, Tellurium (ppm)	< 0.1	IND	IND	IND	IND	IND
Th, Thorium (ppm)	13.9	1.04	13.4	14.5	13.5	14.3
Ti, Titanium (wt.%)	0.328	0.025	0.316	0.341	0.316	0.340
Tl, Thallium (ppm)	0.67	0.039	0.65	0.69	0.65	0.69
Tm, Thulium (ppm)	0.32	0.03	0.30	0.35	IND	IND
U, Uranium (ppm)	2.60	0.160	2.51	2.69	2.53	2.67
V, Vanadium (ppm)	78	5.3	75	80	75	80
W, Tungsten (ppm)	7.74	0.758	7.43	8.05	7.28	8.20
Y, Yttrium (ppm)	20.0	1.40	19.2	20.7	19.4	20.5
Yb, Ytterbium (ppm)	1.98	0.107	1.91	2.05	1.87	2.08
Zn, Zinc (ppm)	716	35.8	703	730	690	743
Zr, Zirconium (ppm)	97	9.4	92	102	94	100
Aqua Regia Digestion						
Ag, Silver (ppm)	3.90	0.37	3.75	4.05	3.63	4.17
Al, Aluminium (wt.%)	3.14	0.130	3.08	3.21	3.06	3.23
As, Arsenic (ppm)	15.8	1.21	15.3	16.4	15.2	16.4
Au, Gold (ppb)	< 10	IND	IND	IND	IND	IND
B, Boron (ppm)	< 10	IND	IND	IND	IND	IND
Ba, Barium (ppm)	39.8	3.79	37.8	41.9	37.9	41.7
Be, Beryllium (ppm)	0.51	0.040	0.49	0.53	0.48	0.55
Bi, Bismuth (ppm)	59	4.1	57	60	55	62
Ca, Calcium (wt.%)	0.287	0.008	0.283	0.291	0.276	0.298
Cd, Cadmium (ppm)	0.97	0.043	0.95	0.99	0.93	1.01
Ce, Cerium (ppm)	45.4	7.0	41.1	49.6	44.0	46.7

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Aqua Regia Digestion continued						
Co, Cobalt (ppm)	28.6	1.14	28.1	29.1	27.6	29.7
Cr, Chromium (ppm)	39.2	1.80	38.4	40.1	37.7	40.8
Cs, Cesium (ppm)	1.47	0.18	1.36	1.58	1.42	1.52
Cu, Copper (wt.%)	1.06	0.039	1.04	1.08	1.04	1.09
Dy, Dysprosium (ppm)	2.25	0.44	1.75	2.75	2.15	2.35
Er, Erbium (ppm)	< 2	IND	IND	IND	IND	IND
Eu, Europium (ppm)	0.69	0.12	0.54	0.83	0.65	0.72
Fe, Iron (wt.%)	7.93	0.332	7.77	8.09	7.76	8.10
Ga, Gallium (ppm)	9.11	0.592	8.76	9.46	8.90	9.32
Gd, Gadolinium (ppm)	3.18	0.65	2.54	3.81	3.04	3.31
Ge, Germanium (ppm)	< 0.3	IND	IND	IND	IND	IND
Hf, Hafnium (ppm)	< 0.8	IND	IND	IND	IND	IND
Hg, Mercury (ppm)	< 0.13	IND	IND	IND	IND	IND
Ho, Holmium (ppm)	< 0.6	IND	IND	IND	IND	IND
In, Indium (ppm)	1.00	0.062	0.96	1.04	0.98	1.02
K, Potassium (wt.%)	0.230	0.027	0.216	0.245	0.219	0.242
La, Lanthanum (ppm)	22.7	2.5	21.3	24.1	22.1	23.4
Li, Lithium (ppm)	28.3	2.57	26.9	29.6	27.2	29.4
Lu, Lutetium (ppm)	< 0.2	IND	IND	IND	IND	IND
Mg, Magnesium (wt.%)	1.92	0.089	1.87	1.96	1.87	1.96
Mn, Manganese (wt.%)	0.101	0.005	0.099	0.104	0.099	0.104
Mo, Molybdenum (ppm)	1.07	0.12	1.01	1.13	1.01	1.14
Na, Sodium (wt.%)	0.011	0.001	0.010	0.011	IND	IND
Nb, Niobium (ppm)	< 0.5	IND	IND	IND	IND	IND
Nd, Neodymium (ppm)	20.5	3.2	17.3	23.7	19.6	21.4
Ni, Nickel (ppm)	28.0	1.50	27.2	28.7	27.2	28.7
P, Phosphorus (wt.%)	0.054	0.003	0.052	0.056	0.051	0.056
Pb, Lead (ppm)	203	9.1	199	207	197	208
Pr, Praseodymium (ppm)	5.18	1.02	4.17	6.18	4.93	5.43
Rb, Rubidium (ppm)	14.7	2.4	13.2	16.1	14.3	15.1
Re, Rhenium (ppb)	< 1	IND	IND	IND	IND	IND
S, Sulphur (wt.%)	1.67	0.117	1.61	1.73	1.62	1.72
Sb, Antimony (ppm)	< 1	IND	IND	IND	IND	IND
Sc, Scandium (ppm)	3.87	0.375	3.67	4.08	3.73	4.01
Se, Selenium (ppm)	15.3	1.41	14.7	16.0	14.9	15.8
Sm, Samarium (ppm)	3.81	0.64	3.17	4.44	3.60	4.01
Sn, Tin (ppm)	12.2	0.62	11.8	12.6	11.9	12.5
Sr, Strontium (ppm)	12.4	0.57	12.0	12.7	11.9	12.8
Ta, Tantalum (ppm)	< 0.05	IND	IND	IND	IND	IND
Tb, Terbium (ppm)	< 0.6	IND	IND	IND	IND	IND
Te, Tellurium (ppm)	< 0.07	IND	IND	IND	IND	IND
Th, Thorium (ppm)	12.0	1.11	11.3	12.6	11.7	12.3
Ti, Titanium (wt.%)	< 0.15	IND	IND	IND	IND	IND

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Aqua Regia Digestion continued						
Tl, Thallium (ppm)	0.13	0.02	0.12	0.14	IND	IND
Tm, Thulium (ppm)	< 0.3	IND	IND	IND	IND	IND
U, Uranium (ppm)	1.55	0.19	1.43	1.66	1.50	1.59
V, Vanadium (ppm)	34.1	1.92	33.1	35.2	32.8	35.5
W, Tungsten (ppm)	4.23	0.82	3.81	4.64	3.90	4.55
Y, Yttrium (ppm)	10.0	1.7	9.1	11.0	9.7	10.3
Yb, Ytterbium (ppm)	< 1.5	IND	IND	IND	IND	IND
Zn, Zinc (ppm)	717	28.2	704	730	700	735
Zr, Zirconium (ppm)	20.1	3.4	17.7	22.4	19.3	20.8
Peroxide Fusion ICP						
Al, Aluminium (wt.%)	6.46	0.254	6.29	6.64	6.29	6.64
As, Arsenic (ppm)	< 20	IND	IND	IND	IND	IND
B, Boron (ppm)	< 20	IND	IND	IND	IND	IND
Ba, Barium (ppm)	320	13.6	311	330	312	329
Be, Beryllium (ppm)	< 2	IND	IND	IND	IND	IND
Bi, Bismuth (ppm)	62	3.8	61	63	58	66
Ca, Calcium (wt.%)	0.431	0.074	0.377	0.485	0.403	0.459
Cd, Cadmium (ppm)	< 1.1	IND	IND	IND	IND	IND
Ce, Cerium (ppm)	73	3.2	70	75	71	74
Co, Cobalt (ppm)	31.0	2.30	29.3	32.6	29.5	32.4
Cr, Chromium (ppm)	< 80	IND	IND	IND	IND	IND
Cs, Cesium (ppm)	5.53	0.395	5.23	5.82	5.34	5.71
Cu, Copper (wt.%)	1.09	0.052	1.06	1.12	1.05	1.13
Dy, Dysprosium (ppm)	4.65	0.220	4.47	4.84	4.48	4.82
Er, Erbium (ppm)	2.62	0.233	2.42	2.81	2.52	2.72
Eu, Europium (ppm)	1.15	0.087	1.09	1.21	IND	IND
Fe, Iron (wt.%)	8.81	0.268	8.67	8.95	8.63	8.99
Ga, Gallium (ppm)	18.5	1.21	17.7	19.3	17.9	19.1
Gd, Gadolinium (ppm)	5.43	0.529	5.00	5.87	5.26	5.61
Ge, Germanium (ppm)	< 3	IND	IND	IND	IND	IND
Hf, Hafnium (ppm)	4.25	0.414	3.72	4.78	IND	IND
Ho, Holmium (ppm)	0.93	0.075	0.88	0.99	IND	IND
In, Indium (ppm)	1.13	0.079	1.08	1.18	IND	IND
K, Potassium (wt.%)	1.81	0.080	1.76	1.86	1.75	1.88
La, Lanthanum (ppm)	38.0	2.35	36.1	39.9	36.4	39.5
Li, Lithium (ppm)	32.2	2.30	30.3	34.1	30.6	33.7
Lu, Lutetium (ppm)	0.40	0.05	0.33	0.47	IND	IND
Mg, Magnesium (wt.%)	2.12	0.071	2.08	2.16	2.09	2.15
Mn, Manganese (wt.%)	0.120	0.006	0.116	0.124	0.117	0.124
Mo, Molybdenum (ppm)	< 1.5	IND	IND	IND	IND	IND
Nb, Niobium (ppm)	12.0	2.1	10.3	13.8	11.5	12.6
Nd, Neodymium (ppm)	31.8	1.73	30.4	33.2	30.8	32.8
Ni, Nickel (ppm)	30.2	4.8	24.5	35.9	28.9	31.5

Table 1 continued.

Constituent	Certified Value	1SD	95% Confidence Limits		95% Tolerance Limits	
			Low	High	Low	High
Peroxide Fusion ICP continued						
P, Phosphorus (wt.%)	0.057	0.006	0.053	0.061	0.051	0.063
Pb, Lead (ppm)	214	11.5	205	223	205	223
Pr, Praseodymium (ppm)	8.83	0.367	8.54	9.12	8.61	9.05
Rb, Rubidium (ppm)	122	2.5	120	124	119	124
S, Sulphur (wt.%)	1.78	0.049	1.74	1.81	1.74	1.82
Sb, Antimony (ppm)	1.74	0.28	1.49	1.99	IND	IND
Sc, Scandium (ppm)	10.4	0.48	9.7	11.0	IND	IND
Si, Silicon (wt.%)	29.44	1.011	28.45	30.42	28.68	30.19
Sm, Samarium (ppm)	5.88	0.396	5.60	6.16	5.66	6.10
Sn, Tin (ppm)	23.8	3.0	21.8	25.8	22.1	25.4
Sr, Strontium (ppm)	31.0	6.1	26.3	35.8	28.4	33.6
Ta, Tantalum (ppm)	0.97	0.093	0.88	1.07	IND	IND
Tb, Terbium (ppm)	0.77	0.057	0.72	0.82	IND	IND
Th, Thorium (ppm)	14.2	0.54	13.8	14.7	13.8	14.7
Ti, Titanium (wt.%)	0.352	0.022	0.338	0.366	0.340	0.364
Tl, Thallium (ppm)	0.73	0.09	0.65	0.80	IND	IND
Tm, Thulium (ppm)	0.39	0.05	0.35	0.43	IND	IND
U, Uranium (ppm)	2.79	0.178	2.64	2.94	2.71	2.87
V, Vanadium (ppm)	77	5.6	73	82	73	81
W, Tungsten (ppm)	7.99	1.28	6.78	9.21	7.30	8.69
Y, Yttrium (ppm)	24.2	0.80	23.7	24.7	23.5	24.9
Yb, Ytterbium (ppm)	2.45	0.186	2.30	2.61	2.19	2.71
Zn, Zinc (ppm)	750	35.9	729	772	721	779

Note: intervals may appear asymmetric due to rounding

INTRODUCTION

OREAS reference materials are intended to provide a low cost method of evaluating and improving the quality of analysis of geological samples. To the geologist they provide a means of implementing quality control in analytical data sets generated in exploration from the grass roots level through to prospect evaluation, and in grade control at mining operations. To the analyst they provide an effective means of calibrating analytical equipment, assessing new techniques and routinely monitoring in-house procedures.

SOURCE MATERIAL

OREAS 927 is one of a suite of sixteen copper CRMs (OREAS 920 to OREAS 935) prepared from material from the CSA mine located near the town of Cobar in central western New South Wales, Australia. The copper ore body is hosted by the Early Devonian CSA Siltstone, a thinly bedded turbiditic sequence of carbonaceous siltstones and mudstones with minor coarser units. The CSA Siltstone is part of the Cobar Supergroup, consisting of lower syn-rift sediments and upper post-rift sag phase sediments. The mineralisation is structurally controlled and confined to a number of

steeply dipping bodies within a major shear zone on the eastern margin of the Early Devonian Cobar Basin. It is characterised by low-grade greenschist alteration and epigenetic low-grade mineralisation enveloping higher-grade shoots of vein complexes or sub-massive to massive sulphides. The sulphides include chalcopyrite, pyrrhotite, pyrite, sphalerite, galena, bornite and cubanite. Iron-rich chlorite and silica are prominent alterations in the siltstone host.

COMMINUTION AND HOMOGENISATION PROCEDURES

The material constituting OREAS 927 was prepared in the following manner:

- drying to constant mass at 105°C;
- preliminary blending of copper ores and barren siltstone materials;
- multi-stage milling to approximately 99% less than 75 microns;
- final homogenisation;
- packaging in 10g units in laminated foil pouches.

ANALYTICAL PROGRAM

Twenty two commercial analytical laboratories participated in the program to characterise the analytes reported in Table 1. The following methods were employed for method specific certification:

- Four acid (HCl-HNO₃-HF-HClO₄) digestion with ICP-OES, ICP-MS or AAS finish (19 laboratories);
- Aqua regia digestion with ICP-OES, ICP-MS or AAS finish (19 laboratories);
- Peroxide fusion with ICP-OES, ICP-MS or AAS finish (12 laboratories).

For the round robin program ten 300g test units were taken at predetermined intervals during the bagging stage, immediately following final homogenisation, and are considered representative of the entire batch. The six samples received by each laboratory were obtained by taking two 20g scoop splits from each of three separate 300g test units. This format enabled nested ANOVA treatment of the results to evaluate homogeneity, i.e. to ascertain whether between-unit variance is greater than within-unit variance. Table 1 presents the certified values together with their associated 1SD's, 95% confidence and tolerance limits and Table 2 shows indicative values. Table 3 provides performance gate intervals for the certified values of each analytical method group based on their pooled 1SD's. Tabulated results of all elements together with uncorrected means, medians, standard deviations, relative standard deviations and percent deviation of lab means from the corrected mean of means (PDM³) are presented in the detailed certification data for this CRM (**Datapack for OREAS 927.xlsx**).

STATISTICAL ANALYSIS

Certified Values, Standard Deviations, Confidence and Tolerance Limits have been determined for each analytical method following removal of individual and laboratory outliers (Table 1). Certified Values are the mean of means after outlier filtering. The 95% Confidence Limit is a measure of the reliability of the certified value, i.e. the narrower the

Confidence Interval the greater the certainty in the Certified Value. It should not be used as a control limit for laboratory performance. Indicative values (Table 2) are provided where i) the number of laboratories reporting a particular analyte is insufficient (< 5) to support certification; ii) interlaboratory consensus is poor; or iii) a significant proportion of results are outlying or results are multimodal.

Table 2. Indicative Values for OREAS 927

Constituent	Unit	Value	Constituent	Unit	Value	Constituent	Unit	Value
4-Acid Digestion								
B	ppm	14.5	Hg	ppm	< 1	Ru	ppm	< 0.1
Aqua Regia Digestion								
Pd	ppb	14	Pt	ppb	< 5	Ru	ppb	< 5
Infrared Combustion								
S	wt.%	1.77						
Peroxide Fusion ICP								
Ag	ppm	3.76	Se	ppm	13.7	Zr	ppm	142
Re	ppm	< 0.1	Te	ppm	< 6			

Standard Deviation values (1SDs) are reported in Table 1 and provide an indication of a level of performance that might reasonably be expected from a laboratory being monitored by this CRM in a QA/QC program. They take into account errors attributable to measurement uncertainty and CRM variability. For an effective CRM the contribution of the latter should be negligible in comparison to measurement errors. The Standard Deviation values include all sources of measurement uncertainty: between-lab variance, within-run variance (precision errors) and CRM variability. The SD for each analyte's certified value is calculated from the same filtered data set used to determine the certified value, i.e. after removal of all individual, lab dataset (batch) and 3SD outliers (single iteration). These outliers can only be removed after the absolute homogeneity of the CRM has been independently established, i.e. the outliers must be confidently deemed to be analytical rather than arising from inhomogeneity of the CRM. The standard deviation is then calculated for each analyte from the pooled accepted analyses generated from the certification program.

Performance Gates (Table 3) are calculated for two and three standard deviations. As a guide these intervals may be regarded as warning or rejection for multiple 2SD outliers, or rejection for individual 3SD outliers in QC monitoring, although their precise application should be at the discretion of the QC manager concerned.

A second method utilises a 5% window calculated directly from the certified value. Standard deviation is also shown in relative per cent for one, two and three relative standard deviations (1RSD, 2RSD and 3RSD) to facilitate an appreciation of the magnitude of these numbers and a comparison with the 5% window. Caution should be exercised when concentration levels approach lower limits of detection of the analytical methods employed as performance gates calculated from standard deviations tend to be excessively wide whereas those determined by the 5% method are too narrow.

Tolerance Limits (ISO Guide 3207) were determined using an analysis of precision errors method and are considered a conservative estimate of true homogeneity. The meaning of tolerance limits may be illustrated for copper by 4-acid digestion, where 99% of the time ($1-\alpha=0.99$) at least 95% of subsamples ($\rho=0.95$) will have concentrations lying between 1.05 and 1.10 wt.%. Put more precisely, this means that if the same number of

subsamples were taken and analysed in the same manner repeatedly, 99% of the tolerance intervals so constructed would cover at least 95% of the total population, and 1% of the tolerance intervals would cover less than 95% of the total population (ISO Guide 35).

The homogeneity of OREAS 927 has also been evaluated in an ANOVA study for all certified analytes. This study tests the null hypothesis that no statistically significant difference exists between the *between-unit variance* and the *within-unit variance* (i.e. p-values <0.05 indicate rejection of the null hypothesis). Of the 179 certified values, no failures were observed indicating no evidence to reject the null hypothesis.

Based on the statistical analysis of the results of the inter-laboratory certification program it can be concluded that OREAS 927 is fit-for-purpose as a certified reference material (see 'Intended Use' below).

PARTICIPATING LABORATORIES

Accurassay, Thunder Bay, ON, Canada
Acme, Santiago, Chile
Acme, Vancouver, BC, Canada
Actlabs, Ancaster, Ontario, Canada
Actlabs, Kamloops, BC, Canada
Actlabs, Thunder Bay, Ontario, Canada
ALS, Brisbane, QLD, Australia
ALS, Burnie, TAS, Australia
ALS, Loughrea, County Galway, Ireland
ALS, Vancouver, BC, Canada
Amdel (BV), Cardiff, NSW, Australia
Intertek Genalysis, Perth, WA, Australia
Intertek Testing Services, Adelaide, SA, Australia
Intertek Testing Services, Beijing, China
Intertek Testing Services, Jakarta Selatan, Indonesia
Intertek Genalysis, Johannesburg, Sth Africa
Intertek Testing Services, Muntinlupa, Philippines
Labtium Oy, Rovaniemi, Finland
MINTEK, Randburg, Sth Africa
PT. Geoservices, Cikarang, Indonesia
SGS, Booyens, Gauteng, South Africa
SGS Didipio, Makati City, Philippines
SGS, Lakefield, Ontario, Canada
SGS Nui Phao, Ha Noi, Vietnam
SGS, Vancouver, BC, Canada
SGS, Vespasiano, MG, Brazil
Shiva Analyticals, Bangalore North, Karnataka, India
Ultra Trace (BV), Perth, WA, Australia

Table 3. Performance Gates for OREAS 927

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion											
Ag, ppm	4.08	0.45	3.17	4.99	2.71	5.44	11.15%	22.30%	33.44%	3.87	4.28
Al, wt. %	6.41	0.309	5.79	7.03	5.48	7.33	4.82%	9.63%	14.45%	6.09	6.73
As, ppm	16.3	1.07	14.2	18.5	13.1	19.6	6.57%	13.15%	19.72%	15.5	17.1
Ba, ppm	308	25	257	359	232	384	8.24%	16.48%	24.72%	293	323
Be, ppm	1.80	0.165	1.47	2.13	1.30	2.29	9.17%	18.34%	27.51%	1.71	1.89
Bi, ppm	57	7	43	71	37	78	12.02%	24.04%	36.07%	54	60
Ca, wt. %	0.390	0.017	0.355	0.425	0.337	0.442	4.49%	8.98%	13.47%	0.370	0.409
Cd, ppm	1.01	0.11	0.78	1.24	0.67	1.35	11.30%	22.59%	33.89%	0.96	1.06
Ce, ppm	72	3.5	65	79	62	83	4.79%	9.59%	14.38%	69	76
Co, ppm	28.7	2.08	24.6	32.9	22.5	35.0	7.23%	14.46%	21.69%	27.3	30.2
Cr, ppm	62	8	46	79	37	87	13.29%	26.58%	39.87%	59	65
Cs, ppm	5.19	0.313	4.56	5.81	4.25	6.13	6.03%	12.06%	18.09%	4.93	5.45
Cu, wt. %	1.08	0.024	1.03	1.13	1.01	1.15	2.18%	4.37%	6.55%	1.02	1.13
Dy, ppm	4.08	0.313	3.46	4.71	3.15	5.02	7.66%	15.32%	22.98%	3.88	4.29
Er, ppm	2.28	0.207	1.86	2.69	1.65	2.90	9.11%	18.23%	27.34%	2.16	2.39
Eu, ppm	1.07	0.069	0.93	1.21	0.87	1.28	6.40%	12.80%	19.20%	1.02	1.13
Fe, wt. %	8.35	0.455	7.44	9.26	6.99	9.72	5.45%	10.89%	16.34%	7.94	8.77
Ga, ppm	18.1	1.48	15.1	21.1	13.7	22.5	8.16%	16.32%	24.48%	17.2	19.0
Gd, ppm	4.89	0.389	4.11	5.67	3.72	6.06	7.96%	15.91%	23.87%	4.65	5.13
Ge, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	2.87	0.235	2.40	3.34	2.16	3.57	8.19%	16.38%	24.58%	2.73	3.01
Ho, ppm	0.76	0.051	0.66	0.86	0.61	0.91	6.77%	13.53%	20.30%	0.72	0.80
In, ppm	1.07	0.066	0.94	1.20	0.87	1.27	6.17%	12.34%	18.51%	1.01	1.12
K, wt. %	1.79	0.060	1.67	1.91	1.61	1.97	3.35%	6.69%	10.04%	1.71	1.88
La, ppm	36.6	1.51	33.6	39.6	32.0	41.1	4.13%	8.27%	12.40%	34.7	38.4
Li, ppm	34.5	1.86	30.8	38.2	28.9	40.1	5.39%	10.79%	16.18%	32.7	36.2
Lu, ppm	0.31	0.022	0.27	0.35	0.24	0.37	6.96%	13.92%	20.89%	0.29	0.32
Mg, wt. %	2.11	0.105	1.90	2.32	1.79	2.42	4.97%	9.94%	14.91%	2.00	2.21
Mn, wt. %	0.115	0.004	0.107	0.122	0.103	0.126	3.33%	6.66%	9.99%	0.109	0.120
Mo, ppm	1.21	0.15	0.92	1.51	0.78	1.65	12.07%	24.14%	36.21%	1.15	1.28
Na, wt. %	0.191	0.012	0.168	0.215	0.156	0.226	6.10%	12.19%	18.29%	0.182	0.201
Nb, ppm	11.1	1.03	9.0	13.1	8.0	14.2	9.34%	18.68%	28.03%	10.5	11.6

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
4-Acid Digestion continued											
Nd, ppm	30.8	1.66	27.5	34.1	25.8	35.7	5.38%	10.76%	16.14%	29.2	32.3
Ni, ppm	29.7	2.08	25.6	33.9	23.5	35.9	6.99%	13.98%	20.97%	28.2	31.2
P, wt. %	0.056	0.003	0.049	0.062	0.046	0.065	5.81%	11.61%	17.42%	0.053	0.058
Pb, ppm	209	8	193	225	185	233	3.82%	7.64%	11.46%	198	219
Pr, ppm	8.25	0.365	7.52	8.98	7.15	9.34	4.43%	8.86%	13.29%	7.83	8.66
Rb, ppm	119	9	101	136	92	145	7.49%	14.98%	22.47%	113	124
Re, ppb	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt. %	1.75	0.106	1.54	1.96	1.43	2.07	6.09%	12.17%	18.26%	1.66	1.84
Sb, ppm	1.65	0.159	1.34	1.97	1.18	2.13	9.62%	19.24%	28.86%	1.57	1.74
Sc, ppm	11.3	1.3	8.8	13.9	7.5	15.2	11.36%	22.72%	34.08%	10.8	11.9
Se, ppm	15.7	1.50	12.7	18.7	11.2	20.2	9.54%	19.07%	28.61%	14.9	16.5
Sm, ppm	5.80	0.486	4.83	6.78	4.35	7.26	8.38%	16.76%	25.13%	5.51	6.09
Sn, ppm	20.7	1.02	18.7	22.8	17.7	23.8	4.92%	9.83%	14.75%	19.7	21.8
Sr, ppm	28.3	1.17	26.0	30.6	24.8	31.8	4.13%	8.26%	12.40%	26.9	29.7
Ta, ppm	0.86	0.078	0.71	1.02	0.63	1.10	9.07%	18.15%	27.22%	0.82	0.91
Tb, ppm	0.71	0.063	0.58	0.84	0.52	0.90	8.86%	17.73%	26.59%	0.67	0.75
Te, ppm	< 0.1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	13.9	1.04	11.8	16.0	10.8	17.0	7.47%	14.93%	22.40%	13.2	14.6
Ti, wt. %	0.328	0.025	0.279	0.378	0.255	0.402	7.49%	14.97%	22.46%	0.312	0.345
Tl, ppm	0.67	0.039	0.59	0.75	0.55	0.78	5.80%	11.60%	17.41%	0.64	0.70
Tm, ppm	0.32	0.03	0.26	0.39	0.22	0.42	10.43%	20.87%	31.30%	0.31	0.34
U, ppm	2.60	0.160	2.28	2.92	2.12	3.08	6.17%	12.34%	18.51%	2.47	2.73
V, ppm	78	5.3	67	88	62	93	6.78%	13.55%	20.33%	74	81
W, ppm	7.74	0.758	6.23	9.26	5.47	10.02	9.80%	19.59%	29.39%	7.36	8.13
Y, ppm	20.0	1.40	17.2	22.8	15.8	24.2	7.02%	14.03%	21.05%	19.0	21.0
Yb, ppm	1.98	0.107	1.76	2.19	1.65	2.30	5.44%	10.87%	16.31%	1.88	2.08
Zn, ppm	716	36	645	788	609	824	5.00%	9.99%	14.99%	681	752
Zr, ppm	97	9.4	78	116	69	125	9.64%	19.28%	28.92%	92	102
Aqua Regia Digestion											
Ag, ppm	3.90	0.37	3.16	4.64	2.79	5.01	9.51%	19.02%	28.52%	3.70	4.09
Al, wt. %	3.14	0.130	2.88	3.40	2.75	3.53	4.14%	8.29%	12.43%	2.99	3.30
As, ppm	15.8	1.21	13.4	18.2	12.2	19.4	7.67%	15.33%	23.00%	15.0	16.6

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Au, ppb	< 10	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
B, ppm	< 10	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ba, ppm	39.8	3.79	32.2	47.4	28.5	51.2	9.51%	19.03%	28.54%	37.8	41.8
Be, ppm	0.51	0.040	0.43	0.59	0.39	0.63	7.79%	15.57%	23.36%	0.49	0.54
Bi, ppm	59	4.1	50	67	46	71	7.01%	14.03%	21.04%	56	62
Ca, wt. %	0.287	0.008	0.272	0.302	0.265	0.310	2.63%	5.26%	7.89%	0.273	0.302
Cd, ppm	0.97	0.043	0.88	1.06	0.84	1.10	4.43%	8.86%	13.28%	0.92	1.02
Ce, ppm	45.4	7.0	31.3	59.5	24.2	66.5	15.54%	31.08%	46.61%	43.1	47.6
Co, ppm	28.6	1.14	26.4	30.9	25.2	32.1	3.98%	7.96%	11.94%	27.2	30.1
Cr, ppm	39.2	1.80	35.7	42.8	33.9	44.6	4.58%	9.15%	13.73%	37.3	41.2
Cs, ppm	1.47	0.18	1.12	1.82	0.94	1.99	11.96%	23.91%	35.87%	1.39	1.54
Cu, wt. %	1.06	0.039	0.99	1.14	0.95	1.18	3.66%	7.32%	10.98%	1.01	1.12
Dy, ppm	2.25	0.44	1.36	3.14	0.92	3.58	19.72%	39.44%	59.16%	2.14	2.36
Er, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Eu, ppm	0.69	0.12	0.44	0.93	0.31	1.06	18.04%	36.09%	54.13%	0.65	0.72
Fe, wt. %	7.93	0.332	7.26	8.59	6.93	8.92	4.19%	8.38%	12.56%	7.53	8.33
Ga, ppm	9.11	0.592	7.93	10.29	7.34	10.89	6.49%	12.99%	19.48%	8.66	9.57
Gd, ppm	3.18	0.65	1.88	4.48	1.23	5.13	20.46%	40.93%	61.39%	3.02	3.33
Ge, ppm	< 0.3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	< 0.8	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hg, ppm	< 0.13	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ho, ppm	< 0.6	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
In, ppm	1.00	0.062	0.88	1.12	0.81	1.18	6.20%	12.40%	18.59%	0.95	1.05
K, wt. %	0.230	0.027	0.176	0.285	0.148	0.312	11.89%	23.78%	35.66%	0.219	0.242
La, ppm	22.7	2.5	17.6	27.8	15.1	30.4	11.21%	22.42%	33.63%	21.6	23.9
Li, ppm	28.3	2.57	23.1	33.4	20.6	36.0	9.08%	18.16%	27.24%	26.9	29.7
Lu, ppm	< 0.2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Mg, wt. %	1.92	0.089	1.74	2.09	1.65	2.18	4.66%	9.32%	13.98%	1.82	2.01
Mn, wt. %	0.101	0.005	0.091	0.112	0.086	0.117	5.12%	10.24%	15.36%	0.096	0.107
Mo, ppm	1.07	0.12	0.83	1.31	0.71	1.43	11.24%	22.48%	33.73%	1.02	1.13
Na, wt. %	0.011	0.001	0.008	0.013	0.007	0.015	12.90%	25.80%	38.71%	0.010	0.011
Nb, ppm	< 0.5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Aqua Regia Digestion continued											
Nd, ppm	20.5	3.2	14.2	26.9	11.0	30.0	15.41%	30.83%	46.24%	19.5	21.6
Ni, ppm	28.0	1.50	25.0	31.0	23.5	32.5	5.37%	10.74%	16.10%	26.6	29.4
P, wt. %	0.054	0.003	0.047	0.060	0.044	0.064	6.23%	12.45%	18.68%	0.051	0.056
Pb, ppm	203	9	185	221	175	230	4.51%	9.02%	13.52%	193	213
Pr, ppm	5.18	1.02	3.13	7.23	2.11	8.25	19.78%	39.56%	59.34%	4.92	5.44
Rb, ppm	14.7	2.4	10.0	19.4	7.6	21.8	16.06%	32.12%	48.18%	14.0	15.4
Re, ppb	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
S, wt. %	1.67	0.117	1.44	1.90	1.32	2.02	7.01%	14.03%	21.04%	1.59	1.75
Sb, ppm	< 1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Sc, ppm	3.87	0.375	3.12	4.62	2.75	5.00	9.69%	19.38%	29.06%	3.68	4.07
Se, ppm	15.3	1.41	12.5	18.2	11.1	19.6	9.21%	18.41%	27.62%	14.6	16.1
Sm, ppm	3.81	0.64	2.53	5.08	1.90	5.71	16.72%	33.45%	50.17%	3.62	4.00
Sn, ppm	12.2	0.62	10.9	13.4	10.3	14.0	5.11%	10.21%	15.32%	11.6	12.8
Sr, ppm	12.4	0.57	11.2	13.5	10.6	14.1	4.62%	9.24%	13.86%	11.7	13.0
Ta, ppm	< 0.05	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tb, ppm	< 0.6	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Te, ppm	< 0.07	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Th, ppm	12.0	1.11	9.8	14.2	8.7	15.3	9.27%	18.53%	27.80%	11.4	12.6
Ti, wt. %	< 0.15	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Tl, ppm	0.13	0.02	0.09	0.17	0.07	0.19	15.90%	31.80%	47.70%	0.12	0.14
Tm, ppm	< 0.3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
U, ppm	1.55	0.19	1.17	1.92	0.98	2.11	12.18%	24.35%	36.53%	1.47	1.62
V, ppm	34.1	1.92	30.3	38.0	28.4	39.9	5.64%	11.27%	16.91%	32.4	35.9
W, ppm	4.23	0.82	2.59	5.86	1.77	6.68	19.36%	38.72%	58.07%	4.01	4.44
Y, ppm	10.0	1.7	6.7	13.4	5.0	15.1	16.67%	33.35%	50.02%	9.5	10.5
Yb, ppm	< 1.5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Zn, ppm	717	28	661	774	633	802	3.93%	7.85%	11.78%	681	753
Zr, ppm	20.1	3.4	13.4	26.8	10.0	30.1	16.71%	33.43%	50.14%	19.1	21.1
Peroxide Fusion ICP											
Al, wt. %	6.46	0.254	5.96	6.97	5.70	7.23	3.93%	7.86%	11.79%	6.14	6.79
As, ppm	< 20	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
B, ppm	< 20	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion ICP continued											
Ba, ppm	320	14	293	347	279	361	4.25%	8.50%	12.75%	304	336
Be, ppm	< 2	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Bi, ppm	62	3.8	54	69	50	73	6.13%	12.26%	18.39%	59	65
Ca, wt.%	0.431	0.074	0.284	0.578	0.210	0.652	17.08%	34.15%	51.23%	0.410	0.453
Cd, ppm	< 1.1	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Ce, ppm	73	3.2	66	79	63	82	4.37%	8.74%	13.11%	69	76
Co, ppm	31.0	2.30	26.3	35.6	24.0	37.9	7.44%	14.87%	22.31%	29.4	32.5
Cr, ppm	< 80	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Cs, ppm	5.53	0.395	4.74	6.32	4.34	6.71	7.15%	14.30%	21.45%	5.25	5.80
Cu, wt.%	1.09	0.052	0.99	1.19	0.93	1.25	4.79%	9.57%	14.36%	1.04	1.14
Dy, ppm	4.65	0.220	4.21	5.09	3.99	5.31	4.72%	9.45%	14.17%	4.42	4.89
Er, ppm	2.62	0.233	2.15	3.09	1.92	3.32	8.92%	17.83%	26.75%	2.49	2.75
Eu, ppm	1.15	0.087	0.98	1.32	0.89	1.41	7.55%	15.10%	22.64%	1.09	1.21
Fe, wt.%	8.81	0.268	8.27	9.34	8.01	9.61	3.04%	6.07%	9.11%	8.37	9.25
Ga, ppm	18.5	1.21	16.1	20.9	14.9	22.2	6.55%	13.10%	19.64%	17.6	19.4
Gd, ppm	5.43	0.529	4.38	6.49	3.85	7.02	9.73%	19.46%	29.19%	5.16	5.71
Ge, ppm	< 3	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Hf, ppm	4.25	0.414	3.42	5.08	3.01	5.49	9.73%	19.46%	29.19%	4.04	4.46
Ho, ppm	0.93	0.075	0.78	1.08	0.71	1.16	8.00%	15.99%	23.99%	0.89	0.98
In, ppm	1.13	0.079	0.97	1.29	0.89	1.36	7.03%	14.06%	21.09%	1.07	1.18
K, wt.%	1.81	0.080	1.65	1.97	1.57	2.05	4.39%	8.78%	13.16%	1.72	1.90
La, ppm	38.0	2.35	33.3	42.7	30.9	45.0	6.20%	12.40%	18.60%	36.1	39.9
Li, ppm	32.2	2.30	27.6	36.8	25.3	39.1	7.16%	14.32%	21.48%	30.6	33.8
Lu, ppm	0.40	0.05	0.29	0.51	0.24	0.56	13.73%	27.47%	41.20%	0.38	0.42
Mg, wt.%	2.12	0.071	1.98	2.26	1.91	2.33	3.34%	6.69%	10.03%	2.01	2.23
Mn, wt.%	0.120	0.006	0.107	0.133	0.101	0.140	5.40%	10.81%	16.21%	0.114	0.126
Mo, ppm	< 1.5	IND	IND	IND	IND	IND	IND	IND	IND	IND	IND
Nb, ppm	12.0	2.1	7.7	16.3	5.6	18.5	17.88%	35.76%	53.63%	11.4	12.6
Nd, ppm	31.8	1.73	28.3	35.2	26.6	36.9	5.43%	10.86%	16.29%	30.2	33.4
Ni, ppm	30.2	4.8	20.7	39.7	15.9	44.5	15.78%	31.55%	47.33%	28.7	31.7
P, wt.%	0.057	0.006	0.046	0.068	0.040	0.074	9.87%	19.74%	29.60%	0.054	0.060
Pb, ppm	214	11	191	237	180	248	5.35%	10.70%	16.06%	203	225

Table 3 continued.

Constituent	Certified Value	Absolute Standard Deviations					Relative Standard Deviations			5% window	
		1SD	2SD Low	2SD High	3SD Low	3SD High	1RSD	2RSD	3RSD	Low	High
Peroxide Fusion ICP continued											
Pr, ppm	8.83	0.367	8.10	9.56	7.73	9.93	4.15%	8.31%	12.46%	8.39	9.27
Rb, ppm	122	3	117	127	114	129	2.05%	4.11%	6.16%	116	128
S, wt. %	1.78	0.049	1.68	1.88	1.63	1.93	2.75%	5.51%	8.26%	1.69	1.87
Sb, ppm	1.74	0.28	1.18	2.30	0.90	2.57	16.09%	32.18%	48.27%	1.65	1.82
Sc, ppm	10.4	0.48	9.4	11.3	8.9	11.8	4.62%	9.24%	13.85%	9.9	10.9
Si, wt. %	29.44	1.011	27.41	31.46	26.40	32.47	3.44%	6.87%	10.31%	27.96	30.91
Sm, ppm	5.88	0.396	5.09	6.67	4.69	7.07	6.73%	13.47%	20.20%	5.58	6.17
Sn, ppm	23.8	3.0	17.7	29.8	14.7	32.9	12.73%	25.46%	38.19%	22.6	25.0
Sr, ppm	31.0	6.1	18.7	43.3	12.6	49.4	19.77%	39.55%	59.32%	29.5	32.6
Ta, ppm	0.97	0.093	0.79	1.16	0.70	1.25	9.54%	19.08%	28.61%	0.93	1.02
Tb, ppm	0.77	0.057	0.65	0.88	0.60	0.94	7.46%	14.91%	22.37%	0.73	0.81
Th, ppm	14.2	0.54	13.2	15.3	12.6	15.8	3.77%	7.54%	11.31%	13.5	14.9
Ti, wt. %	0.352	0.022	0.309	0.395	0.287	0.417	6.15%	12.31%	18.46%	0.334	0.369
Tl, ppm	0.73	0.09	0.54	0.91	0.45	1.00	12.67%	25.34%	38.01%	0.69	0.76
Tm, ppm	0.39	0.05	0.29	0.49	0.24	0.54	12.77%	25.54%	38.31%	0.37	0.41
U, ppm	2.79	0.178	2.43	3.15	2.26	3.32	6.39%	12.78%	19.17%	2.65	2.93
V, ppm	77	5.6	66	88	60	94	7.25%	14.50%	21.75%	73	81
W, ppm	7.99	1.28	5.43	10.55	4.15	11.83	16.01%	32.01%	48.02%	7.59	8.39
Y, ppm	24.2	0.80	22.6	25.8	21.8	26.6	3.31%	6.61%	9.92%	23.0	25.4
Yb, ppm	2.45	0.186	2.08	2.83	1.90	3.01	7.56%	15.12%	22.67%	2.33	2.58
Zn, ppm	750	36	678	822	642	858	4.79%	9.58%	14.36%	713	788

Note: intervals may appear asymmetric due to rounding

PREPARER AND SUPPLIER OF THE REFERENCE MATERIAL

Reference material OREAS 927 has been prepared and certified by:

ORE Research & Exploration Pty Ltd
 37A Hosie Street
 Bayswater North VIC 3153
 AUSTRALIA

Tel: +613-9729 0333
 Fax: +613-9729 8338
 Web: www.ore.com.au
 Email: info@ore.com.au

It has been packaged in 10g units in laminated foil pouches.

INTENDED USE

OREAS 927 is intended for the following uses:

- for the monitoring of laboratory performance in the analysis of geological samples for the analytes reported in Table 1;
- for the verification of analytical methods for analytes reported in Table 1;
- for the calibration of instruments used in the determination of the concentration of analytes reported in Table 1.

STABILITY AND STORAGE INSTRUCTIONS

OREAS 927 has been prepared from mineralised and altered carbonaceous siltstones and mudstones from the CSA mine located near the town of Cobar in central western New South Wales, Australia. It has been packaged in robust foil laminate pouches and under normal storage conditions has long-term stability beyond 10 years.

INSTRUCTIONS FOR THE CORRECT USE OF THE REFERENCE MATERIAL

The certified values for OREAS 927 refer to the concentration level in its packaged state. It should not be dried prior to weighing and analysis.

HANDLING INSTRUCTIONS

Fine powders pose a risk to eyes and lungs and therefore standard precautions such as the use of safety glasses and dust masks are advised.

LEGAL NOTICE

Ore Research & Exploration Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of its ability. The Purchaser by receipt hereof releases and indemnifies Ore Research & Exploration Pty Ltd from and against all liability and costs arising from the use of this material and information.

CERTIFYING OFFICER

Craig Hamlyn (B.Sc. Hons - Geology), Technical Manager – (ORE P/L)

REFERENCES

ISO Guide 3207 (1975), Statistical interpretation of data - Determination of a statistical tolerance interval.

ISO Guide 35 (2006), Certification of reference materials - General and statistical principals.